



Industry
Canada / Industrie
Canada


Canada

strategis.gc.ca

Strategis Index:

A B C D E F G H I J K L M N O P Q R S T U V W X Y Z

CIPO OPIC



Canadian Patents Database

01/09/2002 - 09:19:44

(1) CA 343080

(12) **Patent:**

(54) ALIPHATIC COMPOUND MANUFACTURE

(54) FABRICATION DE COMPOSES ALIPHATIQUES

Patent Information

(72) Inventors (Country): HENRY DREYFUS (Not Available)

(73) Owners (Country): HENRY DREYFUS

(71) Applicants (Country):

(74) Agent:

(45) Issued on: July 17, 1934

(22) Filed on:

(43) Laid open on:

(52) Canadian Class (CPC): 260/753

(51) International Class (IPC): N/A

Patent Cooperation Treaty (PCT): No

(30) Application priority data: None

Availability of licence: N/A

Language of filing: Unknown

ABSTRACT:

CLAIMS: [Show all claims](#)

*** Note: Data on abstracts and claims is shown in the official language in which it was submitted.

View or Download Images :

- Cover Page Image
- Abstract Image
- Claims Image
- Disclosures Image
- Drawings Image

This invention relates to the manufacture of aliphatic compounds and particularly of oxygenated organic compounds from oxides of carbon and hydrogen, or alternatively from compounds synthesised therefrom, e.g. methyl alcohol, mixed or not with oxides of carbon and/or hydrogen.

In a series of researches upon the production of organic compounds by the hydrogenation of oxides of carbon I have found that valuable products are obtainable by utilising catalysts consisting of or containing the compounds of the metals of Groups 1 and 2 of the Periodic System with the oxy acids of the elements of the 2nd, 3rd, 4th and 5th Groups. In particular I have found that the alkali or alkaline earth and copper borates, aluminates, zincates, silicates and phosphates are good catalysts for the production of oxygenated organic compounds from oxides of carbon and hydrogen. The invention is however not limited to these particular salts but comprises also the use of alkali or alkaline earth or copper plumbates, stannates, titanates, tantalates, niobates or vanadates or other salts of oxy acids of the elements of the 2nd, 3rd, 4th and 5th Groups of the Periodic System. Furthermore other metals of Groups 1 and 2 of the Periodic System may be used as the basic radicle. Initially the basic radicle, e.g. sodium, potassium, calcium, barium, magnesium or copper, may be present in the form of a salt of any of the oxy acids referred to above, for example in the form of ortho, pyro, or meta phosphates, or in the form of phosphites or hypophosphites or in the form of ortho or meta silicates.

The compounds may contain the basic and the acid radicles in any convenient proportion. An excess of basic radicle over the acid radicle or of acid radicle over basic radicle sometimes

materially alters the direction of the reaction. Generally excess of the acid radicle tends to produce products of higher degree of oxidation than alcohols, such for example as acids, whereas excess of the basic radicle tends to confine the reaction to the production of aliphatic alcohols. The proportion may for example be one molecular proportion of basic radicle to two proportions of acid radicle, or equal molecular proportions may be used, or one molecular proportion of basic radicle may be used to two molecular proportions of acid radicle. Furthermore intermediate proportions or proportions outside those indicated may be used. The excess of basic or acid radicle may be present in a combined state, as for example in a basic or acid salt, or the excess of the base or of the acid may be present merely in admixture or association with the normal salt.

Copper containing catalysts are advantageously used in conjunction with compounds of the alkalies or alkaline earth metals, for instance compounds of the oxy acids referred to above. Here again the relative proportion of alkali or alkaline earth metal to copper may be varied as desired. For example proportions of 1:2, 1:1 or 2:1 molecules of alkali or alkaline earth metal to copper may be employed.

The catalysts of the present invention may be used alone or in admixture or chemical combination with each other and/or in admixture or chemical combination, e.g. as double salts, with other metals, for example aluminium, chromium, manganese, molybdenum, vanadium, tungsten or uranium or with two or more of such other metals. The other metals are preferably present in the form of compounds and may be present in the form of compounds of the oxy acids previously referred to. If used in such form they may be present as double salts with the metals, the use of which is particularly contemplated by the present invention.

The present invention is not restricted to the use of the metals of Groups 1 and 2 of the Periodic System in the form of simple borates, aluminates, zincates, silicates or phosphates or other salts of oxy acids of the 2nd, 3rd, 4th and 5th Groups of the Periodic System. It further comprises their use in the form of complex salts containing these oxy acids, for example in the form of boro-silicates, boro-tungstates, titano-silicates, phospho-molybdates, phospho-tungstates, phospho-vanadates, silico-molybdates, silico-tungstates, phospho-tungsto-silicates, phospho-molybdo-silicates, phospho-tungsto-molybdates etc.

Reacting gases of varying composition may be employed for the purpose of the present invention, for example reacting gases containing two or more volumes of carbon monoxide or dioxide to one volume of hydrogen, or equal volumes of the oxide of carbon and of hydrogen, or one volume of carbon monoxide or dioxide to two or more volumes of hydrogen, or mixtures containing intermediate proportions. Mixtures of carbon monoxide and dioxide may of course be employed. It is not necessary to utilise pure reacting gases since mixtures containing the desired reacting gases may be employed, for example coke oven gas, producer gas, water gas and the like. The proportions of reacting gases in such industrial gases may be adjusted, if desired, by suitable additions. The reacting gases may contain inert gases, such as nitrogen, or they may contain hydrocarbons, for example methane or other paraffins. The methane or other hydrocarbons may be used as an addition to the reacting gases or may be used wholly or partly in the place of the hydrogen, this modification forming an important feature of the present invention. Steam may moreover be used in addition to or wholly or partly in place of the oxide of carbon.

The actual hydrogenation of the oxides of carbon may be conducted at any suitable temperatures, for example temperatures ranging from 200 to 250°C. to 400 or 500 or even 600°C. or more, but preferably the temperatures used are between 250° and 400°C. and particularly 250° to 300° to 350°C. The reaction is preferably carried out under pressure, for example pressures of 50, 100, 200, 300 or 500 atmospheres or more.

According to a modification of the invention instead of employing oxides of carbon in conjunction with hydrogen the oxygenated organic compounds obtained from such a synthesis, for example methyl or ethyl alcohol or other alcohols, may be used. In this modification of the invention methyl alcohol, for example, can be converted into compounds of higher order, for example into ethyl alcohol, acetaldehyde, acetic acid etc. The alcohols or other compounds may be used alone or in conjunction with carbon monoxide, carbon dioxide and/or hydrogen. The use of hydrogen generally tends to produce higher alcohols, e.g. ethyl alcohol, propyl alcohol and higher alcohols to the exclusion of compounds of a higher order of oxidation, e.g. aldehydes, acids, ketones, whilst the use of carbon dioxide is effective in promoting the formation of such bodies of higher order of oxidation. In cases, however, where the catalyst contains excess or substantial excess of acid radicle over basic radicle the reaction tends to produce products of a higher order of oxidation, e.g. acids and aldehydes even in the presence of hydrogen. The vapours of the methyl alcohol or other compound may be passed with or without carbon monoxide or dioxide and with or without hydrogen over the catalysts of the present invention contained in a heated reaction vessel. The methyl or ethyl alcohol or other compound may furthermore be prepared in a preliminary operation continuously with its

use according to the present invention. For such continuous operation mixtures of carbon monoxide or dioxide and hydrogen or gases containing them may, for example, be passed through the reaction chamber containing zinc oxide or basic zinc chromate or other catalysts or catalyst mixtures capable of producing the methyl alcohol or other compound, and the resulting gases or vapours passed directly over the catalysts or catalyst mixtures of the present invention. Instead of using methyl alcohol or other compound obtainable from carbon monoxide or dioxide and hydrogen, compounds capable of yielding the methyl alcohol or other compound may be used, for example methyl formate, methyl acetate or dimethyl ether.

The reactions according to the present invention may be effected in any suitable reaction chambers or vessels, for example copper vessels or copper lined vessels or steel vessels, and particularly vessels made of steel containing molybdenum, tungsten, manganese, cobalt, nickel or the like.

The following examples serve to illustrate convenient forms of execution of the invention, it being understood that they are given only by way of illustration and are in no way limitative.

Example 1.

Water gas containing about 30% of carbon monoxide and 65% hydrogen is passed under a pressure of between 50 and 150 atmospheres in contact with a catalyst composed of a mixture of copper meta phosphate and sodium phosphate (e.g. containing about 5 - 10% sodium phosphate) heated to a temperature between 250° and 350°C.

There results a copious yield of ethanol and other higher aliphatic alcohols.

in place of this catalyst there is employed a catalyst containing an excess of acid radicle over basic radicle and containing no alkali salt, e.g. a catalyst composed of a mixture of 1 molecular equivalent of copper meta phosphate and 1 molecular equivalent of phosphoric acid, the reaction gases are largely or entirely converted to compounds of a higher degree of oxidation including acetic acid, methyl acetate, acetaldehyde and higher acids and aldehydes.

Example 2.

Methanol or a mixture of methanol and carbon monoxide are passed under a pressure of between 100 and 300 atmospheres in contact with copper meta borate heated to a temperature between 250° and 350 C.

There results a copious yield of ethanol and other higher aliphatic alcohols, together with aldehydes, acids, and ketones.

If the carbon monoxide is wholly or partly replaced by hydrogen and particularly if the carbon monoxide is wholly replaced, the reaction products are substantially free from acids, aldehydes and ketones. If, however, the carbon monoxide is replaced by carbon dioxide, formation of the compounds of a higher order of oxidation is materially increased, whilst if, besides replacing the carbon monoxide with carbon dioxide, there is employed a catalyst containing an excess of acid radicle over basic radicle, e. g. a mixture of 1 molecular equivalent of copper meta borate and 1 molecular equivalent of phosphoric acid, the reaction product consists largely or entirely of acetic acid, methyl acetate, acetaldehyde and higher acids, aldehydes and esters.

By the unqualified term "manufacture of oxygenated organic compounds" I mean the manufacture of such compounds from oxides of carbon and hydrogen or from compounds synthesized therefrom, e.g. methyl alcohol mixed or not with oxides of carbon and/or hydrogen.

What I claim is:

1. Process for the manufacture of oxygenated organic compounds from oxides of carbon and hydrogen or compounds synthesized therefrom characterized in that the reaction is performed in the presence of catalysts consisting of alkali or alkaline earth or copper borates, silicates or phosphates or salts of other oxyacids of phosphorous.

2. Process for the manufacture of oxygenated organic compounds from oxides of carbon and hydrogen, characterized in that the reaction is performed in the presence of catalysts consisting of alkali or alkaline earth or copper borates, silicates or phosphates or salts of other oxyacids of phosphorous.

3. Process according to claim 1, wherein the acid and basic radicals in the catalysts are present in non-equivalent proportions.

4. Process according to claim 1, wherein the catalysts contain an excess of acid radicle over the normal content, which excess is present as an acid salt or in the free state in association with the normal salt.

5. Process according to claim 2, wherein the acid and basic radicals in the catalysts are present in non-equivalent proportions.

6. Process according to claim 2, wherein the catalysts contain an excess of acid radicle over the normal content, which excess is present as an acid salt or in the free state in association with the normal salt.

7. Process according to claim 1 and wherein the reaction is performed at temperatures between 250° and 400°C . and pressures of 50 - 200 or more atmospheres.

8. Process according to claim 2 and wherein the reaction is performed at temperatures between 250° and 400°C . and pressures of 50 - 200 or more atmospheres.

9. Process for the manufacture of oxygenated organic compounds which comprises passing water gas at a temperature between 250° and 300°C . and under pressure of between 50 - 150

343080

atmospheres over a catalyst composed of a mixture of copper metaphosphate and sodium phosphate.

~~Signed at London, England, this tenth day of July, 1950.~~

~~(C) HENRY DREYFUS~~