

APPENDIX D

Slurry Bubble Column Reactor Data

Table I

SUMMARY OF H3 SBCR RUN RESULTS

a) Unless otherwise noted, total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.

b) Conversion is total CO conversion over the period (%).

c) Conversion and selectivities are calculated using H2 as an internal standard in the GC analysis of the offgas.

d) Prod. rate: Rate for production of total hydrocarbons, C1+ (kg/kg cat., hr).

e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Per No	Time Start	Time Stop	Temp C	Pres psi	H2: CO	Synfl cc/hr	Conv. %	Prod. Rate	Selectivities %CH4	%C2	%C3+	%CO2	Alpha GC	Alpha Liq	Olefin/Paraf C3	C4	Olefins C6-18, %	Comments
2	CO.001	16.5	1	162	177	225	450	2.0	20	15.9	0.70	2.3	0.8	96.4	0.53	0.98	0.88	5.00	2.27	25.2	
2	CO.001	16.5	2	202	228	200	450	2.0	20	3.9	0.17	0.0	0.0	99.9	0.00	0.81	0.91	0.00	0.00	21.7	
2	CO.001	16.5	3	254	280	240	450	2.0	20	30.9	1.36	11.7	1.8	85.5	1.04	0.87	0.77	2.63	1.64	22.4	
2	CO.001	16.5	4	302	323	225	450	1.2	20	9.9	0.59	0.7	0.3	98.4	0.67	0.76	0.90	0.00	7.14	29.4	
2	CO.001	16.5	5	350	372	225	450	2.0	20	15.3	0.68	6.0	1.0	92.5	0.49	0.84	0.88	4.00	2.70	23.1	
2	CO.001	16.5	6	398	420	225	300	2.0	20	12.5	0.55	6.1	1.1	92.2	0.63	0.79	0.86	4.35	2.86	21.7	
2	CO.001	16.5	7	446	468	240	300	2.0	20	22.9	1.02	16.5	0.8	81.5	1.16	0.71	0.79	3.03	1.79	22.4	
2	CO.001	16.5	8	494	516	240	600	2.0	20	29.9	1.33	12.6	1.6	85.0	0.84	0.76	0.82	2.63	1.69	22.4	
2	CO.001	16.5	9	517	540	240	600	2.0	0	29.5	1.31	12.0	1.7	85.3	0.96	0.76	--	2.50	1.56	22.4	
2	CO.001	16.5	9	541	564	240	600	2.0	0	28.4	1.26	10.4	1.7	87.1	0.89	0.77	--	3.03	1.72	--	
2	CO.001	16.5	9	565	588	240	600	2.0	0	27.9	1.27	11.1	1.7	86.2	0.93	0.76	--	3.03	1.72	--	
2	CO.001	16.5	9	589	612	240	600	2.0	0	27.0	1.20	10.7	1.7	86.7	0.89	0.76	0.82	2.78	2.00	--	
2	CO.001	16.5	10	637	660	240	600	2.0	20	26.4	1.17	11.0	1.7	86.4	0.85	0.77	0.83	2.86	1.96	22.4	G.C. Calib
2	CO.001	16.5	11	684	706	225	450	2.0	20	11.6	0.51	5.4	1.0	93.0	0.61	0.81	0.87	5.26	3.45	23.8	
3	CO.005	19.5	1	12	36	240	450	2.0	20	33.2	1.23	5.6	1.6	91.8	1.06	0.80	0.81	2.04	1.27	23.1	G.C. Calib
3	CO.005	19.5	2	60	84	220	450	2.0	20	15.0	0.56	2.9	0.6	96.2	0.24	0.86	0.87	4.55	3.23	21.7	
3	CO.005	19.5	3	108	132	240	450	1.2	20	18.5	0.94	6.9	1.0	91.3	0.85	0.81	--	5.88	3.85	26.6	
3	CO.005	19.5	4	156	179	240	450	2.0	20	29.6	1.11	11.5	1.8	85.8	0.91	0.76	0.78	2.22	1.39	21.7	
4	CO.002	20.1	1	37	59	240	450	2.0	20	36.1	1.32	22.9	3.2	72.4	1.51	0.66	0.77	0.65	0.31	16.8	
4	CO.002	20.1	2	85	106	220	450	2.0	20	16.6	0.60	3.8	1.1	94.7	0.35	0.84	0.88	2.44	0.89	--	
4	CO.002	20.1	3	133	149	210	600	1.0	20	5.2	0.28	0.0	0.0	99.1	0.87	0.89	0.94	0.00	0.00	--	Power Fail
5	CO.003	15.1	1	15	35	240	450	2.0	20	31.7	1.53	16.7	2.4	79.8	1.16	0.71	--	1.30	0.60	18.2	G.C. Calib
5	CO.003	15.1	2	61	83	220	450	2.0	20	13.2	0.63	5.1	1.0	93.4	0.51	0.82	0.90	4.55	1.89	--	
5	CO.003	15.1	3	88	107	240	450	2.0	20	28.4	1.37	15.1	2.4	81.4	1.11	0.75	--	1.45	0.97	--	
5	CO.003	15.1	4	133	155	240	450	1.0	20	13.1	0.95	4.2	1.2	93.3	1.24	0.83	0.88	6.67	3.70	--	
5	CO.003	15.1	5	181	203	240	600	1.0	20	13.4	0.97	3.9	1.1	93.7	1.30	0.81	--	5.26	3.45	30.1	
5	CO.003	15.1	6	217	227	240	450	2.0	20	25.4	1.23	14.9	2.4	81.7	1.03	0.73	--	1.89	1.19	--	
6	CO.011	15.3	1	13	35	240	450	2.0	20	14.3	0.67	7.6	1.6	89.4	1.42	0.78	0.83	4.17	2.57	21.7	
6	CO.011	15.3	2	61	83	220	450	2.0	20	5.1	0.23	0.0	0.0	97.2	2.78	0.87	0.82	--	--	--	
6	CO.011	15.3	3	88	107	240	450	2.0	20	13.5	0.63	5.4	1.7	91.1	1.86	0.79	--	4.00	2.83	--	
6	CO.011	15.3	4	133	155	240	450	1.0	20	6.3	0.44	0.4	1.0	95.5	3.05	0.82	0.88	--	--	--	
6	CO.011	15.3	5	181	203	240	600	1.0	20	6.7	0.46	0.2	0.9	96.0	2.91	0.84	0.89	12.00	3.67	27.3	G.C. Calib
6	CO.011	15.3	6	217	226	240	450	2.0	20	12.0	0.57	5.9	1.8	90.4	1.91	0.78	--	4.40	2.43	--	

Table I
(Continued)

SUMMARY OF M3 SBCR RUN RESULTS

a)Unless otherwise noted, total flow is ca.15 L/min. STP, or 3 cm/sec linear gas flow.

b)Conversion is total CO conversion over the period (%).

c)Conversion and selectivities are calculated using N2 as an internal standard in the GC analysis of the offgas.

d)Prod. rate: Rate for production of total hydrocarbons,C1+ (kg/kg cat.,hr).

e)Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt,g	Per No	Time Start	Time Stop	Temp C	Pres psi	H2: CO	Synfl cc/hr	Conv. %	Prod. Rate	Selectivities				Alpha GC	Alpha Liq	Olefin/Paraf		Olefins C6-18,%	Comments
												%CH4	%C2	%C3+	%CO2			C3	C4		
7	CO.012	15.8	1	14	36	240	450	2.0	20	13.9	0.63	6.1	1.5	90.6	1.74	0.80	0.89	4.00	2.57	17.5	
7	CO.012	15.8	2	62	84	220	450	2.0	20	5.1	0.23	0.0	0.2	97.8	2.02	0.89	0.90	--	2.50	--	
7	CO.012	15.8	3	88	92	240	450	2.0	20	13.1	0.59	6.1	1.7	90.4	1.75	0.80	--	5.00	2.25	--	Power Fail
7	CO.012	15.8	4	134	156	240	450	1.0	20	3.9	0.26	4.8	2.3	86.3	6.64	0.70	0.85	16.00	3.50	--	
7	CO.012	15.8	5	182	204	240	600	1.0	20	4.3	0.28	0.1	2.1	91.6	9.29	0.75	0.82	8.50	3.50	30.8	
7	CO.012	15.8	6	218	227	240	450	2.0	20	7.2	0.32	7.3	3.2	85.1	4.45	0.70	--	5.00	3.17	--	
8	CO.015	15.0	1	14	35	240	450	2.0	20	28.3	1.37	12.7	2.0	84.1	1.24	0.76	0.80	1.61	1.07	19.6	G.C.Calib
8	CO.015	15.0	2	61	83	220	450	2.0	20	11.5	0.56	4.4	1.0	93.9	0.80	0.81	0.89	3.60	2.14	--	
8	CO.015	15.0	3	97	106	240	450	2.0	20	26.4	1.28	13.2	2.1	83.5	1.12	0.75	--	1.69	1.20	--	
8	CO.015	15.0	4	133	155	240	450	1.0	20	11.5	0.83	4.8	1.2	92.5	1.53	0.80	0.85	5.60	3.29	--	
8	CO.015	15.0	5	181	191	240	600	1.0	20	12.4	0.90	4.9	0.8	93.6	0.73	0.84	0.85	5.20	3.14	30.8	Power Fail
9	CO.011	15.0	1	13	35	240	450	2.0	20	18.5	0.89	8.8	1.7	88.8	0.77	0.78	0.83	3.18	1.85	20.3	G.C.Calib
9	CO.011	15.0	2	61	82	220	450	2.0	20	6.3	0.31	0.0	1.0	98.6	0.41	0.88	0.93	12.00	1.80	--	
9	CO.011	15.0	3	97	107	240	450	2.0	20	16.6	0.80	8.4	2.1	88.7	0.81	0.77	--	3.30	2.00	--	
9	CO.011	15.0	4	133	155	240	450	1.0	20	8.0	0.58	1.3	1.3	96.3	1.16	0.82	0.87	7.00	2.83	--	
9	CO.011	15.0	5	181	203	240	600	1.0	20	8.7	0.63	1.4	1.1	96.4	1.05	0.83	0.87	5.00	2.67	30.5	
9	CO.011	15.0	6	228	229	240	450	2.0	20	14.7	0.71	7.9	2.2	89.1	0.85	0.78	--	3.78	1.67	--	Power Fail
11	CO.017	15.0	1	9	31	240	450	2.0	20	27.2	1.32	11.2	1.8	85.9	1.14	0.77	0.80	2.09	1.20	30.8	
11	CO.017	15.0	2	55	79	220	450	2.0	20	11.4	0.55	5.0	0.0	94.8	0.22	0.88	0.90	5.00	3.20	--	
11	CO.017	15.0	3	81	103	240	450	2.0	20	25.9	1.26	11.7	1.6	85.6	1.14	0.77	--	1.95	1.26	--	
11	CO.017	15.0	4	129	151	240	450	1.0	20	11.6	0.84	5.0	0.0	93.9	1.19	0.82	0.86	25.0	2.88	--	
11	CO.017	15.0	5	177	199	240	600	1.0	20	11.6	0.84	4.2	0.0	94.7	1.17	0.86	0.86	24.0	1.63	21.0	G.C.Calib
11	CO.017	15.0	6	213	221	240	450	2.0	20	24.3	1.20	12.1	1.4	86.4	0.08	0.78	--	2.47	1.64	--	
12	CO.018	15.6	1	13	35	240	450	2.0	20	33.8	1.56	9.7	2.0	86.6	1.68	0.75	0.85	1.81	1.13	21.0	G.C.Calib
12	CO.018	15.6	2	61	80	220	450	2.0	20	12.6	0.59	2.8	0.0	97.1	0.08	0.90	0.88	--	--	--	
12	CO.018	15.6	3	97	107	240	450	2.0	20	27.9	1.30	9.4	1.9	87.7	1.03	0.75	--	2.65	2.17	--	
12	CO.018	15.6	4	133	155	240	450	1.0	20	12.4	0.86	3.3	0.0	95.0	1.67	0.80	0.86	--	--	--	
2	CO.018	15.6	5	181	203	240	600	1.0	20	13.0	0.90	3.2	0.0	94.9	1.86	0.80	0.85	--	--	38.5	
2	CO.018	15.6	6	217	226	240	450	2.0	20	26.4	1.22	10.1	1.4	86.8	1.74	0.73	--	2.89	2.05	--	

Table I
(Continued)

SUMMARY OF M3 SBCR RUN RESULTS

a) Unless otherwise noted, total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.

b) Conversion is total CO conversion over the period (%).

c) Conversion and selectivities are calculated using H₂ as an internal standard in the GC analysis of the offgas.

d) Prod. rate: Rate for production of total hydrocarbons, C₁₊ (kg/kg cat., hr).

e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Per No	Time Start	Time Stop	Temp C	Pres psi	H ₂ CO	Synfl cc/hr	Conv. %	Prod. Rate	Selectivities %				Alpha GC	Alpha Liq	Olefin/Paraf C ₃ C ₄		Olefins C ₆₋₁₈ , %	Comments
13	CO.016	14.7	1	16	35	240	450	2.0	20	26.4	1.31	8.3	1.7	89.3	0.68	0.78	0.81	2.00	1.41	21.7	G.C. Calib
13	CO.016	14.7	2	65	83	220	450	2.0	20	9.7	0.48	0.0	0.99	9.00	0.91	0.88	--	--	--	--	TCD weak.
13	CO.016	14.7	3	89	105	240	450	2.0	20	25.2	1.25	9.2	1.7	88.6	0.51	0.78	--	2.10	1.41	--	CH ₄ peaks
13	CO.016	14.7	4	134	155	240	450	1.0	20	10.9	0.81	1.2	0.7	97.7	0.32	0.84	0.86	--	--	--	are lower
13	CO.016	14.7	5	181	203	240	600	1.0	20	11.4	0.85	0.0	0.4	99.3	0.25	0.92	0.86	--	--	32.2	than
13	CO.016	14.7	6	210	226	240	450	2.0	20	22.7	1.12	3.8	1.9	93.7	0.46	0.79	--	2.37	1.41	--	expected.
14	CO.019	15.2	1	14	35	240	450	2.0	20	13.9	0.66	0.4	1.7	97.2	0.70	0.80	0.86	5.33	2.67	26.6	G.C. Calib
14	CO.019	15.2	2	66	83	220	450	2.0	20	3.8	0.18	0.0	1.7	96.7	1.56	0.88	--	--	--	--	New TCD
14	CO.019	15.2	3	88	105	240	450	2.0	20	12.2	0.57	0.0	2.0	96.3	1.67	0.80	--	5.60	3.80	--	
14	CO.019	15.2	4	133	155	240	450	1.0	20	--	--	--	--	--	0.85	--	--	--	--	--	Repair G.C
14	CO.019	15.2	5	169	178	240	600	1.0	20	5.9	0.41	0.0	1.5	96.1	2.42	0.80	--	8.50	13.00	--	Valve Leak
14	CO.019	15.2	6	193	203	240	450	2.0	20	10.2	0.48	0.8	2.2	95.0	1.96	0.79	--	4.80	3.40	--	CH ₄ peaks
14	CO.019	15.2	7	217	226	240	450	1.0	20	5.1	0.36	0.0	1.6	95.4	3.09	0.80	--	--	--	--	undetected
15	CO.005	14.7	1	25	35	240	450	2.0	20	27.1	1.34	7.9	1.6	89.7	0.82	0.79	0.82	2.30	1.38	23.1	G.C. Calib
15	CO.005	14.7	2	62	83	220	450	2.0	20	10.7	0.53	0.0	0.9	98.4	0.70	0.83	0.88	4.25	3.25	--	
15	CO.005	14.7	3	86	105	240	450	2.0	20	25.3	1.25	7.6	1.8	89.6	1.01	0.78	--	2.42	1.50	--	
15	CO.005	14.7	4	134	155	240	450	1.0	20	11.6	0.85	0.0	1.1	97.5	1.37	0.82	0.85	7.00	4.60	--	
15	CO.005	14.7	5	182	203	240	600	1.0	20	12.3	0.90	0.0	1.0	97.7	1.33	0.83	0.85	7.00	4.40	--	
15	CO.005	14.7	6	210	226	240	450	2.0	20	23.0	1.13	5.9	1.8	91.4	0.99	0.78	--	3.20	2.00	--	
16	CO.002	15.4	1	14	35	240	450	2.0	20	30.1	1.42	12.5	2.5	83.9	1.09	0.75	0.80	1.00	0.66	17.5	
16	CO.002	15.4	2	67	83	220	450	2.0	20	12.8	0.60	4.2	1.3	93.9	0.65	0.80	0.86	2.57	1.63	--	G.C. Calib
16	CO.002	15.4	3	91	107	240	450	2.0	20	28.2	1.34	17.3	2.9	78.8	0.99	0.71	--	0.93	0.65	--	
16	CO.002	15.4	4	136	155	240	450	1.0	20	12.6	0.89	4.4	1.6	92.8	1.21	0.79	0.84	4.43	2.88	--	
16	CO.002	15.4	5	182	198	240	600	1.0	20	13.1	0.92	3.6	1.4	93.9	1.12	0.81	0.84	4.29	2.75	25.2	
16	CO.002	15.4	6	209	227	240	450	2.0	20	25.6	1.22	17.4	3.1	78.7	0.83	0.71	--	1.00	0.66	--	
17	CO.025	15.6	1	21	35	240	450	2.0	20	26.6	1.24	10.7	2.1	86.4	0.82	0.76	0.82	2.25	1.47	21.7	G.C. Calib
17	CO.025	15.6	2	62	83	220	450	2.0	20	8.4	0.39	0.0	1.1	96.9	1.94	0.82	0.92	6.50	3.00	--	
17	CO.025	15.6	3	90	107	240	450	2.0	20	21.5	1.00	9.0	2.0	88.0	1.03	0.77	--	2.64	1.64	--	
17	CO.025	15.6	4	134	155	240	450	1.0	20	10.3	0.71	0.8	1.2	96.7	1.30	0.82	0.93	7.67	4.25	--	
17	CO.025	15.6	5	181	203	240	600	1.0	20	11.7	0.81	1.3	1.1	96.5	1.12	0.83	0.88	8.00	4.25	32.9	
17	CO.025	15.6	6	217	226	240	450	2.0	20	19.9	0.93	9.3	2.2	87.7	0.91	0.76	--	2.92	1.85	--	
18	CO.004	15.0	1	20	39	240	450	2.0	20	33.9	1.64	15.3	2.4	80.9	1.37	0.74	0.79	1.17	0.78	20.3	Repair G.C
18	CO.004	15.0	2	66	87	220	450	2.0	20	15.1	0.73	4.1	1.6	94.0	0.29	0.81	0.85	3.83	2.25	--	
18	CO.004	15.0	3	92	111	240	450	2.0	20	32.7	1.59	15.7	2.6	80.2	1.49	0.73	--	1.20	0.80	--	
18	CO.004	15.0	4	138	159	240	450	1.0	20	14.7	1.06	4.1	1.2	93.2	1.44	0.80	0.83	6.17	3.75	--	
18	CO.004	15.0	5	186	207	240	600	1.0	20	15.0	1.09	3.6	1.1	94.1	1.18	0.82	0.83	5.67	4.00	33.6	
18	CO.004	15.0	6	214	230	240	450	2.0	20	28.4	1.38	14.9	2.5	86.5	1.13	0.73	--	1.58	1.03	--	

Table I
(Continued)

SUMMARY OF M3 SBCR RUN RESULTS

a)Unless otherwise noted, total flow is ca.15 L/min. STP, or 3 cm/sec linear gas flow.

b)Conversion is total CO conversion over the period (%).

c)Conversion and selectivities are calculated using H2 as an internal standard in the GC analysis of the offgas.

d)Prod. rate: Rate for production of total hydrocarbons, C1+ (kg/kg cat.,hr).

e)Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Per No	Time Start	Time Stop	Temp C	Pres psi	H2: CO	Synfl cc/hr	Conv. %	Prod. Rate	Selectivities				Alpha GC	Alpha Liq	Olefin/Paraf C3 C4		Olefins C6-18, %	Comments
19	CO.021	15.6	1	16	35	240	450	2.0	20	23.2	1.08	9.4	2.0	88.0	0.73	0.77	0.82	2.56	1.54	20.3	
19	CO.021	15.6	2	62	83	220	450	2.0	20	8.3	0.38	0.0	1.3	98.2	0.51	0.82	0.88	4.33	3.33	--	
19	CO.021	15.6	3	90	107	240	450	2.0	20	21.8	1.02	10.2	2.2	86.7	0.95	0.76	--	2.50	1.53	--	
19	CO.021	15.6	4	134	155	240	450	1.0	20	9.9	0.69	1.7	1.6	95.5	1.41	0.81	0.83	6.00	3.80	--	
19	CO.021	15.6	5	182	203	240	600	1.0	20	11.5	0.80	1.8	1.2	95.8	1.16	0.83	0.85	6.50	3.80	30.8	
19	CO.021	15.6	6	210	226	240	450	2.0	20	19.9	0.93	9.6	2.3	87.2	0.95	0.76	--	2.31	1.38	--	
20	CO.041	15.8	1	17	37	240	450	2.0	20	25.3	1.16	11.0	2.1	86.0	0.88	0.76	0.84	2.94	1.61	20.3	
20	CO.041	15.8	2	66	75	220	450	2.0	20	9.1	0.41	0.0	1.5	97.8	0.65	0.82	0.91	8.00	2.75	--	
20	CO.041	15.8	3	90	109	240	450	2.0	20	25.3	1.21	9.5	1.9	87.8	0.82	0.78	--	2.81	1.71	--	
20	CO.041	15.8	4	136	148	240	450	1.0	20	12.7	0.88	1.9	1.2	95.9	0.95	0.83	0.86	9.00	4.20	--	
20	CO.041	15.8	5	169	178	240	600	1.0	20	13.2	0.91	2.0	1.0	96.1	0.93	0.84	--	7.00	3.50	--	
20	CO.041	15.8	6	193	203	240	450	2.0	20	24.6	1.13	9.4	1.8	87.9	0.92	0.78	--	2.93	1.75	--	
21	CO.014	15.1	1	24	38	240	450	2.0	20	8.5	0.40	8.3	3.5	85.8	2.43	0.74	0.83	2.75	1.67	17.5	G.C.Calib
21	CO.014	15.1	2	68	86	220	450	2.0	20	3.2	0.15	0.0	2.3	93.4	4.31	0.76	0.86	3.50	3.00	--	
21	CO.014	15.1	3	93	110	240	450	2.0	20	7.1	0.34	8.7	3.0	85.9	2.46	0.71	--	3.00	2.00	--	
21	CO.014	15.1	4	138	157	240	450	1.0	20	2.2	0.15	0.0	2.8	89.3	7.92	0.67	0.84	9.00	4.00	--	
21	CO.014	15.1	5	186	206	240	600	1.0	20	2.1	0.15	0.0	2.6	94.8	2.68	0.71	0.81	4.50	3.50	--	
22	CO.040	14.5	1	19	32	240	450	2.0	20	1.8	0.09	0.0	4.0	94.1	1.89	0.71	0.82	2.50	2.00	--	G.C.Calib
22	CO.040	14.5	2	43	63	220	450	2.0	20	0.7	0.03	0.0	0.7	97.1	2.17	0.91	--	1.00	2.00	--	Shut down
23	CO.047	15.8	1	21	39	240	450	2.0	20	28.2	1.29	7.7	1.5	89.3	1.47	0.79	0.84	3.14	1.69	24.5	
23	CO.047	15.8	2			220	450	2.0	20	--	--	--	--	--	--	--	--	--	--	--	Repair G.C
23	CO.047	15.8	3	94	111	240	450	2.0	20	25.6	1.17	8.9	1.5	88.2	1.38	0.78	--	3.15	2.00	--	
23	CO.047	15.8	4	141	159	240	450	1.0	20	11.9	0.81	2.9	0.9	94.1	2.13	0.82	0.88	7.33	4.75	--	
23	CO.047	15.8	5	187	207	240	600	1.0	20	11.8	0.81	2.6	0.8	94.6	2.01	0.82	0.87	7.00	3.60	--	
23	CO.047	15.8	6	215	226	240	450	2.0	20	24.0	1.10	10.7	1.9	85.7	1.71	0.75	--	3.54	2.13	--	
24	CO.049	15.6	1	19	39	240	450	2.0	20	30.6	1.41	10.9	1.8	85.7	1.66	0.76	0.82	2.09	1.30	14.0	
24	CO.049	15.6	2	71	87	220	450	2.0	20	12.0	1.07	2.7	0.9	95.3	1.09	0.81	0.95	4.25	3.25	--	
24	CO.049	15.6	3	95	111	240	450	2.0	20	29.5	1.37	9.5	1.6	87.6	1.30	0.78	--	2.32	1.40	--	
24	CO.049	15.6	4	139	159	240	450	1.0	20	12.6	0.87	3.1	1.0	94.1	1.80	0.81	0.86	8.33	4.20	--	
24	CO.049	15.6	5	187	207	240	600	1.0	20	13.4	0.93	2.6	0.9	94.8	1.68	0.82	0.88	8.33	4.20	37.8	
24	CO.049	15.6	6	211	231	240	450	2.0	20	24.9	1.16	10.4	1.7	86.5	1.36	0.76	--	2.75	1.75	--	
25	CO.047	15.6	1	19	33	240	450	2.0	20	28.1	1.30	8.8	1.6	88.1	1.50	0.78	0.85	2.93	1.88	25.9	Repeat R23
25	CO.047	15.6	2	55	69	220	450	2.0	20	7.4	0.34	1.5	1.2	96.3	1.02	0.76	0.89	3.00	4.67	--	
25	CO.047	15.6	3	93	159	240	450	2.0	20	25.6	1.19	8.9	1.6	87.9	1.48	0.77	--	3.14	2.00	--	
25	CO.047	15.6	4	143	159	240	450	1.0	20	10.8	0.75	3.0	1.0	94.2	1.84	0.81	0.94	8.00	4.75	--	
25	CO.047	15.6	5	189	207	240	600	1.0	20	12.4	0.86	2.2	0.8	95.6	1.39	0.83	0.86	7.33	4.50	36.4	
25	CO.047	15.6	6	215	231	240	450	2.0	20	23.2	1.08	9.6	1.7	87.4	1.28	0.77	--	3.50	2.07	--	
5	CO.031	15.9	1	19	39	240	450	2.0	20	30.9	1.41	12.1	1.9	84.9	1.12	0.75	0.83	1.83	1.14	22.4	
5	CO.031	15.9	2	67	87	220	450	2.0	20	13.6	0.62	3.9	0.9	94.6	0.49	0.80	0.85	4.20	2.67	--	
5	CO.031	15.9	3	93	111	240	450	2.0	20	29.5	1.35	12.2	2.1	84.6	1.15	0.75	--	1.97	1.25	--	
5	CO.031	15.9	4	141	159	240	450	1.0	20	12.9	0.88	3.6	1.1	94.3	1.11	0.80	0.88	7.75	4.00	--	
5	CO.031	15.9	5	189	207	240	600	1.0	20	13.9	0.95	3.5	1.0	94.4	1.12	0.81	0.85	6.80	3.71	30.1	
5	CO.031	15.9	6	221	230	240	450	2.0	20	26.6	1.22	12.0	2.2	84.9	0.96	0.74	--	2.30	1.43	--	

Table I
(Continued)

SUMMARY OF M3 SBCR RUN RESULTS

a) Unless otherwise noted, total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.

b) Conversion is total CO conversion over the period (%).

c) Conversion and selectivities are calculated using H₂ as an internal standard in the GC analysis of the offgas.

d) Prod. rate: Rate for production of total hydrocarbons, C₁₊ (kg/kg cat., hr).

e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Per No	Time Start	Time Stop	Temp C	Pres psi	H ₂ : CO	Synfl cc/hr	Conv. %	Prod. Rate	Selectivities %CH ₄	%C ₂	%C ₃₊	%CO ₂	Alpha GC	Alpha Liq	Olefin/Paraf C ₃	C ₄	Olefins C _{6-18, %}	Comments
27	CO.029	15.9	1	23	39	240	450	2.0	20	28.3	1.27	8.3	1.6	87.9	2.21	0.77	0.84	3.40	2.20	27.3	
27	CO.029	15.9	2	71	87	220	450	2.0	20	9.5	0.43	1.7	1.1	96.0	1.23	0.80	0.89	5.67	3.00	--	
27	CO.029	15.9	3	99	111	240	450	2.0	20	25.7	1.16	7.7	1.6	88.8	1.86	0.78	--	4.00	2.36	--	
27	CO.029	15.9	4	150	159	240	450	1.0	20	12.0	0.82	1.9	0.9	95.4	1.88	0.83	0.90	8.33	4.75	--	
27	CO.029	15.9	5	191	207	240	600	1.0	20	12.1	0.82	1.7	0.9	95.6	1.75	0.83	0.89	7.67	4.75	39.9	
27	CO.029	15.9	6	222	230	240	450	2.0	20	23.7	1.08	8.2	1.7	88.5	1.60	0.78	--	3.92	2.67	--	
28	CO.01	15.0	1	19	36	240	450	2.0	20	1.1	0.05	0.0	12.	83.9	4.23	0.58	--	3.33	2.50	--	Shut down
29	CO.053	25.2	1	21	39	240	450	2.0	20	42.0	1.19	15.8	2.3	79.5	2.42	0.73	--	1.00	0.67	17.5	
29	CO.053	25.2	2	71	87	220	450	2.0	20	20.5	0.59	5.7	4.8	89.0	0.50	0.79	0.84	3.38	2.10	--	
29	CO.053	25.2	3	95	111	240	450	2.0	20	39.2	1.13	15.8	2.9	79.2	2.09	0.72	--	1.11	0.74	--	
29	CO.053	25.2	4	143	159	240	450	1.0	20	18.4	0.79	5.3	2.6	90.6	1.52	0.80	0.84	5.86	3.56	--	
29	CO.053	25.2	5	191	207	240	600	1.0	20	19.7	0.85	4.6	1.2	92.9	1.34	0.82	--	5.71	3.44	33.6	
29	CO.053	25.2	6	239	255	240	600	2.0	20	40.8	1.17	14.8	2.1	81.4	1.68	0.75	0.80	1.10	0.74	--	
29	CO.053	25.2	7	303	304	240	450	2.0	20	31.5	0.45	21.0	3.9	72.2	2.93	0.63	--	1.34	0.97	--	G.C.Repair
29	CO.053	25.2	8	332	351	260	450	2.0	20	31.0	0.44	36.4	5.3	52.6	5.74	0.52	--	2.60	1.75	--	
29	CO.053	25.2	9	375	376	240	450	2.0	20	18.0	0.55	23.0	3.5	72.1	1.46	0.66	--	3.21	2.05	--	
29	CO.053	25.2	10	415	423	240	450	2.0	20	21.6	0.98	14.4	2.5	82.4	0.82	0.72	--	2.87	1.79	--	G.C.Repair
30	CO.053	29.6	1	26	39	240	450	2.0	20	41.8	1.02	22.6	2.9	71.5	3.05	0.66	0.77	0.99	0.65	19.6	
30	CO.053	29.6	2	55	63	260	450	2.0	20	46.9	1.11	40.6	5.5	46.0	7.98	0.45	--	0.83	0.64	--	
30	CO.053	29.6	3	79	87	280	450	2.0	20	41.4	0.96	41.9	6.5	42.0	9.63	0.40	--	2.06	1.35	--	
30	CO.053	29.6	4	103	111	240	450	2.0	20	19.9	0.49	19.2	3.6	75.8	1.45	0.64	--	4.29	2.50	--	
30	CO.053	29.6	5	131	135	265	450	2.0	20	36.4	0.89	36.4	5.2	54.4	4.04	0.53	--	2.45	1.60	--	
30	CO.053	29.6	6	154	159	280	450	2.0	20	39.6	0.96	48.3	5.9	39.0	6.84	0.40	--	2.44	1.62	--	
30	CO.053	29.6	7	174	183	300	450	2.0	20	40.7	0.94	42.4	6.8	40.7	10.2	0.47	--	3.11	2.03	--	
30	CO.053	29.6	8	198	207	309	450	2.0	20	38.3	0.85	22.8	7.3	58.3	11.6	0.62	--	3.76	2.48	--	G.C.Calib
30	CO.053	29.6	9	220	231	310	450	2.0	20	37.5	0.87	55.5	7.2	25.5	11.8	0.13	--	3.93	2.67	--	
30	CO.053	29.6	10	242	254	320	450	2.0	20	40.8	0.90	61.7	7.4	14.5	16.4	0.00	--	3.62	2.63	--	
30	CO.053	29.6	11	270	279	320	450	1.0	20	30.8	0.92	42.9	6.0	26.9	24.2	0.30	--	5.68	4.28	--	

Table I
(Continued)

SUMMARY OF M3 SBCR RUN RESULTS

a) Unless otherwise noted, total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.

b) Conversion is total CO conversion over the period (%).

c) Conversion and selectivities are calculated using N2 as an internal standard in the GC analysis of the offgas.

d) Prod. rate: Rate for production of total hydrocarbons, C1+ (kg/kg cat., hr).

e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Per No	Time Start	Time Stop	Temp C	Pres psi	H2: CO	Synfld cc/hr	Conv. %	Prod. Rate	Selectivity			Alpha GC	Alpha Liq	Olefin/Paraf		Olefins C6-C18, %	Comments
No	No		No									%CH4	%C2H6	%C3+			C3	C4		
31	Co.055	15.0	1	23	39	240	450	2.0	20	30.0	1.46	23.7	3.73	70.2	0.61	0.81	0.90	0.60	20.3	
31	Co.055	15.0	2	71	87	220	450	2.0	20	9.1	0.44	10.6	2.53	85.7	0.61	0.85	2.89	1.80	--	
31	Co.055	15.0	3	98	110	240	450	2.0	20	25.8	1.26	23.9	3.94	70.1	0.58	--	1.06	0.70	--	
31	Co.055	15.0	4	143	159	240	450	1.0	20	14.7	1.06	5.5	1.44	91.7	0.78	0.83	5.71	3.22	--	
31	Co.055	15.0	5	196	207	240	600	1.0	20	16.1	1.16	4.7	1.21	92.8	0.80	0.83	6.17	3.11	33.6	
31	Co.055	15.0	6	222	234	240	450	2.0	20	29.1	1.42	18.0	2.84	77.8	0.69	--	1.40	0.91	--	
32	Co.044	16.4	1	23	39	240	450	2.0	20	20.9	0.93	6.7	1.91	90.8	0.77	0.83	3.42	2.17	23.1	
32	Co.044	16.4	2	71	87	220	450	2.0	20	10.3	0.46	0.0	0.92	98.8	0.85	--	4.33	4.50	--	
32	Co.044	16.4	3	102	110	240	450	2.0	20	21.8	0.97	6.4	1.72	91.3	0.79	--	3.00	1.77	--	
32	Co.044	16.4	4	143	159	240	450	1.0	20	9.87	0.25	2.1	3.19	92.5	0.61	0.87	7.33	4.00	--	
32	Co.044	16.4	5	174	182	240	450	2.0	20	20.2	0.89	6.8	1.85	90.8	0.79	--	2.92	1.75	--	
33	Co.053	31.4	1	24	39	240	450	2.0	20	41.4	0.94	23.2	3.14	69.6	0.65	0.76	0.82	0.58	21.7	G.C. Calib
33	Co.053	31.4	2	54	63	240	300	2.0	20	35.2	0.47	29.9	3.93	59.6	0.55	--	0.89	0.70	--	
33	Co.053	31.4	3	78	87	240	300	2.0	20	38.7	0.38	31.1	3.90	57.5	0.54	--	0.97	0.71	--	
33	Co.053	31.4	4	102	111	250	300	2.0	20	39.6	0.38	43.1	4.60	41.1	0.38	--	0.99	0.77	--	
33	Co.053	31.4	5	126	135	260	300	2.0	20	37.7	0.37	42.1	4.59	42.4	0.42	--	1.76	1.21	--	
33	Co.053	31.4	6	150	159	260	450	2.0	20	45.0	0.44	43.2	4.80	40.9	0.44	--	1.35	0.95	--	
33	Co.053	31.4	7	174	183	260	450	2.0	20	45.7	0.73	46.4	4.63	40.2	0.43	--	1.06	0.77	--	
33	Co.053	31.4	8	198	207	260	450	2.0	20	49.2	0.98	44.4	4.26	43.5	0.51	--	0.87	0.65	--	
33	Co.053	31.4	9	222	230	240	450	2.0	20	16.1	0.38	33.7	4.79	59.2	0.35	--	3.14	1.91	--	
34	Co.060	15.6	1	23	32	240	450	2.0	20	31.4	1.46	14.0	2.34	82.2	0.75	0.79	1.61	1.00	23.1	G.C. Calib
34	Co.060	15.6	2	71	87	220	450	2.0	20	13.0	0.60	0.1	1.77	97.8	0.81	0.88	4.00	2.83	--	G.C. Calib
34	Co.060	15.6	3	102	111	240	450	2.0	20	28.8	1.34	14.1	2.40	82.2	0.73	--	1.87	1.17	--	
34	Co.060	15.6	4	150	157	240	450	1.0	20	13.5	0.94	4.3	1.75	92.5	0.77	0.85	7.00	4.67	--	
34	Co.060	15.6	5	191	207	240	600	1.0	20	12.8	0.89	2.2	1.64	94.9	0.82	0.86	6.60	4.33	38.5	G.C. Calib
34	Co.060	15.6	6	222	230	240	450	2.0	20	24.9	1.16	13.8	2.78	82.2	0.74	--	2.73	1.73	--	

Table II

COMPARISON OF CONVERSION AND SELECTIVITY OF
METHANE REDUCTION CATALYSTS AT STARTUP CONDITIONS

Period No. -----	Temp. -----	Pres. -----	H ₂ /CO Ratio -----
1	240 C	450psi	2.0

a) Total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.

Flows: N₂-563 SLH, H₂-225 SLH, CO-112.5 SLH.

b) Conversion is total CO conversion over the period (%).

c) Conversion and selectivities are calculated using N₂ as an internal standard in the GC analysis of the offgas.

d) Prod. rate: Rate for production of total hydrocarbons C+1 (kg/kg cat.,hr).

e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Conv. %	Prod. Rate	Selectivities				Alpha GC	Alpha Liq	Catalyst Prom [‡]	Composit. Metal [‡]	Suppt
-----	-----	-----	-----	-----	%CH ₄	%C ₂	%C ₃ +	%CO ₂	-----	-----	-----	-----	-----
M-3 SBCR													
5	CO.003	15.1	31.7	1.53	16.7	2.4	79.8	1.16	0.71	--	1.0La	0.5Ru	Al
6	CO.011	15.3	14.3	0.67	7.6	1.6	89.4	1.42	0.78	0.83	0.0	0.0	Si
7	CO.012	15.8	13.9	0.63	6.1	1.5	90.6	1.74	0.80	0.89	0.0	0.0	Si
8	CO.015	15.0	28.3	1.37	12.7	2.0	84.1	1.24	0.76	0.80	1.0La	0.43Ru	Al
9	CO.011	15.0	18.5	0.89	8.8	1.7	88.8	0.77	0.78	0.83	0.0	0.0	Si
11	CO.017	15.0	27.2	1.32	11.2	1.8	85.9	1.14	0.77	0.80	1.0La	0.5Ru	Al
12	CO.018	15.6	33.8	1.56	9.7	2.0	86.6	1.68	0.75	0.85	0.0	0.5Ru	Al
13	CO.016	14.7	26.4	1.31	(1)	1.7	89.3	0.68	0.78	0.81	1.0La	0.43Ru	Al
14	CO.019	15.2	13.9	0.66	(2)	1.7	97.2	0.70	0.80	0.86	0.0	0.5Ru	Si
15	CO.005	14.7	27.1	1.34	7.9	1.6	89.7	0.82	0.79	0.82	0.0	0.0	Al
16	CO.002	15.4	30.1	1.42	12.5	2.5	83.9	1.09	0.75	0.80	1.0La	0.43Ru	Al
17	CO.025	15.6	26.6	1.24	10.7	2.1	86.4	0.82	0.76	0.82	8.5Zr	0.0	Si
18	CO.004	15.0	33.9	1.64	15.3	2.4	80.9	1.37	0.74	0.79	1.0La	0.43Ru	Al
19	CO.021	15.6	23.2	1.08	9.4	2.0	88.0	0.73	0.77	0.82	0.7Zr	0.0	Si
20	CO.041	15.8	25.3	1.16	11.0	2.1	86.0	0.88	0.76	0.84	8.5Zr	0.5Ru	Si
21	CO.014	15.1	8.5	0.40	8.3	3.5	85.8	2.43	0.74	0.83	0.0	0.5Ru	Ti
22	CO.040	14.5	1.8	0.09	0.0	4.0	94.1	1.89	0.71	0.82	0.0	0.0	Ti
23	CO.047	15.8	28.2	1.29	7.7	1.5	89.3	1.47	0.79	0.84	0.3K	0.5Ru	Al
24	CO.049	15.6	30.6	1.41	10.9	1.8	85.7	1.66	0.76	0.82	0.1K	0.5Ru	Al
25	CO.047	15.6	28.1	1.30	8.8	1.6	88.1	1.50	0.78	0.85	0.3K	0.5Ru	Al
26	CO.031	15.9	30.9	1.41	12.1	1.9	84.9	1.12	0.75	0.83	1.4Zr	0.0	Al
27	CO.029	15.9	28.3	1.27	8.3	1.6	87.9	2.21	0.77	0.84	0.5K	0.5Ru	Al
28	COW.01	15.0	1.1	0.05	0.0	12.	83.9	4.23	0.58	--	5.0Cu	10.0Zn	Al
29	CO.053	25.2	42.0	1.19	15.8	2.3	79.5	2.42	0.73	--	0.0	0.5Ru	Al
30	CO.053	29.6	41.8	1.02	22.6	2.9	71.5	3.05	0.66	0.77	0.0	0.5Ru	Al
31	CO.055	15.0	30.0	1.46	23.7	3.7	70.2	2.30	0.61	0.81	1.0La	1.0Re	Al
32	CO.044	16.4	20.9	0.93	6.7	1.9	90.8	0.56	0.77	0.83	15Zr	0.0	Si
33	CO.053	31.4	41.4	0.94	23.2	3.1	69.6	4.06	0.65	0.76	0.0	0.5Ru	Al
34	CO.060	15.6	31.4	1.46	14.0	2.3	82.2	1.48	0.75	0.79	0.0	0.0	Al

Note: Catalyst Run 9 screened thru 170 x 400 mesh.

Catalysts For Runs 11 through 28 (except Runs 21 and 22) screened thru 150x 400 mesh.

Catalysts for Runs 21 and 22 screened thru 100 x 400 mesh.

Catalysts Nos. Co.029 and Co.060 contained 30 wt% cobalt.

G.C. Problems

- (1) Weak TCD filaments in G.C. CH₄ peaks smaller than expected.
- (2) Internal valve in G.C. leaked. CH₄ peak undetected.

Table III

M3 SBCR RUN RESULTS

COMPARISON OF CATALYST ACTIVITY AT SIMILAR RUN CONDITIONS

Period No.	Temp.	Pres.	H ₂ /CO Ratio
2	220 C	450psi	2.0

a) Total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.

Flows: N₂-563 SLH, H₂-225 SLH, CO-112.5 SLH

b) Conversion is total CO conversion over the period (%).

c) Conversion and selectivities are calculated using N₂ as an internal standard in the GC analysis of the offgas.

d) Prod. rate: Rate for production of total hydrocarbons, C₁+ (kg/kg cat., hr)

e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Conv. %	Prod. Rate	Selectivities				Alpha GC	Alpha Liq	Olefin C ₃	Paraf C ₄	Olefin C ₆₋₁₈
					%CH ₄	%C ₂	%C ₃ +	%CO ₂					
5	CO.003	15.1	13.2	0.63	5.1	1.0	93.4	0.5	0.82	0.90	4.55	1.89	--
6	CO.011	15.3	5.1	0.23	0.0	0.0	97.2	2.8	0.87	0.82	--	--	--
7	CO.012	15.8	5.1	0.23	0.0	0.2	97.8	2.0	0.89	0.90	--	2.50	--
8	CO.015	15.0	11.5	0.56	4.4	1.0	93.9	0.8	0.81	0.89	3.60	2.14	--
9	CO.011	15.0	6.3	0.31	0.0	1.0	98.6	0.4	0.88	0.93	12.00	1.80	--
11	CO.017	15.0	11.4	0.55	5.0	0.0	94.8	0.2	0.88	0.90	5.00	3.20	--
12	CO.018	15.6	12.6	0.59	2.8	0.0	97.1	0.1	0.90	0.88	--	--	--
13	CO.016	14.7	9.7	0.48	(1)	0.1	99.9	0.0	0.91	0.88	--	--	--
14	CO.019	15.2	3.8	0.18	(2)	1.7	96.7	1.6	0.88	--	--	--	--
15	CO.005	14.7	10.7	0.53	0.0	0.9	98.4	0.7	0.83	0.88	4.25	3.25	--
16	CO.002	15.4	12.8	0.60	4.2	1.3	93.9	0.7	0.80	0.86	2.57	1.63	--
17	CO.025	15.6	8.4	0.39	0.0	1.1	96.9	1.9	0.82	0.92	6.50	3.00	--
18	CO.004	15.0	15.1	0.73	4.1	1.6	94.0	0.3	0.81	0.85	3.83	2.25	--
19	CO.021	15.6	8.3	0.38	0.0	1.3	98.2	0.5	0.82	0.88	4.33	3.33	--
20	CO.041	15.8	9.1	0.41	0.0	1.5	97.8	0.7	0.82	0.91	8.00	2.75	--
21	CO.014	15.1	3.2	0.15	0.0	2.3	85.8	4.3	0.76	0.86	3.50	3.00	--
22	CO.040	14.5	0.7	0.35	0.0	0.7	97.1	2.2	0.91	--	1.00	2.00	--
23	CO.047	15.8	---	---	(3)	---	---	---	---	---	---	---	---
24	CO.049	15.6	12.0	1.07	2.7	0.9	95.3	1.1	0.81	0.95	4.25	3.25	--
25	CO.047	15.6	7.4	0.34	1.5	1.2	96.3	1.0	0.76	0.89	3.00	4.67	--
26	CO.031	15.9	13.6	0.62	3.9	0.9	94.6	0.5	0.80	0.85	4.20	2.67	--
27	CO.029	15.9	9.5	0.43	1.7	1.1	96.0	1.2	0.80	0.89	5.67	3.00	--
29	CO.053	25.2	20.5	0.59	5.7	4.8	89.0	0.5	0.79	0.84	3.38	2.10	--
31	CO.055	15.0	9.1	0.44	10.6	2.5	85.7	1.1	0.61	0.85	2.89	1.80	--
32	CO.044	16.4	10.3	0.46	0.0	0.9	98.8	0.3	0.85	--	4.33	4.50	--
34	CO.060	15.6	13.0	0.60	0.1	1.8	97.8	0.4	0.81	0.88	4.00	2.83	--

Note: Catalyst Run 9 screened thru 170 x 400 mesh.

Catalysts for Runs 11 thru 27 (except Runs 21 and 22) screened through 150 x 400 mesh.

Catalysts for Runs 21 and 22 screened thru 100 x 400.

(1) Weak TCD filaments in G.C. CH₄ peaks smaller than expected.

(2) Internal valve in G.C. leaked. CH₄ peak undetected.

(3) Replaced dual column restrictor valve.

M3 SBCR RUN RESULTS

COMPARISON OF CATALYST ACTIVITY AT SIMILAR RUN CONDITIONS

Period No.	Temp.	Pres.	H2/CO Ratio
4	240 C	450psi	1.0

a) Total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.

Flows: N2-562 SLH, H2-119 SLH, CO-119 SLH

b) Conversion is total CO conversion over the period (%).

c) Conversion and selectivities are calculated using N2 as an internal standard in the GC analysis of the offgas.

d) Prod. rate: Rate for production of total hydrocarbons, C1+ (kg/kg cat., hr)

e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Conv. %	Prod. Rate	Selectivities				Alpha GC	Alpha Liq	Olefin/Paraf		Olefin C6-18,
					%CH4	%C2	%C3+	%CO2			C3	C4	
5	CO.003	15.1	13.1	0.95	4.2	1.2	93.3	1.2	0.83	0.88	6.67	3.70	--
6	CO.011	15.3	6.3	0.44	0.4	1.0	95.5	3.1	0.82	0.88	--	--	--
7	CO.012	15.8	3.9	0.26	4.8	2.3	86.3	6.6	0.70	0.85	16.00	3.50	--
8	CO.015	15.0	11.5	0.83	4.8	1.2	92.5	1.5	0.80	0.85	5.60	3.29	--
9	CO.011	15.0	8.0	0.58	1.3	1.3	96.3	1.2	0.82	0.87	7.00	2.83	--
11	CO.017	15.0	11.6	0.84	5.0	0.0	93.9	1.2	0.82	0.86	25.00	2.88	--
12	CO.018	15.6	12.4	0.86	3.3	0.0	95.0	1.7	0.80	0.86	--	--	--
13	CO.016	14.7	10.9	0.81	(1)	0.8	97.7	0.3	0.84	0.86	--	--	--
14	CO.019	15.2	--	--	(2)	--	--	--	0.80	--	--	--	--
15	CO.005	14.7	11.6	0.85	0.0	1.1	97.5	1.4	0.82	0.85	7.00	4.60	--
16	CO.002	15.4	12.6	0.89	4.4	1.6	92.8	1.2	0.79	0.84	4.43	2.88	--
17	CO.025	15.6	10.3	0.71	0.8	1.2	96.7	1.3	0.82	0.93	7.67	4.25	--
18	CO.004	15.0	14.7	1.06	4.1	1.2	93.2	1.4	0.80	0.83	6.17	3.75	--
19	CO.021	15.6	9.9	0.69	1.7	1.4	95.5	1.4	0.81	0.83	6.00	3.80	--
20	CO.041	15.8	12.7	0.88	1.9	1.2	95.9	1.0	0.83	0.86	9.00	4.20	--
21	CO.014	15.1	2.2	0.15	0.0	2.8	89.3	7.9	0.67	0.84	9.00	4.00	--
23	CO.047	15.8	11.9	0.81	2.9	0.9	94.1	2.1	0.82	0.88	7.33	4.75	--
24	CO.049	15.6	12.6	0.87	3.1	1.0	94.1	1.8	0.81	0.86	8.33	4.20	--
25	CO.047	15.6	10.8	0.75	3.0	1.0	94.2	1.8	0.81	0.90	8.00	4.75	--
26	CO.031	15.9	12.9	0.88	3.6	1.1	94.3	1.1	0.80	0.88	7.75	4.00	--
27	CO.029	15.9	12.0	0.82	1.9	0.9	95.4	1.9	0.83	0.90	8.33	4.75	--
29	CO.053	25.2	18.4	0.79	5.3	2.6	90.6	1.5	0.80	0.84	5.86	3.56	--
31	CO.055	15.0	14.7	1.06	5.5	1.4	91.7	1.4	0.78	0.83	5.71	3.22	--
32	CO.044	16.4	9.9	0.25	2.1	3.2	92.5	2.2	0.61	0.87	7.33	4.00	--
34	CO.060	15.6	13.5	0.94	4.3	1.8	92.5	1.5	0.77	0.85	7.00	4.67	--

Note: Catalyst Run 9 screened thru 170 x 400 mesh.

Catalysts for Runs 11 thru 20 and Run 27 (except Runs 21 and 22)

screened thru 150 x 400 mesh.

Catalysts for Runs 21 and 22 screened thru 100 x 400 mesh.

(1) Weak TCD filaments in G.C. CH4 peaks smaller than expected.

(2) Internal valve in G.C. leaked. CH4 peak undetected.

M3 SBCR RUN RESULTS

COMPARISON OF CATALYST ACTIVITY AT SIMILAR RUN CONDITIONS

Period No.	Temp.	Pres.	H2/CO Ratio
5	240 C	600psi	1.0

a) Total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.

Flows: N2-562 SLH, H2-119 SLH, CO-119 SLH

b) Conversion is total CO conversion over the period (%).

c) Conversion and selectivities are calculated using N2 as an internal standard in the GC analysis of the offgas.

d) Prod. rate: Rate for production of total hydrocarbons, C1+ (kg/kg cat., hr)

e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Conv. %	Prod. Rate	Selectivities				Alpha GC	Alpha Liq	Olefin/Paraf C3	Olefin C4	Olefin C6-18, %
					%CH4	%C2	%C3+	%CO2					
5	CO.003	15.1	13.4	0.97	3.9	1.1	93.7	1.3	0.81	--	5.26	3.45	30.1
6	CO.011	15.3	6.7	0.46	0.2	0.9	96.0	2.9	0.84	0.89	12.00	3.67	27.3
7	CO.012	15.8	4.3	0.28	0.1	2.1	91.6	6.3	0.75	0.82	8.50	3.50	--
8	CO.015	15.0	12.4	0.90	4.9	0.8	93.6	0.7	0.84	0.85	5.20	3.14	30.8
9	CO.011	15.0	8.7	0.63	1.4	1.1	96.4	1.1	0.83	0.87	5.00	2.67	30.5
11	CO.017	15.0	11.6	0.84	4.2	0.0	94.7	1.2	0.86	0.86	24.00	1.63	21.0
12	CO.018	15.6	13.0	0.90	3.2	0.0	94.9	1.9	0.80	0.85	--	--	38.5
13	CO.016	14.7	11.4	0.85	(1)	0.5	99.2	0.3	0.92	0.86	--	--	32.2
14	CO.019	15.2	5.9	0.41	(2)	1.5	96.1	2.4	0.80	--	--	--	--
15	CO.005	14.7	23.0	0.90	0.0	1.0	97.7	1.3	0.83	0.85	7.00	4.40	36.4
16	CO.002	15.4	13.1	0.92	3.6	1.4	93.9	1.1	0.81	0.84	4.29	2.75	25.2
17	CO.025	15.6	19.9	0.81	9.3	1.1	96.5	1.1	0.83	0.88	8.00	4.25	32.9
18	CO.004	15.0	15.0	1.09	3.6	1.1	94.1	1.2	0.82	0.83	5.67	4.00	33.6
19	CO.021	15.6	11.5	0.80	1.8	1.2	95.8	1.2	0.83	0.85	6.50	3.80	30.8
20	CO.041	15.8	13.2	0.91	2.0	1.0	96.1	0.9	0.84	0.87	7.00	3.50	31.5
21	Co.014	15.1	2.1	0.15	0.0	2.6	94.8	2.7	0.71	0.81	4.50	3.50	23.1
23	CO.047	15.8	11.8	0.80	2.6	0.8	94.6	2.0	0.82	0.87	7.00	3.60	38.5
24	CO.049	15.6	13.4	0.92	2.6	0.9	94.8	1.7	0.82	0.88	8.33	4.20	37.8
25	CO.047	15.6	12.4	0.86	2.2	0.8	95.6	1.3	0.83	0.86	7.33	4.50	36.4
26	CO.031	15.9	13.9	0.95	3.5	1.0	94.4	1.1	0.81	0.85	6.80	3.71	30.1
27	CO.029	15.9	12.1	0.82	1.7	0.9	95.6	1.8	0.83	0.89	7.67	4.75	39.9
29	CO.053	25.2	19.7	0.85	4.6	1.2	92.9	1.3	0.82	0.85	5.71	3.44	33.6
31	CO.055	15.0	16.1	1.16	4.7	1.2	92.8	1.3	0.80	0.83	6.17	3.11	33.6
34	CO.060	15.6	12.8	0.89	2.2	1.6	94.9	1.2	0.82	0.86	6.60	4.33	38.5

Note: Catalyst Run 9 screened thru 170 x 400 mesh.

Catalysts for Runs 11 thru 27 (except Runs 21 and 22) screened thru 150 x 400 mesh.

Catalyst for Run 21 screened thru 100 x 400 mesh.

(1) Weak TCD filaments in G.C. CH4 peaks smaller than expected.

(2) Internal valve in G.C. leaked. CH4 peak undetected.

Table VI

SUMMARY OF M4 SBCR RUN RESULTS

a) Unless otherwise noted, total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.

b) Conversion is total CO conversion over the period (%).

c) Conversion and selectivities are calculated using N2 as an internal standard in the GC analysis of the offgas.

d) Prod. rate: Rate for production of total hydrocarbons, C1+ (kg/kg cat., hr).

e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Per No	Time Start	Time Stop	Temp C	Pres psi	H2: CO	Synfl cc/hr	Conv. %	Prod. Rate	Selectivities				Alpha GC	Alpha Liq	Olefin C3	Paraf C4	Olefins C6-18, %	Comments
3	CO.002	15.2	1	25	35	240	450	2.0	20	29.4	1.42	17.3	2.2	79.4	1.01	0.73	0.82	0.91	0.60	17.5	
3	CO.002	15.2	2	73	83	220	450	2.0	20	11.8	0.56	4.7	1.0	93.7	0.59	0.81	0.90	2.71	1.63	--	G.C. Calib
3	CO.002	15.2	3	97	107	240	450	2.0	20	26.4	1.28	16.0	3.1	80.1	0.88	0.73	--	0.98	0.66	--	
3	CO.002	15.2	4	145	155	240	450	1.0	20	11.6	0.83	3.9	2.4	92.8	0.84	0.81	0.87	4.29	3.14	--	G.C. Calib
3	CO.002	15.2	5	182	203	240	600	1.0	20	12.9	0.92	4.0	1.5	93.5	0.91	0.81	0.82	4.29	2.75	24.5	
3	CO.002	15.2	6	217	226	240	450	2.0	20	24.2	1.17	17.1	3.1	79.0	0.83	0.71	--	1.03	0.70	--	
4	CO.024	15.4	1	20	37	240	450	2.0	20	25.5	1.21	8.6	2.0	89.0	0.43	0.79	0.84	2.93	1.93	21.7	
4	CO.024	15.4	2	68	85	220	450	2.0	0	9.5	0.45	0.0	2.1	97.6	0.27	0.83	0.91	5.33	4.00	--	No Synfl
4	CO.024	15.4	3	92	109	240	450	2.0	0	23.7	1.13	9.5	2.1	88.0	0.45	0.77	--	2.81	1.88	--	
4	CO.024	15.4	4	140	157	240	450	1.0	0	10.3	0.73	0.5	1.6	97.2	0.71	0.83	0.87	8.33	4.75	--	
4	CO.024	15.4	5	188	205	240	600	1.0	0	11.3	0.80	0.9	1.5	97.0	0.65	0.83	0.87	6.50	3.80	36.4	
4	CO.024	15.4	6	212	229	240	450	2.0	0	21.5	1.02	9.3	2.3	87.9	0.50	0.76	--	2.93	2.07	--	
5	CO.035	15.4	1	16	37	240	450	2.0	20	24.8	1.18	8.5	2.1	89.0	0.47	0.78	0.84	3.13	1.94	23.1	
5	CO.035	15.4	2	68	85	220	450	2.0	20	8.8	0.42	0.0	2.3	97.4	0.31	0.82	--	5.33	4.00	--	
5	CO.035	15.4	3	99	109	240	450	2.0	20	23.5	1.11	8.7	2.1	88.6	0.61	0.77	--	3.07	1.94	--	
5	CO.035	15.4	4	136	157	240	450	1.0	20	10.4	0.73	0.9	0.0	98.4	0.65	--	0.83	--	--	--	G.C. Calib
5	CO.035	15.4	5	184	205	240	600	1.0	20	10.7	0.76	0.7	1.4	97.1	0.75	0.84	0.88	6.25	4.50	27.3	
5	CO.035	15.4	6	212	228	240	450	2.0	20	19.4	0.92	7.8	2.3	89.4	0.56	0.79	--	3.08	1.77	--	
6	CO.028	15.4	1	23	40	240	450	2.0	20	21.2	1.00	6.1	1.6	91.3	1.01	0.81	0.83	4.86	3.00	28.7	
6	CO.028	15.4	2	67	88	220	450	2.0	20	6.6	0.31	0.0	1.9	97.4	0.72	0.83	0.90	5.50	4.00	--	
6	CO.028	15.4	3	95	112	240	450	2.0	20	20.1	0.94	5.8	1.6	91.6	1.02	0.81	--	4.25	2.67	--	
6	CO.028	15.4	4	139	160	240	450	1.0	20	9.2	0.65	0.0	1.3	97.3	1.46	0.85	0.88	9.50	3.75	--	
6	CO.028	15.4	5	189	208	240	600	1.0	20	9.5	0.67	0.0	1.1	97.5	1.36	0.85	0.88	6.00	3.50	40.6	
6	CO.028	15.4	6	213	232	240	450	2.0	20	18.0	0.84	5.7	1.6	91.5	1.12	0.80	--	4.57	2.88	--	
7	CO.043	15.4	1	18	39	240	450	2.0	20	13.0	0.61	3.7	1.8	93.4	1.06	0.79	0.85	5.60	3.17	27.3	
7	CO.043	15.4	2	53	63	220	450	2.0	20	4.3	0.20	0.0	1.4	96.3	2.25	0.81	0.91	4.00	3.00	--	
7	CO.043	15.4	3	94	111	240	450	2.0	20	12.3	0.58	3.0	1.5	93.9	1.58	0.80	--	5.00	2.83	--	
7	CO.043	15.4	4	138	159	240	450	1.0	20	5.2	0.37	0.0	0.0	99.4	0.64	0.83	0.89	7.00	5.00	--	
7	CO.043	15.4	5	191	207	240	600	1.0	20	5.9	0.41	0.0	2.2	94.8	2.99	0.82	0.89	6.00	3.75	30.1	G.C. Calib
7	CO.043	15.4	6	215	231	240	450	2.0	20	10.2	0.47	4.7	2.1	91.4	1.79	0.78	--	5.50	3.20	--	Repair G.C
8	CO.006	15.0	1	19	40	240	450	2.0	20	2.7	0.13	0.1	0.2	98.8	1.75	0.67	0.85	3.33	2.33	16.1	Shut down

Table VI
(Continued)

SUMMARY OF H4 SBCR RUN RESULTS

a) Unless otherwise noted, total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.

b) Conversion is total CO conversion over the period (%).

c) Conversion and selectivities are calculated using N2 as an internal standard in the GC analysis of the offgas.

d) Prod. rate: Rate for production of total hydrocarbons, C1+ (kg/kg cat., hr).

e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Per No	Time Start	Time Stop	Temp C	Pres H2: psi	Synfl CO	Conv. %	Prod. Rate cc/hr	Selectivities %				Alpha GC	Alpha Liq	Olefin/Paraf C3	C4	Olefins C6-18, %	Comments
9	CO.048	15.4	1	19	40	240	450 2.0	12	19.1	0.90	9.9	1.6	87.4	1.05	0.77	0.88	3.60	2.09	20.3	
9	CO.048	15.4	2	70	84	220	450 2.0	12	6.1	0.28	1.8	1.0	95.2	1.93	0.80	0.91	3.67	3.00	--	
9	CO.048	15.4	3	93	111	240	450 2.0	20	17.8	0.84	10.1	1.7	86.9	1.33	0.77	--	3.30	2.10	--	
9	CO.048	15.4	4	139	159	240	450 1.0	20	8.2	0.57	2.3	1.0	93.8	2.98	0.82	0.90	8.50	4.33	--	
9	CO.048	15.4	5	189	207	240	600 1.0	20	11.9	0.83	2.7	0.9	94.4	1.93	0.84	0.89	5.75	3.20	14.0	
9	CO.048	15.4	6	217	226	240	450 2.0	20	24.2	1.17	17.1	3.1	79.0	0.83	0.71	--	1.03	0.70	--	
10	CAL.02	15.9	1	19	40	240	450 2.0	20	34.5	1.58	12.9	2.0	83.9	1.23	0.75	0.84	1.66	1.06	21.0	
10	CAL.02	15.9	2	69	88	220	450 2.0	20	14.9	0.68	4.6	0.9	94.0	0.47	0.81	0.88	4.40	2.29	--	
10	CAL.02	15.9	3	91	112	240	450 2.0	20	34.2	1.57	12.6	2.0	84.4	1.00	0.75	--	1.71	1.06	--	
10	CAL.02	15.9	4	139	160	240	450 1.0	20	14.6	1.00	4.6	1.1	93.3	0.97	0.80	0.88	7.20	4.00	--	
10	CAL.02	15.9	5	187	201	240	600 1.0	20	16.4	1.12	4.2	1.0	94.0	0.89	0.82	0.86	5.83	3.86	35.7	
10	CAL.02	15.9	6	215	230	240	450 2.0	20	30.9	1.42	13.3	2.1	83.7	0.90	0.74	--	1.90	1.21	--	
11	CAL.03	15.6	1	19	40	240	450 2.0	20	29.7	1.39	13.5	2.1	83.4	1.08	0.74	0.86	1.65	1.03	18.2	ShutDown
12	CO.053	15.9	1	22	40	240	450 2.0	20	34.2	1.56	12.6	2.0	84.2	1.23	0.75	0.83	1.60	1.00	24.5	
12	CO.053	15.9	2	69	88	220	450 2.0	20	14.4	0.66	4.3	1.0	94.3	0.48	0.81	0.89	4.20	2.67	--	
12	CO.053	15.9	3	93	112	240	450 2.0	20	34.0	1.56	13.4	2.2	83.2	1.21	0.74	--	1.50	0.94	--	
12	CO.053	15.9	4	150	152	240	450 1.0	20	13.3	0.91	4.3	1.2	93.3	1.18	0.80	0.89	6.60	3.71	--	
12	CO.053	15.9	5	189	208	240	600 1.0	20	15.6	1.06	4.0	0.9	94.0	1.01	0.82	0.87	5.50	3.57	32.2	
12	CO.053	15.9	6	223	231	240	450 2.0	20	29.8	1.37	12.8	2.0	84.3	0.94	0.75	--	1.89	1.10	--	
13	CO.054	15.7	1	23	40	240	450 2.0	20	10.4	0.48	4.7	1.8	92.3	1.17	0.78	0.86	5.75	4.00	25.9	
13	CO.054	15.7	2	71	88	220	450 2.0	20	0.2	0.01	0.0	19.0	60.8	19.5	0.33	0.94	8.00	5.00	--	
13	CO.054	15.7	3	102	112	240	450 2.0	20	10.6	0.49	4.5	1.5	92.8	1.23	0.79	--	5.50	3.75	--	
13	CO.054	15.7	4	143	160	240	450 1.0	20	5.2	0.36	0.0	1.2	97.0	1.85	0.83	0.95	6.00	4.50	--	
13	CO.054	15.7	5	191	208	240	600 1.0	20	5.0	0.34	0.0	1.3	96.9	1.78	0.82	0.93	6.50	3.33	30.8	
13	CO.054	15.7	6	223	230	240	450 2.0	20	8.8	0.40	4.7	2.0	91.7	1.54	0.78	--	5.00	3.50	--	
14	BlendA	20.0	1	25	39	240	450 2.0	20	29.3	1.41	10.1	1.6	86.3	2.02	0.77	0.86	2.23	1.35	23.1	
14	BlendA	20.0	2	69	87	220	450 2.0	20	12.4	0.60	4.3	0.9	93.9	0.95	0.81	0.91	3.80	2.33	--	
14	BlendA	20.0	3	93	111	240	450 2.0	20	27.5	1.33	10.5	1.7	86.4	1.44	0.76	--	2.09	1.32	--	
14	BlendA	20.0	4	143	158	240	450 1.0	20	12.7	0.91	3.4	1.0	94.0	1.61	0.81	0.86	7.50	3.83	--	
14	BlendA	20.0	5	191	207	240	600 1.0	20	14.1	1.02	3.7	1.0	93.8	1.45	0.82	0.89	6.40	3.43	32.9	
14	BlendA	20.0	6	215	231	240	450 2.0	20	27.0	1.29	11.5	1.9	85.5	1.12	0.76	--	2.04	1.30	--	

SUMMARY OF M4-SECR RUN RESULTS

- a) Unless otherwise noted, total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.
- b) Conversion is total CO conversion over the period (Z).
- c) Conversion and selectivities are calculated using N2 as an internal standard in the GC analysis of the offgas.
- d) Prod. rate: Rate for production of total hydrocarbons, C1+ (kg/kg cat., hr).
- e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Per No	Time Start	Time Stop	Temp C	Pres psi	H2: CO	Synfl cc/hr	Conv. %	Prod. Rate	Selectivities				Alpha GC	Alpha Liq	Olefin/Paraf		Olefins C5-18, Z	Comments
												XCH4	XC2	XC3+	XC02						
15	CO.034	13.0	1	21	39	240	450	2.0	20	27.5	1.54	10.4	1.6	87.2	0.80	0.78	0.84	2.21	1.40	21.0	G.C.Calib
15	CO.034	13.0	2	45	87	220	450	2.0	20	11.0	0.61	4.0	0.9	94.5	0.59	0.82	0.90	4.00	3.00	--	
15	CO.034	13.0	3	95	111	240	450	2.0	20	25.6	1.49	11.5	1.9	85.9	0.82	0.76	--	2.10	1.33	--	
15	CO.034	13.0	4	141	159	240	450	1.0	20	11.2	0.94	3.9	1.0	94.0	1.02	0.82	0.87	8.33	4.00	--	
15	CO.034	13.0	5	189	207	240	600	1.0	20	11.8	0.99	3.9	1.1	94.0	1.03	0.83	--	5.75	3.80	37.8	
15	CO.034	13.0	6	215	231	240	450	2.0	20	21.6	1.19	10.9	1.9	86.3	0.87	0.76	--	3.33	2.15	--	
16	CAL.04	16.1	1	21	39	240	450	1.8	20	26.3	1.34	7.1	1.3	90.3	1.38	0.80	0.85	4.80	3.18	32.9	H2/CO:
16	CAL.04	16.1	2	54	163	220	450	1.8	20	8.4	0.42	2.6	1.0	94.1	2.31	0.80	0.88	5.00	4.00	--	1.76/1.0
17	CAL.08	15.0	1	21	39	240	450	1.8	20	16.9	0.93	5.9	1.0	91.7	1.36	0.82	0.88	5.20	3.33	28.7	H2/CO:
17	CAL.08	15.0	2	47	62	220	450	1.8	20	5.4	0.28	0.1	0.8	96.9	2.23	0.83	--	4.00	3.00	--	1.76/1.0
18	CAL.07	15.0	1	21	39	240	450	2.0	20	20.6	1.03	7.7	1.2	90.0	1.09	0.81	0.88	5.00	3.00	32.2	
18	CAL.07	15.0	2	47	62	220	450	2.0	20	6.7	0.33	1.8	1.4	95.0	1.81	0.84	--	4.00	3.00	--	
19	CAL.05	15.7	1	23	39	240	450	2.0	20	26.6	1.22	7.3	1.3	90.2	1.19	0.82	0.86	4.11	2.70	18.2	G.C.Calib
19	CAL.05	15.7	2	47	62	220	450	2.0	20	9.0	0.41	2.3	1.4	94.8	1.56	0.84	--	5.50	3.00	--	
20	CAL.06	15.0	1	15	30	240	450	2.0	20	5.6	0.26	3.1	2.1	92.0	2.86	0.80	0.90	4.50	3.50	30.8	G.C.Calib
20	CAL.06	15.0	2	55	63	240	450	2.0	20	3.5	0.16	0.0	3.3	92.8	3.87	0.80	0.85	3.00	2.50	--	
20	CAL.06	15.0	3	103	110	240	450	2.0	20	1.7	0.08	0.0	3.3	89.5	7.22	0.80	--	1.50	3.00	--	Cat.Loss
21	CO.004	15.9	1	23	40	240	450	2.0	20	39.3	1.80	15.2	2.3	81.2	1.38	0.74	0.89	1.16	0.73	23.1	
21	CO.004	15.9	2	71	88	220	450	2.0	20	16.1	0.74	8.1	1.2	90.2	0.48	0.78	0.87	3.38	2.22	--	
21	CO.004	15.9	3	105	110	240	450	2.0	20	37.6	1.47	16.4	2.3	80.2	1.20	0.73	--	1.10	0.70	--	
21	CO.004	15.9	4	136	138	240	450	1.0	20	14.9	1.02	7.4	1.4	89.9	1.29	0.77	0.84	4.67	2.82	--	
21	CO.004	15.9	5	166	184	240	600	1.0	20	18.4	1.26	6.1	1.1	91.9	0.94	0.81	0.84	5.25	2.91	--	G.C.Repair
21	CO.004	15.9	6	199	207	240	600	2.0	20	39.0	1.80	14.2	1.9	83.0	0.91	0.78	0.82	0.85	0.77	--	
21	CO.004	15.9	7	212	214	240	450	2.0	20	34.6	1.59	15.8	2.3	81.0	1.00	0.76	--	0.86	0.81	--	G.C.Repair
22	BlendB	30.5	1	23	39	240	450	2.0	20	35.6	1.64	12.7	1.6	79.4	6.29	0.75	0.81	1.40	0.81	27.3	
22	BlendB	30.5	2	78	87	240	450	1.0	20	15.8	1.07	1.5	0.9	90.5	7.06	0.80	0.83	5.00	2.22	38.5	G.C.Calib
22	BlendB	30.5	3	125	135	240	450	0.7	20	10.6	0.86	0.8	0.8	92.6	5.83	0.82	0.87	7.33	3.20	33.6	G.C.Calib
22	BlendB	30.5	4	150	158	240	450	1.0	20	14.1	0.99	3.9	1.0	91.0	4.07	0.80	--	5.40	2.25	--	
22	BlendB	30.5	5	174	183	240	450	2.0	20	30.1	1.44	13.2	1.8	82.4	2.56	0.75	--	1.33	0.69	--	
22	BlendB	30.5	6	191	207	260	450	1.0	20	23.5	1.63	10.0	1.9	82.1	6.02	0.74	--	2.92	1.15	--	
22	BlendB	30.5	7	223	232	280	450	1.0	20	26.9	1.79	17.8	3.1	68.4	10.7	0.64	--	3.00	1.88	--	
22	BlendB	30.5	8	247	255	280	450	0.7	20	17.1	1.34	8.8	2.6	78.8	9.8	0.70	--	6.00	3.53	--	
23	CAL.09	15.0	1	23	40	240	450	2.0	20	17.4	0.84	0.02	1.2	97.9	0.95	0.84	0.88	5.40	3.33	29.4	G.C.Calib
23	CAL.09	15.0	2	57	63	220	450	2.0	20	6.6	0.32	0.2	0.9	98.0	0.92	0.90	--	4.00	3.00	--	

Table VI
(Continued)

SUMMARY OF M4 SBCR RUN RESULTS

a) Unless otherwise noted, total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.

b) Conversion is total CO conversion over the period (%).

c) Conversion and selectivities are calculated using N₂ as an internal standard in the GC analysis of the offgas.

d) Prod. rate: Rate for production of total hydrocarbons, C₁+ (kg/kg cat., hr).

e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Per No	Time Start	Time Stop	Temp C	Pres psi	H ₂ : CO	Synfl cc/hr	Conv. %	Prod. Rate	Selectivities				Alpha GC	Alpha Liq	Olefin/Paraf		Olefins C ₅ -18, %	Comments
												XCH ₄	XC ₂	XC ₃ +	XCO ₂			C ₃	C ₄		
25	CO.056	15.0	1	23	39	240	450	2.0	20	11.4	0.55	7.8	3.6	87.2	1.43	0.67	0.87	3.60	2.30	20.3	
25	CO.056	15.0	2	47	63	220	450	2.0	20	4.5	0.22	0.3	2.7	95.7	1.27	0.73	--	4.67	3.00	--	
26	CAL.10	15.6	1	23	39	240	450	2.0	20	21.9	1.01	5.4	1.5	91.9	1.25	0.79	0.85	3.60	2.27	25.9	
26	CAL.10	15.6	2	54	63	240	450	2.0	20	21.7	1.30	8.3	1.1	89.9	0.68	0.80	--	3.78	2.45	--	
26	CAL.10	15.6	3	78	87	240	450	2.0	20	17.2	1.04	11.7	1.4	86.1	0.78	0.76	--	3.57	2.30	--	
26	CAL.10	15.6	4	102	111	240	450	2.0	20	17.7	1.01	11.9	1.4	86.0	0.73	0.77	--	3.52	2.28	--	
26	CAL.10	15.6	5	118	126	240	450	2.0	20	16.2	0.75	4.9	1.7	92.3	1.10	0.77	--	4.29	2.75	--	
27	Co.050	14.6	1	23	39	240	450	2.0	20	20.4	1.01	6.8	1.9	90.2	1.04	0.78	0.87	2.50	1.69	18.9	
27	Co.050	14.6	2	78	87	220	450	2.0	20	8.1	0.39	0.0	4.8	92.6	2.56	0.79	0.87	8.50	3.00	--	
27	Co.050	14.6	3	102	111	240	450	2.0	20	19.8	0.98	9.1	2.6	87.0	1.30	0.76	--	2.50	1.69	--	
27	Co.050	14.6	4	142	157	240	450	1.0	20	8.4	0.61	1.1	2.9	93.3	2.78	0.79	0.90	6.25	5.00	--	
27	Co.050	14.6	5	173	182	240	450	2.0	20	17.3	0.87	9.9	3.0	85.4	1.74	0.75	--	2.50	1.75	--	

M4 SBCR RUN RESULTS

COMPARISON OF CATALYST ACTIVITY AT SIMILAR RUN CONDITIONS

Period No.	Temp.	Pres.	H ₂ /CO Ratio
1	240 C	450psi	2.0

a) Total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.

Flows: N₂-563 SLH, H₂-225 SLH, CO-112.5 SLH

b) Conversion is total CO conversion over the period (%).

c) Conversion and selectivities are calculated using N₂ as an internal standard in the GC analysis of the offgas.

d) Prod. rate: Rate for production of total hydrocarbons C₁+ (kg/kg cat., hr).

e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Conv. %	Prod. Rate	Selectivities				Alpha GC	Alpha Liq	Olefin/Paraf C ₃	Olefin C ₄	Olefin C _{6-18, %}
					%CH ₄	%C ₂	%C ₃ +	%CO ₂					
3	CO.002	15.2	29.4	1.42	17.3	2.3	79.4	1.01	0.73	0.82	0.91	0.60	17.5
4	CO.024	15.4	25.5	1.21	8.6	2.0	89.0	0.43	0.79	0.84	2.93	1.93	21.7
5	CO.035	15.4	24.8	1.18	8.5	2.1	89.0	0.47	0.78	0.84	3.13	1.94	23.1
6	CO.028	15.4	21.2	1.00	6.1	1.6	91.3	1.01	0.81	0.83	4.86	3.00	28.7
7	CO.043	15.4	13.0	0.61	3.7	1.8	93.4	1.06	0.79	0.85	5.60	3.17	27.3
8	CO.006	15.0	2.7	0.25	0.1	0.2	98.8	1.75	0.67	0.85	3.33	2.33	16.1
9	CO.048	15.4	19.1	0.90	9.9	1.6	87.4	1.05	0.77	0.88	3.60	2.09	20.3
10	CAL.02	15.9	34.5	1.58	12.9	2.0	83.9	1.23	0.75	0.81	1.66	1.06	21.0
11	CAL.03	15.6	29.7	1.39	13.5	2.1	83.4	1.08	0.74	0.86	1.65	1.03	18.2
12	CO.053	15.9	34.2	1.56	12.6	2.0	84.2	1.23	0.75	0.83	1.60	1.00	24.5
13	CO.054	15.7	10.4	0.48	4.7	1.8	92.3	1.17	0.78	0.86	5.75	4.00	25.9
14	BlendA	20.0	29.3	1.41	10.1	1.6	86.3	2.02	0.77	0.86	2.23	1.35	23.1
15	CO.034	13.0	27.5	1.54	10.4	1.6	87.2	0.80	0.78	0.84	2.21	1.40	21.0
16	CAL.04	16.1	26.3	1.34	7.1	1.3	90.3	1.38	0.80	0.85	4.80	3.18	32.9
17	CAL.08	15.0	16.9	0.93	5.9	1.0	91.7	1.36	0.82	0.88	5.20	3.33	28.7
18	CAL.07	15.0	20.6	1.03	7.7	1.2	90.0	1.09	0.81	0.88	5.00	3.00	32.2
19	CAL.05	15.7	26.6	1.22	7.3	1.3	90.2	1.19	0.82	0.86	4.11	3.00	28.7
20	CAL.06	15.0	5.6	0.26	3.1	2.1	92.0	2.86	0.80	0.90	4.50	3.50	30.8
21	CO.004	15.9	39.3	1.80	15.2	2.3	81.2	1.38	0.74	0.80	1.16	0.73	23.1
23	CAL.09	15.0	17.4	0.84	0.0	1.2	97.9	0.95	0.83	0.88	5.40	3.33	29.4
24	CO.053	28.5	50.4	1.28	14.1	2.1	81.8	2.03	0.75	0.79	1.14	0.68	21.7
25	CO.056	15.0	11.4	0.55	7.8	3.6	87.2	1.43	0.67	0.87	3.60	2.30	20.3
26	CAL.10	15.6	21.9	1.01	5.4	1.5	91.9	1.25	0.79	0.85	3.60	2.27	25.9
27	Co.050	14.6	20.4	1.01	6.8	1.9	90.2	1.04	0.78	0.87	2.50	1.69	18.9

Note: Catalysts for Runs 3 thru 15 (except 8) screened through 150 x 400 mesh.

Catalyst for Run 8 screened thru 100 x 400 mesh.

Cat. Nos. CAL.08 and CAL.07 were prereduced and coated with wax.

H₂ to CO ratio for Runs 16 and 17 was 1.76/1.0.

Cat. No. CAL.06 was H₂ reduced and air stabilized.

Cat. No. CAL.09 was prereduced and coated with Soya.

M4 SBCR RUN RESULTS

COMPARISON OF CATALYST ACTIVITY AT SIMILAR RUN CONDITIONS

Period No.	Temp.	Pres.	H ₂ /CO Ratio
2	220 C	450psi	2.0

- a) Total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.
Flows: N₂-563 SLH, H₂-225 SLH, CO-112.5 SLH
- b) Conversion is total CO conversion over the period (%).
- c) Conversion and selectivities are calculated using N₂ as an internal standard in the GC analysis of the offgas.
- d) Prod. rate: Rate for production of total hydrocarbons C₁+ (kg/kg cat., hr).
- e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Conv. %	Prod. Rate	Selectivities				Alpha GC	Alpha Liq	Olefin/Paraf		Olefin C ₆₋₁₈ , %
					%CH ₄	%C ₂	%C ₃ +	%CO ₂			C ₃	C ₄	
3	CO.002	15.2	11.8	0.56	4.7	1.0	93.7	0.59	0.81	0.90	2.71	1.63	--
4	CO.024	15.4	9.5	0.45	0.0	2.1	97.6	0.27	0.83	0.91	5.33	4.00	--
5	CO.035	15.4	8.8	0.42	0.0	2.3	97.4	0.31	0.82	--	5.33	4.00	--
6	CO.028	15.4	6.6	0.31	0.0	1.9	97.4	0.72	0.83	0.90	5.50	4.00	--
7	CO.043	15.4	4.3	0.20	0.0	1.4	96.3	2.25	0.81	0.91	4.00	3.00	--
9	CO.048	15.4	6.1	0.28	1.8	1.0	95.2	1.93	0.80	0.91	3.67	3.00	--
10	CAL.02	15.9	14.9	0.68	4.6	0.9	94.0	0.47	0.81	0.88	4.40	2.29	--
12	CO.053	15.9	14.4	0.66	4.3	1.0	94.3	0.48	0.81	0.89	4.20	2.67	--
13	CO.054	15.7	0.2	0.01	0.0	20.	60.8	19.5	0.33	0.94	8.00	5.00	--
14	Blend A	20.0	12.4	0.60	4.3	0.9	93.9	0.95	0.81	0.91	3.80	2.33	--
15	CO.034	13.0	11.0	0.61	4.0	0.9	94.5	0.59	0.82	0.90	4.00	3.00	--
16	CAL.04	16.1	8.4	0.42	2.6	1.0	94.1	2.31	0.80	0.88	5.00	4.00	--
17	CAL.08	15.0	5.4	0.28	0.1	0.8	96.9	2.23	0.83	--	4.00	3.00	--
18	CAL.07	15.0	6.7	0.33	1.8	1.4	95.0	1.81	0.85	--	4.00	3.00	--
19	CAL.05	15.7	9.0	0.41	2.3	1.4	94.8	1.56	0.84	--	5.50	3.00	--
20	CAL.06	15.0	3.5	0.16	0.0	3.3	92.8	3.87	0.80	0.85	3.00	2.50	--
21	CO.004	15.9	16.1	0.74	8.1	1.2	90.2	0.48	0.78	0.86	3.38	2.22	--
23	CAL.09	15.0	6.6	0.32	0.2	0.9	98.0	0.92	0.90	--	4.00	3.00	--
25	CO.056	15.0	4.5	0.22	0.3	2.7	95.7	1.27	0.73	--	4.67	3.00	--
27	Co.050	14.6	8.1	0.39	0.0	4.8	92.6	2.56	0.79	0.87	8.50	3.00	--

Note: Catalysts for Runs 3 through 15 screened thru 150 x 400 mesh.
Blend A contains 15.0 gm of Cat. No. CO.005 plus 5.0 gm of Cat. No. WGS.03.

Cat. NOs. CAL.08 and CAL.07 were prereduced and wax coated.

H₂ to CO for Runs 16 and 17 was 1.76/1.0.

Cat. No. CAL.06 was H₂ reduced and air stabilized before charging.

Cat. No. CAL.09 was prereduced and coated with Soya.

Table IX

DATE: 09/30/94

M4 SBCR RUN RESULTS

COMPARISON OF CATALYST ACTIVITY AT SIMILAR RUN CONDITIONS

Period No.	Temp.	Pres.	H2/CO Ratio
4	240 C	450psi	1.0

a) Total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.

Flows: N2-562 SLH, H2-119 SLH, CO-119 SLH

b) Conversion is total CO conversion over the period (%).

c) Conversion and selectivities are calculated using N2 as an internal standard in the GC analysis of the offgas.

d) Prod. rate: Rate for production of total hydrocarbons C1+ (kg/kg cat., hr).

e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Conv. %	Prod. Rate	Selectivities				Alpha GC	Alpha Liq	Olefin C3	Paraf C4	Olefin C6-18, %
3	CO.002	15.2	11.6	0.83	3.9	2.4	92.8	0.84	0.81	0.87	4.29	3.14	--
4	CO.024	15.4	10.3	0.73	0.5	1.6	97.2	0.71	0.83	0.87	8.33	4.75	--
5	CO.035	15.4	10.4	0.73	0.9	0.0	98.4	0.65	--	0.83	--	--	--
6	CO.028	15.4	9.2	0.65	0.0	1.3	97.3	1.46	0.85	0.88	9.50	3.75	--
7	CO.043	15.4	5.2	0.37	0.0	0.0	99.4	0.64	0.83	0.89	7.00	5.00	--
9	CO.048	15.4	8.2	0.57	2.3	1.0	93.8	3.00	0.82	0.90	8.50	4.33	--
10	CAL.02	15.9	14.6	1.00	4.6	1.0	93.3	0.97	0.80	0.88	7.20	4.00	--
12	CO.053	15.9	13.3	0.91	4.3	1.2	93.3	1.18	0.80	0.89	6.60	3.71	--
13	CO.054	15.7	5.2	0.36	0.0	1.2	97.0	1.85	0.83	0.95	6.00	4.50	--
14	BlendA	20.0	12.7	0.91	3.4	1.0	94.0	1.61	0.81	0.86	7.50	3.83	--
15	CO.034	13.0	11.2	0.94	3.9	1.0	94.0	1.02	0.82	0.87	8.33	4.00	--
21	CO.004	15.9	14.9	1.02	7.4	1.4	89.9	1.29	0.77	0.84	4.67	2.82	--

Note: Catalysts for Runs 3 through 21 screened thru 150 x 400 mesh.

Table X

DATE: 12/30/94

M4 SBCR RUN RESULTS

COMPARISON OF CATALYST ACTIVITY AT SIMILAR RUN CONDITIONS

Period No.	Temp.	Pres.	H ₂ /CO Ratio
5	240 C	600psi	1.0

a) Total flow is ca. 15 L/min. STP, or 3 cm/sec linear gas flow.

b) Conversion is total CO conversion over the period (%).

Flows: N₂-562 SLH, H₂-119 SLH, CO-119 SLH

c) Conversion and selectivities are calculated using N₂ as an internal standard in the GC analysis of the offgas.

d) Prod. rate: Rate for production of total hydrocarbons C₁+ (kg/kg cat., hr).

e) Alpha: Based on GC analysis of offgas and liquid product.

Run No	Cat. No	Cat. wt, g	Conv. %	Prod. Rate	Selectivities				Alpha GC	Alpha Liq	Olefin/Paraf Olefin		
					%CH ₄	%C ₂	%C ₃ +	%CO ₂			C ₃	C ₄	C _{6-18, %}
3	CO.002	15.2	12.9	0.92	4.0	1.5	93.5	0.91	0.81	0.82	4.29	2.75	24.5
4	CO.024	15.4	11.3	0.80	0.9	1.5	97.0	0.65	0.83	0.87	6.50	3.80	36.4
5	CO.035	15.4	10.7	0.76	0.7	1.4	97.1	0.75	0.84	0.88	6.25	4.50	27.3
6	CO.028	15.4	9.5	0.67	0.0	1.1	97.5	1.36	0.85	0.88	6.00	3.50	40.6
7	CO.043	15.4	5.9	0.41	0.0	2.2	94.8	2.99	0.82	0.89	6.00	3.75	30.1
9	CO.048	15.4	11.9	0.83	2.7	0.9	94.4	1.93	0.84	0.89	5.75	3.20	14.0
10	CAL.02	15.9	16.4	1.12	4.2	1.0	94.0	0.89	0.82	0.86	5.83	3.86	35.7
12	CO.053	15.9	15.6	1.06	4.0	0.9	94.0	1.0	0.82	0.87	5.50	3.57	32.2
13	CO.054	15.7	5.0	0.34	0.0	1.3	96.9	1.78	0.82	0.93	6.50	3.33	30.8
14	BlendA	20.0	14.1	1.02	3.7	1.0	93.8	1.45	0.82	0.89	6.40	3.43	32.9
15	CO.034	13.0	11.8	0.99	3.9	1.1	94.0	1.03	0.83	0.87	5.75	3.80	37.8
21	CO.004	15.9	18.4	1.26	6.1	1.1	91.9	0.94	0.81	0.84	5.25	2.91	32.2

Note: Catalysts for Runs 3 through 21 screened thru 150 x 400 mesh.