

3441 - 30/5.01 - 122  
Produktion im Allgemeinen  
Chemische Fabrik

R. - A. B. L. & C. O.

Oberh.-Kulzen, den 21. August 1936.  
Abt. RVA Lehm, 28.

000428

He. W.

Lehm.

V B. 60.

Dieseloil aus HL Ka: no Nr. 258 Eing. 12.8.36.

*Schweröl - Best. Blatt*

d <sub>15</sub>	=	0,849
Farbe	=	orange, grün irisierend
Viskosität bei 20°C	=	5,17 °E
Stockpunkt	=	- 28°C
Flammpunkt	=	108 °C
Siedebeginn		220°C
- 230°C		0,5 Vol.-%
240 "		1,5 "
250 "		2,5 "
260 "		3,0 "
270 "		4,0 "
280 "		5,0 "
290 "		6,0 "
300 "		9,0 "
310 "		10,5 "
320 "		15,0 "
330 "		19,5 "
340 "		24,0 "
350 "		31,0 "
360 "		44,0 "

*Rae*