

ChevronTexaco provides no warranties, either express or implied, as to the accuracy or validity of any of the work in this report. Anyone accessing or using the reports indemnifies and holds ChevronTexaco harmless against any liability that comes from using or relying on the information contained therein.

PERSONAL AND CONFIDENTIAL

BRIEF OF PARTIAL REPORT

Laboratory Montebello Experiment No. 2001
Date Approved September 15, 1955 Partial Report No. 1
Date Work Completed October 13, 1951 Subject: Hydrocarbon
Synthesis

Subject: Hydrocarbon Synthesis: Montebello Runs No. 58, 59, 60, 61, and 62; CM&S Catalyst.

Object: To test ammonia-synthesis catalysts for hydrocarbon synthesis.

History: Hydrocarbon Research, Inc., obtained high sustained liquid yields in a pilot unit using a powdered ammonia-synthesis catalyst for synthesizing hydrocarbons from carbon monoxide and hydrogen. Since this yield level had never been attained at Montebello using other catalysts, the decision was made for Montebello Laboratory to test some ammonia-synthesis catalysts for hydrocarbon synthesis.

Experimental Work: Runs 58, 59, 60, 61, and 62 were made between May 4, 1951, and October 13, 1951, using both new and spent catalysts of the fused iron-alumina-silica-potassia type prepared by Consolidated Mining and Smelting Company. The catalysts were charged to Montebello reactor 5S, reduced with hydrogen at 200 psi and 700 to 800°F. Synthesis feed gas was obtained by using the Texaco Synthesis Gas Generation Process with natural gas and oxygen in a 2-cubic-foot generator. A water wash tower was used to remove traces of carbon and to cool the feed gas to facilitate measurement.

Conclusions: 1. The five runs made with CM&S catalysts resulted in wide variations in yield of liquid product.
2. The liquid yields did not show the same correlation with space velocity and catalyst particle size that was exhibited with magnetite and mill scale catalysts.
3. The best run, Number 59, had a C₃+ yield of approximately 9.0 lbs/MCF H₂+CO. The distinguishing features of the catalyst in Run 59 were:
a) The catalyst had previously been used in ammonia synthesis.
b) It was essentially fully reduced when received at Montebello.
c) No potassium carbonate was added to the catalyst as received.

FIH-(WEK-WAMcM)-GK-WJC(2)-RWH-HDM(2)-RLSr(2)-duBE(2)

JCW-CEL

RP

WMS

NOTICE

The information herein contained is not public but belongs to The Texas Company which has provided it solely for an expressly restricted private use. All persons, firms or corporations who receive such information shall be deemed to be under a strict obligation to have agreed to make no disclosure of it, in whole or in part, to any other person or to any other firm or corporation, without the express written consent of any or all of such individuals or firms, for restricted use as is expressly authorized in writing by the Texas Company.

The information herein contained is not public but belongs to The Texas Company which has provided it solely for an expressly restricted private use. All persons to whom such information is furnished shall be deemed to have agreed to keep such information confidential and to make no disclosure thereof to any third party without the prior written consent of The Texas Company. Any disclosure of any or all of such information without such restricted use as is expressly authorized in writing by The Texas Company.

PERSONAL AND CONFIDENTIAL

HYDROCARBON SYNTHESIS

PARTIAL REPORT NO. 1

Montebello Research Laboratory Experiment No. 2001
 Work Completed: October 13, 1951 Report Approved: Sept. 15, 1955

MONTEBELLO RUNS NO. 58, 59, 60, 61, and 62

CM AND S CATALYST

INDEX

	<u>Page</u>
I. INTRODUCTION	1
II. EQUIPMENT AND MATERIALS	1
III. RESULTS AND DISCUSSION	3
IV. YIELDS AND CATALYST ACTIVITY	8
V. CONCLUSIONS	16
VI. APPENDIX	19

INDEX TO FIGURES

1. EFFECT OF CATALYST AGE ON LIQUID YIELD	9
2. YIELD OF C ₃ + VERSUS BPD	10
3. LIQUID YIELD AS FUNCTION OF CONVERSION	11
4. LIQUID YIELD AS FUNCTION OF CONVERSION AND SELECTIVITY	12
5. YIELD VERSUS ACTIVITY INDEX	13
6. YIELD VERSUS SPACE VELOCITY	14

INDEX TO TABLE

I. OPERATING CONDITIONS AND YIELD DATA SUMMARY	7
--	---