

- [54] **HYDROCARBON SYNTHESIS FROM CO AND H₂ USING RU SUPPORTED ON A TITANIUM OXIDE**
- [75] Inventors: **M. Albert Vannice**, Plainfield; **Robert L. Garten**, Summit, both of N.J.
- [73] Assignee: **Exxon Research and Engineering Co.**, Linden, N.J.
- [21] Appl. No.: **673,356**
- [22] Filed: **Apr. 5, 1976**
- [51] Int. Cl.² **C07C 1/04**
- [52] U.S. Cl. **260/449 R; 252/460; 252/466 R**
- [58] Field of Search **260/449 R, 449.6**

[56] **References Cited**

U.S. PATENT DOCUMENTS

2,464,532	3/1949	Sellers	260/449.6
2,637,739	5/1953	McGrath	260/449.6
2,699,988	1/1955	McGrath et al.	260/449.6 X
2,850,515	9/1958	Riblett et al.	260/449.6

OTHER PUBLICATIONS

- Shultz et al., Report of Investigations, 6974, Bureau of Mines, 1967, pp. 1-3, 5-14, 18.
- Karn et al., I & EC, Product Res & Dev., 4, No. 4, (1965) pp. 265-269.
- Pichler, Brennstoff-Chemie, 19, 226-230, 1938.
- Kratel, Doctoral Dissertation, Technical University

Berlin-Charlottenburg, 1937, Kasser Wilhem Inst. at Mulheim-Ruhr pp. 17-35.

Primary Examiner—Howard T. Mars
Attorney, Agent, or Firm—Joseph J. Allocca; Ernest A. Forzano

[57] **ABSTRACT**

A new method for the synthesis of hydrocarbons with chain lengths of from 2 to 10 carbon atoms inclusive and for selective generation of olefinic hydrocarbons in this carbon number range with reduced wax formation, said products being synthesized from CO and H₂ at pressures of from 100 to 3100 kPa which method comprises the steps of passing a synthesis gas stream of CO and H₂ at a H₂/CO ratio of from 0.1-10 at a space velocity of from 100 hr⁻¹ to 50,000 hr⁻¹ over a catalyst comprising from 0.01 to 15 wt. % ruthenium on TiO₂, other titanium-containing oxides or mixtures of said titanium-containing oxides for a time sufficient to effect the generation of desired olefinic hydrocarbon products, at a temperature of from 100° to 500° C and a pressure of from 100 to 10⁵ kPa (1-1000 atm). The supported ruthenium catalyst has a BET surface area of from 10 to 60 m²g⁻¹ of total catalyst with a ruthenium crystallite size of preferably less than 5 nm (50 Å).

23 Claims, No Drawings

http://www.PatentGopher.com

HYDROCARBON SYNTHESIS FROM CO AND H₂ USING Ru SUPPORTED ON A TITANIUM OXIDE

Ruthenium supported on TiO₂, other titanium-containing oxides or mixtures of titanium oxides results in a catalyst system which exhibits superior hydrocarbon synthesis characteristics. Such supported ruthenium catalysts exhibit selectivity to olefinic products of from 2 to 10 carbons inclusive in processes for olefin generation accompanied by greater product yields and exhibit improved longevity and tolerance to sulfur, activity maintenance, resistance to ruthenium volatilization in oxidizing atmospheres which might be encountered during catalyst regeneration and reduced wax formation in the synthesis process.

Ruthenium catalysts have been known for 50 years to be the most active of the Group VIII metals in the CO/H₂ synthesis reaction. It was discovered by Pichler (see H. Pichler, *Brennstoff-Chem.* 19, 226 (1938), H. Pichler and H. Buffleb, *Brennstoff-Chem.* 21, 247, 273, 285 (1940)) in 1938 that Ru can produce at low temperatures and very high pressures high molecular weight paraffinic waxes. Because it is such a good hydrogenation catalyst, ruthenium has not been noted for its capability to produce olefins. This is shown by the only study conducted under typical synthesis conditions using supported Ru where at 2160 kPa, 220°-240° C, and H₂/CO ratios of 1 to 3, it was noted that the hydrocarbon product contained only "moderate" amounts of olefins (see F. S. Karn et al, *I&EC Product Res. & Devel.* 4, 265 (1965)). At a H₂/CO ratio of 1, over 85 wt. % of the hydrocarbon product was composed of C₃+ material. In addition, at 100 kPa and 222° C methane was the only hydrocarbon product observed. It is clear then that typical Ru catalysts would be expected to produce primarily high molecular weight paraffins at moderate pressures and methane as the principal product at atmospheric pressure.

Because it is so expensive, only supported, highly dispersed Ru catalysts can be considered for any commercial synthesis process since only in this state can the catalytic activity of most, if not all, of the Ru atoms be utilized. It is necessary then to prepare these catalysts in such a way that they possess a large Ru surface area thereby reducing the weight loading of Ru required to achieve the desired activity. Since it is now possible to produce catalysts in this manner, they may now be seriously considered as candidates for the commercial synthesis of olefins and paraffins from CO and H₂.

DESCRIPTION OF THE INVENTION

A new method for the selective synthesis of olefinic hydrocarbons and particularly olefins of from C₂ to C₁₀ chain length inclusive from CO and H₂ at pressures of from 100 to 3100 kPa which method comprises the steps of passing a synthesis gas stream comprising CO and H₂ at a H₂/CO ratio of from 0.1-10, preferably 0.5-4, most preferably 1-3 at a space velocity of from 100 hr⁻¹ to 50,000 hr⁻¹ over a catalyst comprising from 0.01 to 15 wt. % ruthenium on TiO₂, other titanium-containing oxides or mixtures thereof for a time sufficient to effect the generation of desired olefinic hydrocarbon products at a temperature of from 100° to 500° C, preferably 150°-400° C, most preferably 150°-300° C and a pressure of from 100 to 10⁵ kPa, preferably 100-3100 kPa, most preferably, 100-2060 kPa. The supported ruthenium catalyst system used in the instant process

has a total BET surface area of from 10 to 60 m²g⁻¹ with a ruthenium crystallite size of preferably less than 5 nm.

Ruthenium supported on TiO₂, other titanium-containing oxides or mixtures of titanium oxides results in a catalyst system which exhibits superior hydrocarbon synthesis characteristics in synthesis processes. The titanium-containing oxide supports which may be used in the practice of this invention are oxides having surface areas of from 1 to 200 m²g⁻¹, preferably 10-100 m²g⁻¹, most preferably, 25-100 m²g⁻¹. The oxides are selected from the group comprising TiO₂, Al₂O₃-TiO₂, SiO₂-TiO₂, TiO₂-Carbon, ZrTiO₄, alkaline earth titanates (BaTiO₃, CaTiO₃, SrTiO₃, MgTiO₃) alkali titanates (Na₂TiO₃, Li₂TiO₃, K₂TiO₃) and rare earth titanates, preferably, the titanium oxide TiO₂. With most supported metal catalysts, the higher the surface area of the support, the higher the dispersion of the supported metal at a given metal loading. It is therefore, desirable to use a TiO₂ with as high a surface area as possible to maximize the dispersion of the ruthenium metal. However, when working with TiO₂, samples with surface areas of 150 to 250m²g⁻¹ (usually prepared by precipitation techniques) desurface on heating to ~ 500° C. Commercially available TiO₂ made by flame hydrolysis of TiCl₄ has a stable surface area of ~ 60 m²g⁻¹ for thermal treatments at temperatures of ~ 500° C and is therefore the preferred support. For thermal treatments at temperatures below 500° C, TiO₂ prepared by precipitation techniques may be successfully employed. Ruthenium is deposited on the chosen support in a concentration of from 0.01 to 15 wt. %, preferably 0.1 to 10 wt. %, most preferably 0.5 to 5 wt. %, with the ruthenium possessing a crystallite size, as determined by standard techniques such as X-ray diffraction or transmission electron microscopy of from 1 to 20 nm, preferably 1-10 nm, most preferably 1-5 nm.

Using standard experimental techniques, for a ruthenium on TiO₂ system, reduced in hydrogen at 450° C, X-ray diffraction shows no particles of Ru in the reduced catalyst which indicates particles having crystallite sizes of less than 5 nm, which corresponds to a dispersion of greater than 20%.

Ruthenium catalysts supported on TiO₂, other titanium-containing oxides, or mixtures thereof, exhibit selectivity to olefin products, especially C₂-C₁₀ inclusive olefins. Such catalysts, when used in the present system, exhibit improved selectivity to said olefins, improved longevity and tolerance to sulfur and resistance to ruthenium volatilization in oxidizing atmospheres as compared with ruthenium catalysts of the prior art which are supported on materials such as Al₂O₃, SiO₂ or carbon.

The ruthenium catalysts employed in the practice of the instant process are themselves prepared by techniques known in the art for the preparation of other catalysts systems, such as Ru on Al₂O₃, etc. A suitable ruthenium salt, such as ruthenium chloride, ruthenium nitrate or ruthenium acetate, etc., is dissolved in a solvent such as water or any suitable solvent and stirred with the chosen titanium oxide system. Preferably, the support is TiO₂ prepared by flame hydrolysis of TiCl₄, which TiO₂ has a surface area of ~ 60 m²g⁻¹. After thorough mixing the mixture is allowed to dry and then heat treated in air at a temperature of from 100 to 150° C or alternatively may be dried immediately by heating in air at a temperature of between 100° to 150° C for several hours.

The final step however, is the essential step of heat treating the supported ruthenium catalyst, prepared as outlined above, or by similar techniques, in a reducing atmosphere such as hydrogen at a temperature greater than 300° C, preferably greater than 400° C, most preferably, greater than 500° C, for about 0.5 to 4 hours, preferably 1-2 hours.

EXAMPLE I

Ruthenium catalysts with improved selectivity to olefin products and to hydrocarbons with carbon chain lengths of two carbons to ten carbons are obtained by depositing ruthenium on TiO₂ or titanium-containing oxide supports. Thus, a 2% Ru/TiO₂ catalyst is prepared by stirring together 10 grams of TiO₂ and 3ml of RuCl₃ solution containing 0.2 g of ruthenium. The TiO₂ is prepared by the flame hydrolysis of TiCl₄ to give a support with 60 m²g⁻¹ surface area. Titania made by other techniques such as precipitation and calcination of a suitable salt is also satisfactory. After thoroughly mixing the TiO₂ and ruthenium solution, the mixture is dried overnight in air at 110°-120° C.

To illustrate the desirable properties of Ru/TiO₂ catalysts, they were compared to ruthenium supported on conventional supports such as Al₂O₃ or carbon. Thus, a 5% Ru/ η -Al₂O₃ catalyst was prepared by thoroughly mixing 5.26 ml of RuCl₃ solution containing 0.526 grams of ruthenium with 10 grams of η -Al₂O₃. The resulting mixture was dried overnight in air at 110°-120° C. A 4% Ru/carbon catalyst was prepared by thoroughly mixing 6 ml of RuCl₃ solution containing 0.12 grams of ruthenium with 3 grams of carbon with a surface area of ~ 1000 m²g⁻¹. The resultant mixture was dried overnight in air at 110°-120° C.

The desirable selectivity characteristics of TiO₂ or titanium-containing oxide-supported ruthenium catalysts compared to other supports is demonstrated in Tables I, II and III. At 103 kPa total pressure Ru/TiO₂ shows a markedly different product distribution than Ru/Al₂O₃. The formation of methane and very high molecular weight hydrocarbons is suppressed over the Ru/TiO₂ catalysts giving a product spectrum in which the carbon chain length range of two to five carbon atoms is maximized. For Ru/Al₂O₃, much more methane and higher molecular weight hydrocarbons are produced. Ru/TiO₂ also possesses the desirable characteristic that a large fraction of the C₂-C₃ products are olefinic. Thus, this catalyst is particularly suitable for producing from CO and H₂ a product stream which is highly olefinic and with carbon chain lengths of two to five carbon atoms. Olefins such as ethylene, propylene, butenes and pentenes in this range are particularly desirable as chemical intermediates for the production of plastics, rubber, alcohols, ketones and aldehydes, esters and acids.

Table II illustrates the desirable selectivity characteristics of TiO₂ or titanium-containing oxide-supported ruthenium catalysts at higher total pressures of reactants. At 10³ kPa the Ru/TiO₂ makes less methane and C₈+ hydrocarbons than Ru/Al₂O₃ with most of the products from Ru/TiO₂ being in the C₂ to C₇ carbon number range. Ru/TiO₂ thus exhibits improved selectivity to the desirable C₂ to C₇ hydrocarbons. Table II

also illustrates the improved selectivity to olefins of Ru/TiO₂ compared to Ru/Al₂O₃. In the C₂ to C₅ carbon number range 42% of the products are olefins with Ru/TiO₂ whereas only 25% are olefins with Ru/Al₂O₃. Ru/TiO₂ is thus more selective for the production of the desirable olefins with carbon chain lengths of two to five carbon atoms.

Table III compares Ru/TiO₂ with ruthenium on a variety of other supports. Ruthenium supported on TiO₂ or titanium-containing oxide supports produces 42 wt. % of the products with carbon chain lengths of two to five carbon atoms, while ruthenium on Al₂O₃, carbon or ruthenium metal produce only 31%, 2% and 25%, respectively of products in this carbon number range. In addition, the fraction of olefins in the products is greatest for Ru/TiO₂ as indicated by the ethylene/ethane ratios for each catalyst. Ruthenium on Al₂O₃ or carbon, or unsupported ruthenium metal produce little or no ethylene in the C₂ fraction from CO and H₂ under the reaction conditions used in Table III whereas Ru/TiO₂ produces about one-half of the C₂ reaction as ethylene.

TABLE I

Selectivity of Ruthenium Catalysts
(Reaction Conditions: H₂/CO = 1, Pressure = 103 kPa)

Catalyst ^(a)	Temp. (° C)	% CO Conv.	Product Carbon Number	Total	wt % Olefin	wt % Par-affin
				wt %		
2% Ru/TiO ₂	262	0.7	C ₁	26	—	—
			C ₂	17	12	5
			C ₃	28	20	8
			C ₄	19	15	4
			C ₅	10	7	3
			C ₆ +	—	—	—
5% Ru/Al ₂ O ₃	267	1.7	C ₁	47	—	—
			C ₂	13	5	8
			C ₃	21	—	—
			C ₄	7	6	1
			C ₅	6	—	—
			C ₆ +	5	—	—

(1 atm = 103 kPa)

^(a)Each catalyst reduced 1 hour at 450° C prior to introducing feed at the reaction temperature.

TABLE II

Selectivity of Ruthenium Catalysts
(Reaction Conditions: H₂/CO = 1, Pressure = 980 kPa)

Catalyst ^(a)	Temp. (° C)	% CO Conv.	Product Carbon Number	Total	Wt % Olefin	Wt. % Par-affin
				wt %		
2% Ru/TiO ₂	267	7	C ₁	14	—	—
			C ₂	6	2	4
			C ₃	21	14	7
			C ₄	20	16	4
			C ₅	17	10	7
			C ₆	13	8	5
			C ₇	9	5	4
			C ₈ +	—	—	—
5% Ru/ η -Al ₂ O ₃	274	10	C ₁	24	—	—
			C ₂	6	1	5
			C ₃	16	12	4
			C ₄	11	6	5
			C ₅	12	6	6
			C ₆	11	—	—
			C ₇	9	—	—
			C ₈ +	12	—	—

(1 atm = 103 kPa)

^(a)Each catalyst reduced 1 hour at 450° C prior to introducing feed at the reaction temperature.

TABLE III

Catalyst	T° C	% CO Conv.	Product Mole %						
			CH ₄	C ₂ H ₄	C ₂ H ₆	C ₃ H ₆ C ₃ H ₈	C ₄ H ₈ C ₄ H ₁₀	C ₅ H ₁₀ C ₅ H ₁₂	C ₆ +
2% Ru/TiO ₂ ^(a)	228	1.8	54	6	5	16	10	5	4
5% Ru/Al ₂ O ₃ ^(a)	229	10.6	66	1	9	6	9	6	4
4% Ru/Carbon ^(b)	234	1.6	98	0	2	0	0	0	0
Ru Metal Powder ^(c)	217	27.1	74	0	13	8	3	1	1

^(a)Catalysts reduced for 1 hour at 450° C before feed introduced.

^(b)Catalyst reduced 1 hour at 400° C before feed introduced.

^(c)Catalyst reduced 1 hour at 300° C before feed introduced.

What is claimed is:

1. A process for the selective synthesis of olefins from C₂ to C₁₀ chain length inclusive, said process comprising the steps of passing H₂ and CO at a H₂/CO ratio of 0.1 to 10 over a catalyst comprising ruthenium on a titanium-containing oxide support, wherein said titanium-containing oxide support is selected from the group consisting of TiO₂, ZrTiO₄, TiO₂-carbon, TiO₂-Al₂O₃, TiO₂-SiO₂, alkaline earth titanates, alkali titanates, rare earth titanates and mixtures thereof, at a space velocity of from 100 to 50,000 V/V/Hr. at a temperature of from 100° to 500° C., at a pressure of from 100 to 10³kPa for a time sufficient to effect the generation of the desired olefinic products in the desired ratio wherein the concentration of said ruthenium in said catalyst is from 0.01 to 15% by weight.

2. The process of claim 1 wherein the titanium-containing oxide is TiO₂.

3. The process of claim 1 wherein the titanium-containing oxide has a surface area of from 1 to 200 m²g⁻¹.

4. The process of claim 2 wherein the TiO₂ has a surface area of from 25 to 100 m²g⁻¹.

5. The process of claim 1 wherein the ruthenium concentration is from 0.5 to 5 wt. %.

6. The process of claim 1 wherein the catalyst consisting of ruthenium supported on a titanium-containing oxide has a ruthenium particle crystallite size of from 1 to 20 nm.

7. The process of claim 6 wherein the catalyst consisting of ruthenium supported on a titanium-containing oxide has a ruthenium particle crystallite size of less than 5 nm.

8. The process of claim 1 wherein the catalyst consisting of ruthenium supported on a titanium-containing oxide has a surface area of from 10 to 60 m²g⁻¹.

9. The process of claim 1 wherein the H₂/CO ratio is 4.0 to 0.5, the temperature is from 150° to 400° C and the pressure is from 100 to 3100 kPa.

10. The process of claim 1 wherein the H₂/CO ratio is 3 to 1, the temperature is from 150° to 300° C and the pressure is from 100 to 2060 kPa.

11. The process of claim 2 wherein the ruthenium on titanium oxide catalyst has a weight loading of ruthenium of from 0.5 to 5 wt. % based on total catalyst.

12. The process of claim 2 wherein the ruthenium on titanium oxide catalyst has a ruthenium crystallite size of less than 5 nm (<50A).

13. The process of claim 3 wherein the titanium-containing oxide has a surface area of from 10 to 100 m²g⁻¹.

14. The process of claim 3 wherein the titanium-containing oxide has a surface area of from 25 to 100 m²g⁻¹.

15. The process of claim 1 wherein the ruthenium concentration is from 0.1 to 10 wt. %.

16. The process of claim 6 wherein the catalyst consisting of ruthenium supported on a titanium-containing oxide has a ruthenium particle crystallite size of from 1 - 10 nm.

17. The process of claim 2 wherein the TiO₂ has a surface area of from 1 - 200 m²g⁻¹.

18. The process of claim 2 wherein the TiO₂ has a surface area of 10 - 100 m²g⁻¹.

19. The process of claim 2 wherein the catalyst consisting of ruthenium supported on TiO₂ has a ruthenium particle crystallite size of from 1 - 20 nm.

20. The process of claim 19 wherein the catalyst consisting of ruthenium supported on TiO₂ has a ruthenium particle crystallite size of from 1 - 10 nm.

21. The process of claim 2 wherein the ruthenium on TiO₂ catalyst has a weight loading of ruthenium of from 0.1 to 10 wt. %, based on total catalyst.

22. The process of claim 2 wherein the H₂/CO ratio is 4.0 to 0.5, the temperature is from 150° to 400° C. and the pressure is from 100 to 3100 kPa.

23. The process of claim 2 wherein the H₂/CO ratio is 3 to 1, the temperature is from 150° to 300° C. and the pressure is from 100 to 2060 kPa.

* * * * *

55

60

65