

19



Europäisches Patentamt
European Patent Office
Office européen des brevets

11 Publication number:

**0 031 243
A1**

12

EUROPEAN PATENT APPLICATION

21 Application number: 80304580.6

51 Int. Cl.³: **C 07 C 31/04**
C 07 C 29/15, B 01 J 23/56

22 Date of filing: 18.12.80

30 Priority: 19.12.79 US 105407

43 Date of publication of application:
01.07.81 Bulletin 81/26

84 Designated Contracting States:
BE DE FR GB IT

71 Applicant: **UNION CARBIDE CORPORATION**
270, Park Avenue
New York, N.Y. 10017(US)

72 Inventor: **Kaiser, Steven William**
900 Glendale
South Charleston West Virginia 25303(US)

74 Representative: **McCall, John Douglas et al,**
W.P. THOMPSON & CO. Coopers Building Church Street
Liverpool L1 3AB(GB)

54 Preparation of methanol from synthesis gas with promoted palladium catalysts.

57 A catalytic process for the production of methanol from hydrogen and carbon monoxide at a temperature of from about 200°C to about 400°C and a pressure of from about 150 to about 20,000 psia which comprises effecting the reaction in the presence of a heterogeneous solid catalyst comprising palladium and lithium, magnesium, strontium, barium, molybdenum or a mixture thereof.

EP 0 031 243 A1

1.

DESCRIPTION"PREPARATION OF METHANOL FROM SYNTHESIS GAS WITH
PROMOTED PALLADIUM CATALYSTS"

This application is related to copending European application Ref: A2326/U filed on even date herewith which describes a process for producing methanol from synthesis gas using a catalyst containing palladium and calcium.

10 This invention relates, in general, to a catalytic process for producing methanol from synthesis gas. More particularly, the invention concerns reacting synthesis gas in the presence of a promoted palladium catalyst to form methanol at high carbon efficiencies and improved rates of production.

Methanol is an increasingly important feed-stock for the production of carbon-based chemicals. Existing or proposed commercial processes using methanol include dehydrogenation to form formaldehyde, carbonylation to form acetic acid, homologation to form ethanol and reactions over zeolitic materials to form gasoline-
20 grade fractions. The presently anticipated increase in commercial methanol manufacture has underscored the need for new and improved catalysts characterized by high carbon efficiencies and good productivity to methanol.

The use of catalysts to influence the product distribution resulting from the hydrogenation of carbon monoxide is well known in the art. Among the vast array of products obtainable from the reaction of carbon monoxide and hydrogen, methane is thermodynamically the most favored, longer chain hydrocarbons are next followed by
30 high molecular weight alcohols with methanol being

2.

thermodynamically one of the least stable products which can be formed. Hence, specific catalysts for methanol synthesis are required in order to selectively produce methanol at high reaction efficiencies from synthesis gas. The prevalent commercial catalysts today for methanol manufacture from a synthesis gas are composed of oxides and mixed oxides of chromium, zinc and copper.

Palladium is also known in the art as an effective methanol catalyst. U. S. Patent No. 4,119,656 to Poutsma et al., dated October 10, 1978, discloses the formation of hydroxylated hydrocarbons such as methanol and ethylene glycol from synthesis gas in the presence of a palladium catalyst. While the process of Poutsma et al is characterized by very high selectivities of methanol, generally above 95 percent, the productivity of methanol is substantially below that achieved in commercial methanol synthesis processes. Hence, it would be desirable to significantly improve the methanol production rate of the Poutsma et al process while maintaining its high process efficiency.

This invention describes a catalyst for the production of methanol from the reaction of carbon monoxide and hydrogen, such catalyst being an improvement of that disclosed in the aforementioned U. S. Patent 4,119,656. The process of the invention involves contacting a heterogeneous solid catalyst comprising palladium and an effective amount of a metal additive selected from the group consisting of lithium, magnesium, strontium, barium, molybdenum and mixtures of same with

3.

synthesis gas comprising carbon monoxide and hydrogen at a temperature of from about 200°C to about 400°C and a pressure of from about 150 to about 20,000 psia to selectively form methanol.

The preferred reaction conditions are a temperature from about 250°C to about 350°C and a pressure from about 150 to about 3,000 psia.

10 The present invention is predicated on the discovery that the production rate of methanol in the aforementioned Poutsma et al process can be significantly enhanced by the addition of a metal promoter or additive as herein described to a palladium catalyst such as utilized in the Poutsma et al process. Thus, up to a three-fold increase in methanol manufacture can be achieved in accordance with the invention relative to the process of U. S. Patent 4,119,656 without adversely affecting the very high process efficiencies achieved with such process.

20 In accordance with the invention, a synthesis gas containing carbon monoxide and hydrogen is contacted with a palladium catalyst containing one or more of the aforementioned metal promoters under reaction conditions of temperature and pressure which thermodynamically favor the formation of methanol relative to hydrocarbons, such as, methane. The selectivity of the reaction to methanol is generally at least 90 percent, more typically about 95 percent or greater, and under preferred reaction conditions about 98 percent.

Molybdenum is the preferred metal promoter insofar as methanol production is concerned, albeit less

4.

preferred than lithium, magnesium, strontium and/or barium with regard to reaction efficiency to methanol. That is, the use of molybdenum in conjunction with palladium results in a significant increase in the manufacture of reaction products which although comprised primarily of methanol also include methane, two or more carbon atom hydrocarbons, and hydroxylated compounds, such as, ethanol. In contrast thereto, the use of lithium, magnesium, strontium and/or barium in accordance with the invention results in a generally higher reaction selectivity to methanol, typically above 95%, and under preferred reaction conditions about 98%, but a lower reaction productivity relative to the use of molybdenum.

Reaction selectivity, or efficiency, is defined herein as the percentage of carbon atoms converted from carbon monoxide to a specified compound other than CO_2 .

The promoted palladium catalyst of the invention comprises palladium and one or more of the aforementioned metal additives employed in a fine dispersion or slurried in a high boiling point solvent (i.e. one which boils above the reaction temperature under the reaction conditions), or alternatively, supported upon an inert carrier material. The preferred mode of operation is to support the palladium catalyst and the desired metal additive(s) on a particulate high surface area support and the supported combination then placed into the reaction zone. In an alternate embodiment of the invention, the desired amount of metal additive is incorporated into the support during formulation so as to be an integral part of the finished support, the palladium being thereafter deposited

5.

upon such support. If desired, a portion of the metal additive may be incorporated into the support and the remainder deposited upon the support with the palladium catalyst.

A support having a surface area of at least 1.0 square meters per gram (BET low temperature nitrogen adsorption isotherm method) is generally preferred, a surface area above 10 square meters per gram being particularly desirable, although surface area is not the sole determinative variable. Silica gel is a preferred catalyst support with alpha alumina, gamma alumina, magnesia, carbon, zirconia and titania being among the useful albeit less desirable catalyst supports.

For the purpose of this invention it is believed that palladium deposited on particles of a compound of one or more of the aforementioned metal additives such as the oxide or carbonate is substantially the same as palladium and such additive(s) deposited on any of the above support materials.

On the basis of experience to date, the amount of palladium on the support preferably ranges from about 0.1 wt. % to about 20 wt. %, based on the weight of the support material. More preferably, the amount of palladium is within the range of about 2 to about 5 weight percent. The amount of metal additive in the catalyst may vary depending upon the particular metal additive; the catalyst support employed and the method of catalyst preparation. For a given additive, catalyst support, and method of catalyst preparation, the optimum concentration of additive is readily determined by simple experimentation. For

6.

lithium, magnesium, strontium and/or barium additives supported on a silica gel support, the preferred concentration of additive is from about .05% to about 1% by weight of the catalyst support. For molybdenum, concentrations of from about 0.1 to about 5.0% by weight of the support are suitable with concentrations of from about 0.2 to about 3.0% by weight being preferred.

Palladium and one or more of the aforementioned additives may be deposited onto the catalyst base or support by any of the commonly accepted techniques for catalyst preparation, as for example, impregnation from a solution containing the salts of palladium and the desired metal additive(s), precipitation, coprecipitation, or ion exchange. Typically, a solution of heat decomposable inorganic or organic palladium compound and a compound of lithium, magnesium, strontium, barium and/or molybdenum is contacted with the support material and then dried and heated, the latter under reducing conditions to form the finely dispersed promoted palladium catalyst.

The metal additive and palladium metal catalyst may be deposited concurrently or sequentially. That is, palladium may be codeposited with the metal additive of choice or it may be deposited upon the carrier either before or after such metal additive. Similarly, if more than one metal additive is used, the additives themselves may be deposited concurrently or in any desired sequence.

The palladium deposited is typically in metal form, desirably as fine discrete particles. The form of additive metal component is, however, not completely

7.

understood. It may be chemically associated with the palladium or it may be a physical admixture. For example, the additive may be alloyed with the palladium or not, in the form of a metal or an oxidized state of the metal, or it may be a silicate, carbonate, or other compound of the additive or the like.

Conditions of temperature, of pressure, and of gas composition are within the ranges that are essentially conventional for synthesis gas conversion to methanol for palladium catalysts. The reaction temperature markedly affects the productivity of the reaction with regard to methanol formation. Thus, an increase in reaction temperature results in an increased conversion to methanol with the proviso that the reaction pressure is correspondingly increased to avoid thermodynamic limitations. Increased pressure enhances the productivity of the reaction but may affect product distribution. Thus, for example, at increased pressures there may be an increased proportion of impurities, such as, ethanol and methyl formate in the product mixture. For purposes of economy, the reaction pressure is preferably within the range of 150 - 3,000 psia although a reaction pressure of from about 150 - 20,000 psia is generally suitable.

The preferred space velocities in the flow reactor may vary from about 10^2 to about 10^6 per hour; space velocity being defined as volumes of reactant gas at 0°C and 760 mm. mercury pressure, per volume of catalyst, per hour. Generally, the higher the space velocity, the more economical the overall reaction, although at excessively high space velocities the productivity of the reaction is adversely affected while excessively low space velocities

8.

cause the production of a more diverse spectrum of reaction products.

The molar ratio of hydrogen to carbon monoxide in the synthesis gas preferably is from about 1:10 to 10:1. More preferably the hydrogen to carbon monoxide ratio is within the range of at least 1:5 to 5:1, a ratio of about 2:1 being most preferred. Increasing the percentage of hydrogen relative to carbon monoxide in the gas mixture increases the rate of the reaction, but adversely affects the economics of the overall process.

The catalysts cited in the examples below were all prepared by essentially the following sequence of steps: The desired quantities of palladium (II) chloride, ammonium paramolybdate, and the nitrate salts of lithium, magnesium, strontium and barium, depending upon the desired catalyst composition, were dissolved in a 1:1 HCl/H₂O (by volume) solution at ambient temperature. The volume of solution was chosen to just fill the void volume (pores) of the support sample being impregnated. DavisonTM Grade 59 silica gel (8-20 mesh - U. S. Sieves) was placed in a vacuum flask. The top of the flask was sealed with a rubber septum, and the flask was evacuated through the side arm. A syringe needle was then used to inject the solution onto the evacuated support. When addition was complete, the impregnated support was allowed to stand at one atmosphere for approximately 30 minutes. It was then carefully dried in a nitrogen atmosphere using the following sequence: 80°C. (for 1 hr.); 110°C. (2 hrs.); 150°C. (2 hrs.); and about 300°C. (2 hrs.). The dried,

9.

impregnated support was placed in a quartz tube through which hydrogen was continuously passed. The temperature was raised from 100° to 500°C., over a five hour period and then held at 500°C. for 1 hour. The reduced catalyst was then cooled to ambient temperature over a period of approximately two hours in a flowing hydrogen atmosphere and finally flushed with nitrogen before being removed.

10 In order to remove significant amounts of impurities which were present in the support material as received from the manufacturer, the DavisonTM Grade 59 silica support was initially "washed" with oxalic acid prior to being used as the catalyst support. Such treatment consisted of passing a mixture of oxalic acid, glycerine, and water in proportions of 1:1.5:2.5 by weight, respectively, through a bed of support material (length/diameter ratio of about 20 to 25) contained within a glass tube which drained through a stopcock at its base. The contents of the tube were maintained at
20 about 90°C by means of resistance heating wire wrapped around the exterior of the tube. About 2.5 volumes of oxalic acid solution were used to wash one volume of 8-20 mesh silica gel over a three-hour period. The material was then washed with about six volumes of distilled water at 90°C over a period of about four hours and then dried at 350°C for about four hours.

The chemical analysis of the silica gel for iron, aluminum, sodium and calcium impurities following the above-described treatment was as follows:

10.

Iron as Fe_2O_3	0.01% \pm 0.004%
Aluminum as Al_2O_3	0.01% \pm 0.004%
Sodium as Na_2O	0.01% \pm 0.004%
Calcium as CaO	0.02% \pm 0.01%

The reactor used in the following Examples was an internally silver-plated 316 stainless steel, bottom-agitated "Magnedrive" autoclave with a centrally positioned catalyst basket and a side product effluent line. It is of the type depicted in Figure 1 of the paper by Berty, Hambrick, Malone and Ullock, entitled "Reactor for Vapor-Phase Catalytic Studies", presented as Preprint 42E at the Symposium on Advances in High-Pressure Technology - Part II, Sixty Fourth National Meeting of the American Institute of Chemical Engineers (AIChE), at New Orleans, Louisiana, on March 16-20, 1969 and obtainable from AIChE at 345 East 47th. Street, New York, New York 10017. A variable speed, magnetically driven fan continuously recirculated the reaction mixture over the catalyst bed. The following modifications were found to facilitate operation:

1. Hydrogen feed gas was introduced continuously at the bottom of the autoclave through the well for the shaft of the Magnedrive agitator.
2. Carbon monoxide feed gas was introduced continuously through a separate port at the bottom of the autoclave, in order to avoid a hydrogen-rich zone in the autoclave.

11.

Effluent gases were removed through a port in the side of the reactor. Condensable liquid products were removed from the exit stream in a brine-cooled condenser at ca. 5 to 10°C and were collected in a holding tank under pressure. The non-condensable components of the exit stream were vented through a wet test meter at atmospheric pressure to determine their total volume. A rubber septum in the atmospheric pressure line permitted syringe sampling of the non-condensable gases. No external recycle was employed.

10

The weight of a given volume of catalyst sample was determined and the sample was placed in the catalyst basket. The quantity of catalyst charged was from about 15 to about 50 cc. depending upon the particular sample. Silver-plated screens and thin layers of glass wool were placed above and below the catalyst bed to prevent circulation of solid fines. The catalyst basket was charged to the reactor, and the reactor then sealed. The sealed reactor and the process lines were pressure tested at operating pressure. Nitrogen, hydrogen, or a mixture of the two was used for this test.

20

When the reactor was shown to be leak free, pure hydrogen was passed through the reactor, and the temperature raised to about 240°C. The hydrogen and carbon monoxide flows were then adjusted at the desired molar ratio to give a total purge rate of approximately 500 STP* liters/hr. This corresponds to a space velocity of from about 10,000 to about 33,000 STP volumes of gas per volume of catalyst per hour depending upon the volume of

*"STP" means standard temperature and pressure defined as 0°C and 1 atm. pressure.

12.

catalyst charged in the particular example. The hydrogen-carbon monoxide ratio was determined by gas chromatographic analysis of an effluent gas aliquot.

When the appropriate gas composition was obtained, the reactor temperature was raised to 300°C. A period from about 0.5 hour to about one hour was allowed for the reactor to reach a steady-state at this temperature. The liquid product trap was then drained, a wet test meter reading was taken, and the time was noted as the beginning of a run. During the course of a run, one or more effluent gas samples were analyzed for hydrogen, carbon monoxide, methane, C₂ and C₃ hydrocarbons, methanol, ethanol, methyl formate, dimethyl ether and acetaldehyde. At the end of a run, the liquid product was collected, and the volume of effluent gas was noted. The liquid product was analyzed by gas chromatography.

10

The results of the tests are shown in Tables I and II. Examples B to L of Table I demonstrate the effect of the various promoters on the rate of methanol production relative to the unpromoted catalyst of Example A.

20

Examples M to P of Table II demonstrate the efficacy of the invention with alpha and gamma alumina catalyst supports. In addition, the examples demonstrate that an increase in methanol productivity can be achieved in accordance with the invention by depositing the metal additive upon the support prior to the deposition of the palladium catalyst rather than concurrently therewith as in the examples of Table I.

13.

TABLE I

METHANOL PRODUCTION DATA^(a) FOR
SUPPORTED PALLADIUM CATALYSTS^(b)
CONTAINING LITHIUM, MAGNESIUM,
STRONTIUM, BARIUM OR MOLYBDENUM

<u>EXAMPLE</u>	<u>PROMOTER</u>	<u>RATE TO METHANOL</u> ^(c)
A	None	9.2
B	0.1% Li	16.3
C	0.2% Li	19.3
10 D	0.4% Li	11.2
E	0.1% Mg	11.8
F	0.2% Mg	16.8
G	0.4% Mg	12.4
H	0.2% Sr	20.2
I	0.2% Ba	16.1
J	0.69% Ba	15.3
K	0.2% Mo	14.9
L	2.0% Mo	28

20 (a) Catalysts were tested at 300°C and a reaction pressure of 2,500 psia using a 1:1 molar ratio of H₂:CO synthesis gas composition at a space velocity of 10,000 hr⁻¹.

(b) The catalysts consist of 5 weight percent Pd plus the indicated weight percent of promoter supported on DavisonTM Grade 59 silica gel support. The weight percent of each component is based on the weight of the support.

(c) "Rate" is the rate of synthesis of methanol in pounds of product per cubic foot of catalyst per hour.

TABLE II
 METHANOL PRODUCTION DATA (a) FOR 2.5 WEIGHT PERCENT PALLADIUM CATALYSTS SUPPORTED ON ALPHA OR
 GAMMA ALUMINA (b)

EXAMPLE	SUPPORT	RATE TO METHANOL (c)
M	α -Al ₂ O ₃	5.0
N	α -Al ₂ O ₃ + 3% BaO (d)	7.7
O	γ -Al ₂ O ₃	1.7 (e)
P	γ -Al ₂ O ₃ + 7.9% BaO (d)	4.2 (e)

(a) Catalysts were tested at 300°C and a reaction pressure of 2,500 psia using a 1:1 molar ratio of H₂:CO synthesis gas composition at a space velocity of 26,000 hr⁻¹.

(b) The supports of all four Examples were manufactured by Norton Company.

(c) The rate of synthesis of methanol is expressed in pounds of product per cubic foot of catalyst per hour.

(d) Support was prepared by impregnating the alumina with an aqueous solution of barium nitrate, drying and calcining in air at 500°C for two hours.

(e) The values of methanol production for Examples O and P comprise the rate to methanol plus the rate of dimethyl ether calculated as methanol. This assumes that dimethyl ether results from the dehydration of two molecules of methanol at acid sites on the support.

15.

CLAIMS

1. A heterogeneous catalytic process for the production of methanol characterised in that hydrogen and carbon monoxide are reacted at a temperature of
5 from about 200°C to about 400°C and a pressure of from about 150 to about 20,000 psia, in the presence of a heterogeneous solid catalyst containing palladium and lithium, magnesium, strontium, barium or molybdenum or a mixture thereof.

10 2. A process according to claim 1 characterised in that the catalyst is supported on silica gel.

3. A process according to claim 2 characterised in that the support has a surface area of at least 1.0 square meter per gram.

15 4. A process according to claim 1, 2 or 3 characterised in that the palladium concentration or the catalyst support is from about 0.1 to about 20% by weight based on the weight of the support.

20 5. A process according to claim 4 characterised in that the palladium concentration on the catalyst support is from about 2 to about 5% by weight based on the weight of the support.

25 6. A process according to any of claims 1 to 5 characterised in that the catalyst contains palladium and molybdenum.

7. A process according to claim 6 characterised in that the molybdenum concentration on the catalyst support is from about 0.2% to about 3.0% by weight of the support.

30 8. A process according to any of claims 1 to 7 characterised in that the reaction temperature is from about 250°C to about 350°C and the reaction pressure is from about 150 psia to about 3000 psia.

35 9. A process according to any of claims 1 to 8 characterised in that the hydrogen and carbon

16.

monoxide are in a volume ratio of from about 1:10 to about 10:1.

10. A process according to claim 9 characterised in that the ratio is from about 1:5 to about 5:1.

5 11. A process according to claim 10 characterised in that the ratio is about 2:1.

10 12. A process according to any of claims 1 to 11 characterised in that the space velocity of the hydrogen and carbon monoxide is from about 10^2 to about 10^6 per hour.

0031243

European Patent
Office

EUROPEAN SEARCH REPORT

Application number
EP 80304580.6

DOCUMENTS CONSIDERED TO BE RELEVANT			CLASSIFICATION OF THE APPLICATION (Int. Cl.)
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	
	<p><u>AT - B - 105 591</u> (I.G. FARBEN-INDUSTRIE) + Page 3, line 60 + --</p> <p><u>US - A - 1 681 753</u> (H.H. STORCH) + Claims; page 2, lines 87-109 + --</p>	<p>1,6,8,9</p> <p>1,4,8-10,12</p>	<p>C 07 C 31/04 C 07 C 29/15 B 01 J 23/56</p>
D	<p><u>US - A - 4 119 656</u> (POUTSMA et al.) + Description of experimental 12, procedure + -----</p>	<p>1-5,8-10,12</p>	<p>TECHNICAL FIELDS SEARCHED (Int. Cl.)</p> <p>C 07 C 31/00 C 07 C 29/00 B 01 J</p>
			CATEGORY OF CITED DOCUMENTS
			<p>X: particularly relevant A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention E: conflicting application D: document cited in the application L: citation for other reasons</p>
			<p>&. member of the same patent family, corresponding document</p>
X	The present search report has been drawn up for all claims		
Place of search	Date of completion of the search	Examiner	
VIENNA	17-03-1981	KÖRBER	