



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C10J 3/06, 3/14, 3/66</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 96/40843</b> <b>(43) International Publication Date:</b> 19 December 1996 (19.12.96)
<b>(21) International Application Number:</b> PCT/US96/09628 <b>(22) International Filing Date:</b> 7 June 1996 (07.06.96)  <b>(30) Priority Data:</b> 08/486,372                      7 June 1995 (07.06.95)                      US  <b>(71) Applicants:</b> HYLSA S.A. DE C.V. [MX/MX]; Avenida Munich 101, San Nicolás de los Garza, Nuevo León (MX). PROLER ENVIRONMENTAL SERVICES, INC. [US/US]; 15630 Jacintoport Boulevard, Houston, TX 77015 (US).  <b>(72) Inventors:</b> BISHOP, Norman, G.; 234 Taranto Street, Houston, TX 77015 (US). VIRAMONTES-BROWN, Ricardo; Mirador de la Sierra 347, Colonia Lomas del Valle, Garza Garcia, Nuevo León (MX).  <b>(74) Agent:</b> SAFFORD, A., Thomas, S.; Curtis, Morris & Safford, P.C., 530 Fifth Avenue, New York, NY 10036 (US).		<b>(81) Designated States:</b> CA, JP, MX, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> METHOD AND APPARATUS FOR GASIFICATION OF ORGANIC MATERIALS		
<b>(57) Abstract</b> <p>A process and apparatus for gasification of organic materials (typically incorporated in domestic and industrial wastes, including auto shredder residues) to produce useful synthesis gas (with a major content CO &amp; H<sub>2</sub>) with effectively non-toxic ash residue by means of at least one continuously operated burner, preferably stoichiometrically balanced (1:2 for natural gas/oxygen) at least at startup and shut down (optionally with some excess of oxygen, usually under steady-state conditions, such as at a ratio of 1:4 or higher, especially if the charge has well over 18 % water content), directed into a primary single stage reaction zone (through an opening in common with the effluent product gas discharged therefrom such as to assure intimate contact therebetween), which zone contains a tumbling charge in a rotating barrel-shaped horizontal reactor thus heated to from about 650 to about 800 °C (below the incipient fusion temperature of the charge) and controlled to remain in such temperature range (by adjustment of the burner volume and fuel-to-oxygen ratio for any given charge) resulting in thermally cracking and gasifying the organic materials in the charge and reacting the complex hydrocarbons and gas evolved (1) normally with the CO<sub>2</sub> and H<sub>2</sub>O derived from burner combustion of a fuel and oxygen-containing gas at a high flame temperature, typically 2500 to 3000 °C, (2) with excess oxygen, and/or (3) partially with H<sub>2</sub>O or CO<sub>2</sub> otherwise added to or, present in, the charge.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic			SE	Sweden
CG	Congo	KR	Republic of Korea	SG	Singapore
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LR	Liberia	SZ	Swaziland
CS	Czechoslovakia	LT	Lithuania	TD	Chad
CZ	Czech Republic	LU	Luxembourg	TG	Togo
DE	Germany	LV	Latvia	TJ	Tajikistan
DK	Denmark	MC	Monaco	TT	Trinidad and Tobago
EE	Estonia	MD	Republic of Moldova	UA	Ukraine
ES	Spain	MG	Madagascar	UG	Uganda
FI	Finland	ML	Mali	US	United States of America
FR	France	MN	Mongolia	UZ	Uzbekistan
GA	Gabon	MR	Mauritania	VN	Viet Nam

**METHOD AND APPARATUS FOR GASIFICATION  
OF ORGANIC MATERIALS**

**RELATED APPLICATIONS**

This application is a division and continuation-in-part of application Serial No. 08/158,195, filed November 24, 1993 (due to be issued as Patent No. 5,425,792 on June 20, 1995), which in turn  
5 was a File Wrapper Continuation of then co-pending parent Application Serial No. 07/879,608, filed May 7, 1992 (the contents of which are incorporated herein by reference).

**FIELD OF THE INVENTION**

The present invention relates to a method and  
10 apparatus for producing reducing gases having a high content of hydrogen and carbon monoxide, commonly known as synthesis gas (or syngas), from solid organic residues. More particularly the invention relates to a method and apparatus for gasifying industrial and  
15 domestic wastes of several types, including the non-metallic residues of automobile scrap, known as Auto Shredder Residues (ASR) also called "fluff", tire chips, residues from the petrochemical, polymer and plastics industries, and in general wastes of organic compounds  
20 (including even liquids such as used motor oil), to produce a gas having a high content of hydrogen and carbon monoxide (typically more than 50%, or even well over 65% on a dry basis) which can be utilized as raw material in other industrial processes, for example, to  
25 reduce iron ores to metallic iron in the ironmaking processes known as Direct Reduction processes, or to be utilized as a source of energy to run an internal combustion engine or to produce steam and/or electricity. In its broader aspects the disclosed method can be used  
30 for devolatilization of coal or of other such non-waste complex molecular sources of carbon and/or hydrogen.

**BACKGROUND OF THE INVENTION**

In these days, and primarily in the industrialized countries, there is a deep concern about the safe disposal of domestic and industrial wastes which have acquired great ecological importance. These wastes often include a substantial proportion of organic content.

Many such wastes often contain toxic substances and are nonbiodegradable. They cannot therefore simply be disposed of in landfills due to contamination problems of air and water. Another alternative to dispose of these wastes is incineration. Normal and simple incineration however is not permitted if the product gases are not duly cleaned because it causes air pollution with toxic chemicals for example, chlorine compounds and nitrogen oxides. In some countries, environmental laws and regulations have been passed which prohibit burial or incineration of these types of wastes. Therefore these alternatives for disposal of such wastes are now subject to many restrictions.

A thorough description of the problems which the shredding industry is facing regarding disposal of fluff and some suggestions for utilization of the energy content of fluff, is found in a paper by M.R. Wolman, W.S. Hubble, I.G. Most and S.L. Natof, presented at the National Waste Processing Conference in Denver, Colorado held on 14 June, 1986, and published by ASME in the proceedings of said conference. This paper reports an investigation funded by the U.S. Department of Energy to develop a viable process to utilize the energy content of fluff. However, the process therein suggested is aimed to carry out a total incineration of the wastes, utilizing the heat from said incineration for steam production, while the present invention is addressed to producing from organic materials a high quality gas as an energy source.

It has also been proposed in the past to carry out a controlled combustion of the organic wastes and to utilize the heat or other values (such as process gases) released by such combustion. Such prior art processes typically gasify organic materials by one of two processes: pyrolysis, that is, thermal decomposition of the materials by indirect heating; or partial combustion of the materials with air or oxygen.

Energy consumption is one of the most important costs in ironmaking. Typical direct reduction processes consume from 2.5 to 3.5 Gigacalories ( $10^9$  calories) per metric ton of product, known as sponge iron or direct reduced iron (DRI). Therefore, many processes have been proposed which utilize all types of available energy sources, such as coal, coke, liquid fuels, natural gas, reducing gases from biomass, nuclear energy and solar energy. Most of such proposals have not met practical success, sometimes because the materials and means needed are not yet available or because the relative costs for using such other energy sources are higher than for traditional fossil fuels.

Utilization of organic wastes as a source of energy for the ironmaking industry offers great economic advantages and solves environmental problems in those countries where large quantities of automobiles are scrapped or other wastes with high organic material content are generated. Metallic scrap is recycled for steelmaking. The nonmetallic residues of automobiles (fluff), however, had not been utilized to produce reducing gases useful in the production of iron or in other industrial processes.

#### SUMMARY OF THE INVENTION

Accordingly, it is an object of the present invention to provide a process and apparatus for producing reducing gases, also known as synthesis gas, preferably from low cost carbon/hydrogen sources such as garbage, or other organic containing wastes, and with an

adaptability to accommodate a wide range of different kinds of charges (wet and dry), and which syngas is strongly reducing and thus can be utilized as raw materials in chemical processes and also as fuel.

5 It is a further object to practice the method with a simplified low cost apparatus.

Other objects of the invention will be described hereinbelow or will be evident to those readers skilled in the art.

10 The present invention comprises a process wherein gasification of organic materials is carried out by thermal cracking of complex hydrocarbons and reaction of the gases evolved from such hot materials (preferably at 650°C to 800°C) with carbon dioxide and water  
15 (normally generated by combustion, preferably stoichiometric, at least initially, of a fuel and oxygen from at least one continuous burner at high flame temperature, typically at 2500 to 3000°C). For methane ( $\text{CH}_4$ ), the stoichiometric ratio of the burner fuel-to-oxygen would  
20 be 1:2 (thus natural gas, normally being largely methane, has about the same ratio). The heat produced by the combustion of the fuel etc. is transferred to the gasifiable materials not only by convection, but also by direct radiation from the flame and by tumbling contact  
25 with the glowing interior refractory lining of a rotary reactor. The burner(s) inside the reactor is balanced in positioning and capacity in such a way that it is capable of delivering the necessary heat for thermally decomposing the materials and also for carrying out the  
30 endothermic gaseous reactions of complex hydrocarbons with the water and carbon dioxide, as well as providing necessary amounts of  $\text{H}_2\text{O}$  and  $\text{CO}_2$  reactants for such reactions.

Another feature of the present invention is  
35 that a high quality gas is obtained in a single stage or primary reaction zone. This results in a commercially desirable, simple, low cost, low maintenance, apparatus

having relatively few exposed or moving parts. Prior art processes typically are more complex, often requiring require two stages (with the bulk of the CO and H<sub>2</sub> gas being produced in the second stage). Complex gases within the reaction zone reacts by dissociation according to their thermal/chemical equilibrium composition and become substantially stable simple hydrocarbon-derived gases at lower temperatures [resulting in a stable synthesis gas containing primarily hydrogen (H<sub>2</sub>) and carbon monoxide (CO) {at the very least 50%, or 60% on a dry basis}; and secondarily, carbon dioxide (CO<sub>2</sub>), water (H<sub>2</sub>O), and nitrogen (N<sub>2</sub>); and lesser amounts of residual hydrocarbons, including methane (CH<sub>4</sub>), ethane (C<sub>2</sub>H<sub>6</sub>), ethylene (C<sub>2</sub>H<sub>4</sub>), and acetylene (C<sub>2</sub>H<sub>2</sub>)].

Since one of the advantages of this invention is to supply a high quality process gas at a cost competitive with traditional process gases (such as reformed natural gas), it may be necessary in practicing the invention in one of its broader aspects and under certain market conditions and with certain kinds of "fluff" or other waste materials to use an excess of oxygen stoichiometrically in the burner or to the reactor to reduce the amount of fuel (e.g. natural gas) used in the burner relative to the amount of organic waste gasified. If the cost of natural gas or other standard fuel is too high, the syngas itself can be used in the burner. However, essentially the same thing can be accomplished preferably and more efficiently, by reducing the fuel supplied to the burner to result in a relatively more substantial stoichiometric excess of oxygen. This is essentially the same result (since the oxygen will react in the reaction zone with the disassociated molecules which are the syngas precursors {which however most advantageously are already in a highly reactive state, and which also avoid cost of extra handling of withdrawing, cleaning, and recycling essentially the same "fuel"}). The net result of this alternative will be that

(1) the same amount of garbage will be processed, (2) but at less cost (the syngas effluent precursor normally being less costly than natural gas); however, (3) with less net syngas product. Less syngas can be  
5 advantageous, if it is to be used only as a medium grade fuel (since in essence the natural gas saved is a better fuel). On the other hand, if the product is to be used as a reducing gas, the conversion of natural gas into  $H_2$  and CO has value which to some degree may have to be  
10 balanced into deciding how to adjust the burner feed ratio.

An excess of oxygen is also needed when the charge has more than on the order of 15% water content. In practicing the process according to the present  
15 invention in a process demonstration plant (rated at up to 4,000 pounds organic feed per hour), the primary process burner was initially restricted, for safety reasons, to operating near the theoretical stoichiometric balance (1:2) between fuel and oxygen in order to  
20 eliminate the potential for run-away temperatures and/or atmospheric conditions which could lead to damaging and/or explosive conditions in the hearth of the gasification apparatus. This works well in gasifying Automobile Shredder Residue (ASR). Such ASR materials  
25 almost uniformly contain between 8 and 15 percent moisture ( $H_2O$ ). At such moisture levels the 1:2 fuel-to-oxygen ratio for the primary burner works very efficiently. However, certain feed materials other than ASR, including Municipal Solid Waste (MSW), Recycled  
30 Card-board Residue (RCR), and blends of each with tire chips, are found normally to contain between 25% to 50% free water ( $H_2O$ ). Such larger water content results in less gasification efficiency, when compared with gasifying feed materials, such as ASR, which contain less  
35 water. To improve the gasification efficiency when gasifying feed materials with excessive levels of moisture ( $H_2O$ ) it is necessary to reduce the total water

( $H_2O_{(g)}$ ) content in the gasification reactor. As pre-drying of feed material, such as MSW, would not be economically feasible. The total water introduced into the gasification reactor preferably is lowered by  
5 reducing the amount of fuel fed to the primary process burner relative to the oxygen. How this can be accomplished is exemplified as follows:

-For Firing 1:2 Ratio: Primary Process Burner:  $CH_4 + 2O_2 \rightarrow CO_2 + 2H_2O$

10 Here, 45% of the molecular weight of the combustion product is water.

-Firing 1:4 Ratio: Primary Process Burner:  $CH_4 + 4O_2 \rightarrow CO_2 + 2H_2O + 2O_2$

15 Here, only 25% of the molecular weight of the combustion product is water.

The decrease in water introduced via the primary process burner operating with a 1:4 fuel-to-oxygen ratio amounts to a reduction in total weight of water in the hearth of the gasification reactor of about  
20 30%; assuming the MSW feed material used in this example contained 35% water.

Higher levels of water contained in the source feed, gasification efficiency losses can be offset by reducing the injected fuel relative to injected oxygen in  
25 the primary process burner, provided that the temperature of the atmosphere inside the gasification reactor is retained in the preferred range i.e., 650°C to 800°C (or more preferably, 700°C to 750°C).

$CO_2$  can be added to the reactor with much the  
30 same effect that excessive moisture in the charge would have (serving to be a potentially low cost substitute for natural gas, especially since  $CO_2$  is an unwanted by-product in both the syngas process and in the Direct Reduction of iron process discussed below {which latter  
35 process advantageously is integrated to use syngas}). The  $CO_2$  can be added to the burner so long as the flame and temperature range is adequately maintained, or can be

added directly to the reactor, with a compensating in the burner feed ratio (again so as to maintain the proper temperature range).

In determining the burner ratio for a given charge, not so much excess oxygen should be used as to result in substantial insufficient gasification (by over production of  $H_2O$  &  $CO$  at the expense of  $H_2$  &  $CO$ ) nor to result in excessive temperatures above the preferred range. If as much as  $CO_2$  is present in the syngas product (on a dry basis) that is too much (and in fact would soon result in the temperature rising unacceptably and fuse the residual ash in the reactor. Nor should the modification be so as to result in the need for the prior art's separate two-stage processing (at two significantly different temperatures, with the second stage being in the absence of the solid burden). The limit for excess oxygen for some ASR charges for example might be up to 10% more oxygen relative to the molar content of the fuel. Excessive oxygen, especially during transition, can make control of the process difficult and is safer, if minimized. Alternatively, as economics may dictate, a portion of the previously generated synthesis gas may replace an equivalent amount of natural gas in the burner, up to 100 percent replacement.

In operation, the process for gasification in the preferred apparatus is started over a 4 hour period by heating the internal atmosphere and refractories of the gasification apparatus up to about  $650^{\circ}C$  to  $800^{\circ}C$  prior to introduction of a charge of organic feed material into the hearth area of the apparatus. The heating of the internal atmosphere and the refractories of the apparatus is accomplished by one or more process burners which are operated at a fuel-to-oxygen ratio of 1:2; thus, generating a sufficient volume of burner product gases which are essentially void of uncombusted fuel and free oxygen; i.e.  $CO_2$  and  $H_2O$ . During the heat-up period the hot product gases ( $CO_2$  and  $H_2O$ ) from the

primary process burner pass into and then out of the hearth of the gasification apparatus and through the connecting ducts and gas cleaning system for a period of several hours; thus, preheating the apparatus and  
5 completely purging free oxygen (air) from the entire gasification reactor as well as the product gas management system.

When the refractories and atmosphere inside the hearth of the gasification apparatus reach a temperature  
10 level sufficient to ensure autothermal ignition (above 650°C) of organic gases with any residual free oxygen (air) which may remain in the hearth, a charge of organic feed material is fed into the gasification apparatus. The solid organic feed materials are quickly elevated in  
15 temperature above their melting and boiling temperatures and become organic vapors (gas) which at the autothermal temperature ignites with the last vestige of free oxygen (air) that may remain in the hearth area of the gasification apparatus. The hearth area of the  
20 gasification apparatus quickly becomes void of free oxygen, and the heterogeneous mixture of organic vapors which evolve from the organic feed material enter into the hearth area atmosphere and makes contact with the high temperature flame from the primary process burner  
25 and with the flame products of combustion ( $\text{CO}_2$  and  $\text{H}_2\text{O}$ ). The process of gasification by both exothermic and endothermic reactions result in the reformation and/or dissociation of complex molecular bonds, and stable production of synthesis gas is achieved.

30 As the synthesis gas product passes from the gasification apparatus through the connecting ducts and gas cleaning devices, said synthesis gas pushes the residual startup gases ( $\text{CO}_2$  and  $\text{H}_2\text{O}$ ) forward through the system until the entire gas management system is safely  
35 devoid of startup gas and free oxygen (air); and the potential for generating an explosive mixture of synthesis gas and oxygen is eliminated.

With the steady state gasification process established and the preferred atmospheric temperature in the gasification apparatus being in the range of 650°C to 800°C, and with organic vapors from the organic feed material coming into direct contact with the flame from the primary process burner (which is operating with a 1:2 ratio of fuel-to-oxygen), the total energy input that is necessary to maintain the proper thermal balance to offset endothermic gasification reactions and systems heat losses can be determined. Once the optimum energy input requirement is determined, the base rate of oxygen injection through said burner can be established. For example: assume one ton per hour of organic material is fed to the gasification apparatus (generating  $\frac{1}{2}$  ton of ash); 3 million Btu/hour is required to balance the thermal heat losses; the primary process burner is operating with a 2:1 ratio of fuel as natural gas and oxygen; and further, assume natural gas has a HHV of 1000 Btu/scf; then 3000 scf/h of natural gas and two times that amount (6000 scf/h) of oxygen will be required for stoichiometric combustion. Thus, this example identifies the base rate of oxygen injection.

Once the base oxygen rate is known, fuel to the primary process burner can be slowly decreased while the oxygen injection rate remains at the optimum level as determined above. At the same time, evolving organic vapors are pulled into the vortex of the high velocity flame; thus, replacing the withdrawn fuel (natural gas in this example). The organic vapors rather than natural gas then react with free oxygen contained in the burner flame and the resulting exothermic reactions act to sustain the process atmospheric temperature in the hearth of the gasification apparatus.

Direct combustion between the organic feed material and oxygen injected through the primary burner should not occur due to the ready availability of organic

vapors which mix in the vortex of the primary process burner flame.

As the gasification process is transmuted from one primary burner fuel-to-oxygen ratio to a leaner fuel ratio, oxygen injection remains approximately at the same level as first established by the 1:2 fuel-to-oxygen ratio to the primary process burner. The hearth bed material and atmospheric temperature inside the gasification apparatus remains approximately the same as when operating the primary process burner with a 1:2 fuel-to-oxygen ratio; however, organic vapors contained in the synthesis gas are further reformed to carbon oxides and hydrogen and the hydrocarbon content of organic gases will be reduced toward zero.

The higher ratio of oxygen relative to fuel injected through the primary process burner does not result in a significant increase in the volume percentage of carbon dioxide in the resulting synthesis gas. The example given below was taken from actual operating data and reflects the relative effect the primary process burner firing ratio has on the resulting synthesis gas.

#### Typical Synthesis Gas Produced By

##### Primary Process Burner:

	Analysis	1:2 Ratio	1:4 Ratio
30	H <sub>2</sub>	35.96	36.60
	CO	33.57	34.16
	CO <sub>2</sub>	13.20	13.90
	N <sub>2</sub>	6.01	5.98
	CH <sub>4</sub>	6.80	6.09
35	C <sub>2</sub> H <sub>4</sub>	2.60	2.06
	C <sub>2</sub> H <sub>6</sub>	0.55	0.37
	C <sub>2</sub> H <sub>2</sub>	0.67	0.40
	C <sub>6</sub> H <sub>6</sub>	0.64	0.44
		-----	-----
	Total	100.00	100.00
40	HHV	380	354

In the above example, it is apparent that the percentage of hydrocarbon gases are reduced; thus, a 6.8%

loss in heating value. By further reducing the fuel injection ratio relative to the oxygen injection ratio, the hydrocarbon gases can be ultimately reduced to near zero; and the HHV of the synthesis gas will decrease accordingly to reflect the higher relative percent of H<sub>2</sub> (325 BtU/ft<sup>2</sup>) and CO (323 BtU/ft<sup>3</sup>) contained in the resulting synthesis gas.

Regarding the rotary reactor disclosed in the present invention, it comprises some unique characteristics, namely: it has a continuously operating burner, it has a common opening serving both the burner input and the product effluent output (assuring intimate intermixing of the two) , and the rotary reactor is disposed substantially horizontally with respect to its axis of rotation, while known rotary reactors are inclined so that the materials tumbling inside are caused to move from their charge end to their discharge end. In the rotary reactor of the present invention solids move from the charge end to the discharge end of the reactor by the tumbling action of the rotating vessel, and by the volumetric displacement of reacted solid ash in the bed by unreacted material and inert solids contained in the feed material. The center of the reactor has a bulged shape to give the bed an adequate volume and burden retention time and to conform to the shape of the burner flame.

The process could be carried out in other apparatus such as a generally cylindrical horizontal stationary reactor having internal slightly-angled rotating paddles for tumbling the burden. The latter has some drawbacks such as possible obstruction of the preferred single flame within the reactor chamber and the engineering problems of the paddles and supporting moving parts being within the high temperature regions of the reactor.

Another important feature of the present invention is the unique structure of the high temperature

seals which minimize seepage of outside air into the rotary reactor.

Because the primary process burner is driven by oxygen and fuel (natural gas, syngas, fuel oil, coal, etc.) the nitrogen content of the resulting product gas is normally limited to the nitrogen contained in the organic feed materials; thus, the nitrogen content of the product gas is normally less than ten percent by volume.

A significant aspect of this invention is the mixing of the evolved complex hydrocarbon gases and entrained soot-laden dust particles exiting the reactor into and through the high temperature CO<sub>2</sub> and H<sub>2</sub>O laden recirculating vortex created in the reactor's atmosphere by the counter-current burner gas stream(s). The flame of the primary process burner preferably enters the reactor from a counter-current direction relative to the movement of the burden material. The dust-laden gases generated by this process preferably pass out of the gasification reactor past the burner in a co-current direction relative to the movement of the bed of burden (ash plus gasifying materials).

In the preferred embodiment the reactor rotates on a horizontal axis. On the charge end of the reactor the feed tube to the burden serves the following purposes: (1) as a raw material feed input, and (2) as an atmospheric seal.

Raw material/feed is force-fed by appropriate means such as by a method of extrusion into the gasification reactor by an auger which is of standard commercial design; however, the diameter, length, and taper of the extrusion tube from the auger into the reactor, and the exact position and clearance between the extrusion tube and the rotating reactor have been determined by practice and provide a support for the rotating slip-seal design on the feed-end of the reactor. Solid feed material in the auger serves as part of the atmospheric seal on the feed-end of the reactor. The auger can also

serve a shredding function for oversized pieces of feed material.

Another method for feeding raw material into the reactor involves a hydraulic ram system in which two  
5 sets of hydraulic rams act to compact and force feed the material through a specially designed feed tube.

The nature of the carbonaceous feed material consumed in this process is such that some of the feed material has extremely low melting and volatilization  
10 temperatures; for example, plastics, rubber, and oil/grease. Therefore, it is important that the temperature of the feed material be controlled to prevent premature reactions before the material reaches the inside of the gasification reactor. The design of the feed extrusion  
15 tube and the receiving shaft, or tube through which the feed material is injected and through which the atmospheric seal must be maintained are important parts of the design of this invention.

The process temperature must be controlled to  
20 prevent ash materials in the bed from reaching their temperatures for incipient fusion; thus, preventing the formation of agglomerates in the bed and on the wall of the reactor. The critical ash fusion temperature has been determined by practice for various types of raw feed  
25 material(s). In the ideal practice of the art of this process it is important to maintain the highest possible bed temperature; however, the temperature of the bed should remain below the point of incipient fusion of the ash (hence the preferred 650-800°C range).

30 Non-reactive dust particles which become airborne pass out of the gasification reactor with the product gas into the hot gas discharge hood and then through hot ducts into a cyclone, venturi, or other appropriately adapted commercial equipment. The gas then  
35 passes through a packed-bed column where the acids are scrubbed from the gas and the wash water is adjusted to a

Ph'of about seven (7). The clean gas is then moved by compressor via pipeline to storage for use.

The design of the hot gas discharge hood is another important aspect of this invention. The hot gas discharge hood provides the port support structure for the process burner.

Secondary air/oxygen injector(s) may advantageously be located in the hot gas discharge hood and/or the hot cyclone for the purpose of adding air and/or oxygen to control the temperature of the product gas as it exits the hot gas discharge hood and/or to aid in "finishing" the gasification of any residual hydrocarbons or soot. In practice of this process it is important to maintain the temperature of the product gas at a sufficiently high level until the gas reaches the gas scrubber in order to avoid condensation of any remaining higher molecular weight gases exiting through the hood. The added residence time of the product gas in the hot gas discharge hood and the hot ducts and cyclone leading to the gas scrubber is such as to increase reaction efficiencies between gases and the carbonaceous portion of the dust.

By controlled additions of air and/or oxygen to the hot gas discharge hood, both the temperature and pressure in the discharge hood can be better managed. It has been found that by raising the temperature of the product gas to about 700°C by the injection of about 5 percent by volume of oxygen, the residual complex hydrocarbon gases are predominantly decomposed into carbon monoxide and hydrogen. Ideally, such additions are minimized in order to maintain the quality of the synthesis gas. However, the differing types of burden require adjustments to give the required flexibility to the process. Where the type of burden is not standardized, such flexibility can be accomplished by adjusting the amount of air and/or oxygen additions. The amount of air and/or oxygen added in the hot gas

discharge duct must also be controlled in view of the BTU requirements of the product gas being produced. For example: if the content of nitrogen in the product gas is not critical relative to the end use of the gas, air can  
5 be used exclusively to control the temperature and pressure in the hot gas discharge hood. However, if the content of nitrogen in the process gas must be maintained at a low level in order to meet the required BTU specifications for the gas, oxygen can be used instead of  
10 air.

Because the synthesis gas produced by this process is naturally high in particulate matter and acid gases, the sensible energy of the gas cannot be easily utilized by heat exchangers. On the other hand, the gas  
15 can be controlled to contain between about 1335 Kcal/m<sup>3</sup> and 3557 Kcal/m<sup>3</sup> (150 and 400 BTU/cubic foot) and can be easily scrubbed of particulate matter and acids.

Ash discharged directly from the reactor and from the hot cyclone is very low in leachable metals.  
20 This ash does not require further treatment to be disposed of in an environmentally safe manner. Dust remaining in the product gas following the hot cyclone can be removed in a wet venturi scrubber and recovered from the wash water as a sludge. Such sludge may be  
25 relatively high in leachable metals and therefore may require treatment for environmentally safe disposal.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 shows a partially schematic diagram of a preferred embodiment of the present invention useful  
30 for gasifying organic wastes to yield a synthesis gas and showing a number of exemplary end uses for such gas;

Figure 2 shows a partially schematic vertical cross section in more detail of a rotary reactor of the type illustrated in Figure 1; and

35 Figure 3 shows a cross section of a rotary high temperature seal for the charge end of the reactor shown in Figure 2.

**DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS**

A preferred embodiment of the invention as applied to the gasification of fluff will be described with reference to the appended drawings wherein common  
5 elements are designated by the same numerals in all the figures for easier reference. Referring to Figure 1, showing a partially schematic diagram of the general process and apparatus, numeral 10 designates a charging  
10 hopper wherefrom fluff is introduced into the gasification reactor 18 by an auger feeder 20 having an auger 14 (shown in Figure 2) driven by a motor 12.

Reactor 18 is of the rotary type and is provided with riding rings 22 and 24 which rest and roll on support rolls 26 and 28. Motor 30 causes reactor 18  
15 to rotate about its horizontal axis by means of a suitable transmission device 32, for example of the type of chain and sprocket ring 34, in a manner known in the art.

The discharge end 35 of reactor 18 debouches  
20 into a gas collecting hood 36 having at its upper portion an emergency stack 38, through which the product gases can flow by safety valve 40, and a lower discharge section for collection of the solid residues or ash resulting from gasification of the fluff. Rotary  
25 valve(s) 42 is provided for regulation of solids discharge and contributes to prevent combustible gas from leaking to the outer atmosphere. Screw-type conveyor 44 driven by motor 46 cools the ash and transfers it into receiving bin 48 for disposal.

30 A burner 49 is positioned generally horizontally through hood 36 with its nozzle 50 reaching the interior of reactor 18 in the manner shown and described with reference to Figure 2. Fuel gas and oxygen are fed to burner 49 through conduits 52 and 54.

35 From hood 36, the gases produced by reactor 18 are transferred through take off conduit 58 into a hot cyclone 60. The solid fine particles of fluff or soot 61

which may be entrained by the gases from reactor 18 are separated and are collected, cooled, and discharged into receiving bin 48.

A secondary burner 64, fed with oxygen/air and/or fuel gas, is positioned upstream of cyclone 60 for optional addition of air or oxygen to gasify any hydrocarbons or soot in the form of fine particles or gases which may reach that point.

The raw product gas flows through conduit 70 into a wet venturi scrubber 72 where entrained dust particles are removed. More preferably the raw product gas may be cooled, for example to 150°C, and passed through a bag house (with subsequent vitrification of the collected materials). The bag filter will even remove with collected dust the trace amounts (well under 1%) of the solidified more refractory hydrocarbon gases such as toluene, xylene, cumene, etc. that may survive in the product gas. The product gas then passes through packed bed tower 74 where acids (together with any benzene (C<sub>6</sub>H<sub>6</sub>) passing the bag filter) are removed by water wash. Emergency pressure control valve 76 is provided at purge line 78 to relieve excess pressure in the system should upset conditions occur. Solids collected by scrubber 72 are sent into sludge tank 80 forming a sludge 82.

Clean and cool product gas flows to compressor 84 through pipe 86, connected to a flare stack 98 provided with valve 100 for disposal of excess gas surges.

The product gas can be utilized for a variety of purposes. For example, the high quality clean product gas can produce mechanical power as a fuel for an internal combustion engine 88, or can be stored in tank 90 for later use (e.g. to be burned for its heat content), or used to produce electricity in a gas turbine generator 92, or to produce steam in boiler 94 or to be used as a reducing gas in a direct reduction process 96.

Referring now to the more detailed drawing of the gasification reactor 18 shown in Figure 2, the bed of material 102 to be gasified is formed in the reactor 18, and solids are caused to move from the charge end 103 to the discharge end 35 by tumbling action induced by rotation of reactor 18 and by the volumetric displacement of reacted solid ash in the bed 102 by unreacted and inert solids contained in the feed material delivered by auger feeder 20. The tumbling and mixing action of hot reacted and inert ash with fresh unreacted solids in the feed material greatly increases the rate of heat transfer in the bed 102 and thus enhances the rate and completeness of gasification of the raw feed material.

The depth of bed 102, and the retention time for feed material in reactor 18, are determined by the diameter and length of the reaction zone and are also relative to the length, diameter, and the angle of the slope of reactor 18 leading to discharge end 35.

A horizontal rotation axis is preferred among other reasons because the seals 120 and 122, located at the periphery of reactor 18 generally at its charge end 103 and discharge end 35, do not have to withstand excessive thrust or strain due to uneven distribution of the center of gravity of reactor 18. This also applies to the support rolls 26 and 28, which are of a simpler design and easier to maintain if reactor 18 rotates horizontally.

In one of the preferred embodiments, the shape of reactor 18 is an important feature of this invention because the hot volatile gases which evolve from the bed of material 102 must be brought immediately into contact with the extremely hot products of combustion ( $\text{CO}_2 + \text{H}_2\text{O}$ ) from burner 49, in order to more directly absorb the high temperature energy of the flame via the endothermic reactions of complex gases to form gases of simpler compounds. The shape and length of the flame from burner 49 is such that volatile gases which evolve from the bed

102', and over the entire length of reactor 18, react with the high temperature products of the combustion from burner 49.

Reactor 18 is provided with refractory lining 108 in the manner known in the art. Refractory lining 108 contributes to a uniform and efficient heating of bed 102 because the exposed portion of refractory lining 108 receives heat from the flame by radiation and also by convection. The lining 108 includes a typical intermediate insulation layer 107 (shown in Figure 3) as a thermal protection to the metallic shell 109 of the reactor 18. Uniform and efficient absorption of the high temperature energy from burner 49 by bed 102 also depends upon the rotation speed of reactor 18 and is necessary to prevent overheating of areas of bed 102 which are exposed directly to the heat of the flame, as well as to prevent overheating refractory lining 108. If uncontrolled overheating of bed 102 and/or refractory lining 108 should occur, fusion and/or melting and agglomeration of ash-to-ash and/or ash-to-refractory lining 108 could result in damage to refractory lining 108.

It has been found that the process can be adequately controlled by monitoring the heat in the reactor and making adjustments to keep the process operating within the preferred temperature range. This can be accomplished by two thermocouples, one positioned in the widest part of the reactor and the other in the throat of the discharge of the reactor. Two or more such on-board thermocouples are positioned to project through reactor wall and the refractory and are exposed to direct temperature of residue and atmospheric gases within the reactor.

A second burner 51 has been shown in dashed lines to illustrate an alternative embodiment having a plurality of burners. However, in the preferred embodiment only a single burner 49 is used.

Adjustable positioning of nozzle 50 of burner 49, shown in solid and dotted lines, inside reactor 18 is an important feature for optimal operation of the process. The preferred position of nozzle 50 will be such  
5 that an effective reaction between the gases evolved from bed 102 and the oxidants produced by the flame of burner 49 is accomplished. The flame causes a vortex near the discharge end 35 of reactor 18 and the gases evolving  
10 from bed 102 must pass by or through the influence zone of the flame. This arrangement results in the production of a high quality gas in a single reaction zone.

The discharge end 35 of reactor 18 is provided with a foraminous cylinder 110 for screening of fine and coarse solid particles of ash discharged from reactor 18.  
15 The fine particles 116 and coarse particles 118 are collected through conduits 112 and 114, respectively, for disposal or further processing.

Burner 49 in this preferred embodiment is operated stoichiometrically to minimize the direct  
20 oxidation of the material in bed 102 inside reactor 18.

Seals 120 and 122 are provided to substantially prevent uncontrolled introduction of atmospheric air into reactor 18. The design of seals 120 and 122 will be better appreciated with reference to Figure 3. The  
25 design of reactor 18, (shape, length and horizontal axis rotation), results in minimal thermal expansion, both axial and radial. Seals 120 and 122 are specifically designed to absorb both axial and radial expansion, as well as normal machine irregularities, without damage  
30 while maintaining a secure seal.

The seals comprise a static U-shaped ring 130 seen in cross section supported by annular disk plate 132 which closes off the end of the reactor space 138 and in turn is attached by flange 134 to the outer housing  
35 structure of the auger feeder 20. A fixed packing 136 is provided to ensure that no gas leaks from space 138 which

communicates with the interior of reactor 18 through annular space 140.

Two independent annular rings 142 and 144, made of stainless steel, are forced to contact the static U-shaped ring 130, by a plurality of springs 146. Rings 142 and 144 are fastened to supporting annular plate 148 to form an effective seal between ring 142 and plate 148 by conventional fasteners 150. Supporting plate 148 is securely attached to member 152 which forms part of or is fixed to the outer shell of reactor 18.

Springs 146 maintain the sealing surfaces of rings 142 and 144 against the surface of static ring 130, in spite of temperature deformations or wear.

#### EXAMPLE NO. 1

A pilot plant incorporating the present invention was operated during many trial runs. The rotating kiln reactor is on the order of 4.3 meters long by 2.4 meters wide (14 x 8 feet) at its widest point and is shaped generally and has accessory equipment as illustrated in Figure 1. The following data was obtained: Auto shredder waste from a shredder plant was fed to a rotary reactor as described in the present specification.

Typical analysis of the ASR material, (also called "fluff") which is the material remaining after metallic articles, such as auto bodies, appliances and sheet metal, are shredded and the metals are removed, is in weight percent as follows:

	Fiber	26.6%	Metals	3.3%
30	Fabric	1.9%	Foam	1.4%
	Paper	3.7%	Plastics	12.5%
	Glass	2.4%	Tar	3.6%
	Wood Splinters	1.4%	Wiring	1.3%
	Elastomers	3.3%	Dirt/Other	38.6%
35	<u>TOTAL = 100.0%</u>			

It should be understood, however, that actual analyses vary in a wide range due to the nature and

origin of this material. Depending on the shredding process, fluff contains a variable weight percentage of noncombustible (ash). Bulk density of fluff is approximately  $448 \text{ kg/m}^3$  ( $28 \text{ lb/ft}^3$ ). In general,

- 5 noncombustibles account for about 50% by weight and combustible or organic materials account for about 50%.

About 907 kg/hr (2000 lb/hr) of fluff were fed to the rotary furnace by means of the auger-type feeder after a period of heat-up of the reactor, so that its  
 10 interior temperature reached above  $650^\circ\text{C}$  ( $1202^\circ\text{F}$ ). During stable operation, the temperature in the reactor was more or less homogeneous and near  $700^\circ\text{C}$  ( $1292^\circ\text{F}$ ). Although the temperature of the flame may reach about  $3000^\circ\text{C}$  ( $5432^\circ\text{F}$ ), the endothermic reactions between the  
 15 gases evolved from the hot fluff and the oxidants ( $\text{CO}_2$  and  $\text{H}_2\text{O}$ ) produced by the burner cause the interior reactor temperature in the bed and adjacent internal atmosphere to stabilize at about  $700^\circ\text{C}$  ( $1292^\circ\text{F}$ ).

The reactor was set to rotate at about 1 r.p.m.  
 20 The burner was operated stoichiometrically using about 64.3 NCMH (2271 NCFH) of natural gas and 129 NCMH (4555 NCFH) of oxygen. A rate of 573 NCMH (20,235 NCFH) of good quality synthesis gas was obtained.

Typical analysis of the synthesis gas produced  
 25 is:

		<u>% Volume (dry basis)</u>
	$\text{H}_2$	33.50
	$\text{CO}$	34.00
	$\text{CH}_4$	8.50
30	$\text{CO}_2$	13.50
	$\text{N}_2$	5.50
	$\text{C}_2\text{H}_2$	0.75
	$\text{C}_2\text{H}_4$	3.50
	$\text{C}_2\text{H}_6$	<u>0.75</u>
35	<b>TOTAL:</b>	<b>100.00</b>

As can be readily observed, the product gas obtained contained 67.5% of reducing agents ( $\text{H}_2$  and  $\text{CO}$ ) and 13.5% of hydrocarbons which in some applications for  
 40 this gas, for example, in the direct reduction of iron ores, may undergo reformation in the direct reduction process and produce more reducing components ( $\text{H}_2 + \text{CO}$ ).

The heating value (HHV) of the product gas was about 3,417 Kcal/m<sup>3</sup> (384 BTU/ft<sup>3</sup>), which corresponds to a medium BTU gas and may be used for example to fuel an internal combustion machine, and certainly can be burned to produce steam or for any other heating purpose. As a comparison, the gas effluents from blast furnaces have a heating value of about 801 TO 1068 Kcal/m<sup>3</sup> (90 to 120 BTU/ft<sup>3</sup>) and even so are utilized for heating purposes in steel plants.

The amount of dry ash discharged from the reactor amounts to about 397 kg/hr (875 lb/hr) and additionally about 57 kg/hr (125 lbs/hr) were collected as sludge from the gas cleaning equipment.

The hot ashes collected directly from the reactor discharge port and from the hot cyclone are very low in "leachable" heavy metals, and consistently pass the TCLP tests without treatment. These ashes contain between eight and twelve percent recyclable metals, including iron, copper, and aluminum. The hot ashes are composed of iron oxides, silica, alumina, calcium oxide, magnesium oxide, carbon, and lesser amounts of other matter.

After removal of oversize metal pieces by screening, the remaining dry ash is environmentally safe for landfilling without further treatment. The toxicity analysis of the concentration of the eight RCRA metals in an extract obtained by TCLP tests is illustrated in the following table.

Metals	Regulatory Concentrations (mg/L)	*TCLP Test Results (mg/L)
Silver	5.0	< 0.01
Arsenic	5.0	< 0.05
Barium	100.0	5.30
Cadmium	1.0	< 0.01
Chromium	5.0	< 0.05
Mercury	0.2	< 0.001
Lead	5.0	< 0.02
Selenium	1.0	< 0.05

\* Toxicity Characteristics Leachate Procedure (per Resource Conservation & Recovery Act).

Dust solids collected from the gas scrubbing system are recovered as sludge and have been analyzed for the eight RCRA metals as illustrated in the following table:

Metals	Regulatory Concentrations (mg/L)	TCLP Test Results (mg/L)
Silver	5.0	< 0.01
Arsenic	5.0	0.06
Barium	100.0	3.2
Cadmium	1.0	0.78
Chromium	5.0	< 0.05
Mercury	0.2	< 0.001
Lead	5.0	4.87
Selenium	1.0	< 0.07

Several TCLP tests have been made and in each case the sludge materials have passed the test without additional treatment.

#### EXAMPLE NO. 2

The effectiveness of the seals which are described and claimed in this application, constituting an important feature of the present invention, can be seen comparing the results of two trial runs of the pilot plant (the first with a commercial seal installed and the other with a seal made as shown in Fig. 3).

	COMMERCIAL SEAL SCMH (SCFH)			FIGURE 3 SEAL SCMH (SCFH)		
Gases Produced (except N <sub>2</sub> )	574	(20,279)	64%	606	(21,408)	94%
Nitrogen	333	(11,753)	36%	36	(1,263)	6%
TOTAL Gas Produced	907	(32,032)	100%	642	(22,671)	100%

Although it has been found that about 3 percent of the nitrogen content in the final product gas is originated from the fluff material, it can be seen that an important decrease in the nitrogen content of the produced synthesis gas was made by the unique construction of the inventive seals, which contribute to gas produced having a higher quality and value.

EXAMPLE NO. 3

In order to assess the suitability of the synthesis gases produced according to this invention for the chemical reduction of iron ores, the following  
5 material balance was carried out running a computer simulation program specifically devised for said purpose.

The basis for calculations was 1 metric ton of metallic iron produced.

Although the reducing gas produced according to  
10 the present invention can be utilized by any of the known direct reduction processes. The material balance was calculated as applied to the HYL III process invented by employees of one of the Co-assignees of this application. Examples of this process are disclosed in U.S. patents  
15 3,765,872; 4,584,016; 4,556,417 and 4,834,792.

For an understanding of this example, reference can be made to Figure 1 where one of the applications shown is the direct reduction of iron ores, and to Table I showing the material balance.

20 926 Kg (2042 lb.) of fluff are gasified in reactor 18.

95 NCM (3354 NCF) of natural gas are fed to burner 49 along with 190 NCM (6709 NCF) of oxygen. Gasification of this amount of fluff produces 1,000 NCM  
25 (35,310 NCF) of raw hot reducing gas ( $F_1$ ) which after cleaning and cooling will reduce to 785 NCM (27,718 NCF) with the composition identified as  $F_2$ .

The thus clean reducing gas then is combined with about 1,400 NCM (49,434 NCF) of recycled gas  
30 effluent from the reduction reactor after being cooled by quench cooler 124 and divided as composition  $F_7$ .

The mixture of fresh reducing gas  $F_2$  and recycled gas  $F_7$  is then passed through a  $CO_2$  removal unit 126, which can be of the type of packed bed absorption towers  
35 using alkanolamines resulting in 1,876 NCM (66,242 NCF) with the composition of  $F_3$ , which clearly is a gas with high reductant potential, of the type normally used in

Direct Reduction processes. By means of unit 126, 297 NCM (10,487 NCF) of  $\text{CO}_2$  are removed from the system as gas stream  $F_{10}$ . The resulting gas stream  $F_3$  is then heated by heater 110 to about  $950^\circ\text{C}$  ( $1742^\circ\text{F}$ ) and is fed to the reduction reactor 104 as gas stream  $F_4$  to carry out the reduction reactions of hydrogen and carbon monoxide with iron oxides to produce metallic iron.

The gas stream effluent  $F_5$  from said reduction reactor 104 has consequently an increased content of  $\text{CO}_2$  and  $\text{H}_2\text{O}$  as a result of reactions of  $\text{H}_2$  and  $\text{CO}$  with the oxygen of the iron ore, therefore the effluent gas  $F_5$  is dewatered by cooling it in a direct contact water quench cooler 124 to give 1687 NCM (59,568 NCF) of a gas  $F_6$ . From gas  $F_6$  a purge  $F_8$  of 287 NCM (10,134 NCF) is split out and removed from the system to eliminate inerts (e.g.  $\text{N}_2$ ) from building up in the system and also for pressure control. The rest of the gas is recycled as described above as gas stream  $F_7$  (being combined with  $F_2$ , stripped of  $\text{CO}_2$ , and then fed to the reduction reactor as gas stream  $F_3$  having the composition shown in Table 1).

Optionally a cooling gas, preferably natural gas, can be circulated in the lower portion of the reactor in order to cool down the direct reduced iron (DRI) before discharging it.

To this end, about 50 NCM (1766 NCF) of natural gas  $F_9$  are fed to a cooling gas loop and circulated through the lower portion of the reduction reactor 104. The gas stream effluent from the cooling zone of said reactor is cooled and cleaned at quench cooler 106 and recirculated within said cooling loop.

TABLE 1

Material Balance of the HYL III D.R. Process (of Example 3)  
Using Synthesis Gas From Gasification of ASR Materials

	F <sub>1</sub>	F <sub>2</sub>	F <sub>3</sub>	F <sub>4</sub>	F <sub>5</sub>	F <sub>6</sub>	F <sub>7</sub>	F <sub>8</sub>	F <sub>9</sub>	F <sub>10</sub>
H <sub>2</sub> & Vol.	28	35	44	44	33	40	40	40	0.4	
CO	26	33	26	26	14	16	16	16	0.1	
CO <sub>2</sub>	11	14	0	0	11	13	13	13	0.4	100
CH <sub>4</sub>	7	10	16	16	13	16	16	16	93.7	
N <sub>2</sub>	4	5	12	12	11	14	14	14	0.5	
C <sub>3</sub> H <sub>8</sub>	0								4.6	
C <sub>4</sub> H <sub>10</sub>	0								0.3	
H <sub>2</sub> O	24	3	2	2	18	1	1	1		
Flowrate (NCM) Ton Fe	1,000	785	1,876	1,876	2,023	1,687	1,400	287	50	297
Temperature (°C)	500	30	40	950	639	30	30	30	25	30

**WE CLAIM:**

1. Method for gasifying organic materials in a primary reactor having a single reaction zone to produce a synthesis gas, said method comprising:
  - 5 feeding a charge of waste organic materials into a charge end of said reactor and continuously tumbling said waste organic materials in said reactor so as to form a bed in said reactor and move said bed toward a discharge end of said reactor;
  - 10 heating the waste organic materials sufficiently to volatilize, thermally decompose, and otherwise gasify hydrocarbons contained in the organic materials resulting in evolved gases and residual ash, by means of at least one high temperature burner gas stream
  - 15 above said bed formed by combustion with an oxygen-containing gas (1) of a fuel separate from said charge and suitable to produce CO<sub>2</sub> and/or H<sub>2</sub>O and (2) with said evolved gases when there is an excess of said oxygen-containing gas, said fuel and said oxygen-containing gas
  - 20 being in a ratio and at a volume such that the amount of said fuel is sufficient to keep the temperature of the bed and adjacent atmosphere within said primary reactor above 650°C and below the fusion temperature of the residual ash;
  - 25 continuously operating said at least one high temperature burner gas stream at the discharge end to provide sufficient energy and oxidizing combustion products within said primary reactor to react with the evolved gases in said primary reactor to yield the
  - 30 synthesis gas; and
  - discharging said residual ash and synthesis gas at the discharge end countercurrent to the burner gas stream such that said burner gas stream makes good contact with said evolved gases.
- 35 2. Method according to claim 1, wherein said combustion is substantially stoichiometric.

3. Method according to claim 1, wherein said oxidizing combustion products comprise  $H_2O$  and  $CO_2$ .

4. Method according to claim 3, wherein said charge has a moisture content of about 15% to about 50% and the burner has a fuel-to-oxygen ratio in excess stoichiometric sufficient to maintain the temperature in said primary reactor above  $650^{\circ}C$  and below the fusion temperature of the residual ash.

5. Method according to claim 4, wherein the burner has a fuel-to-oxygen ratio about 1:4.

6. Method according to claim 3, wherein said high temperature gas stream is generated with a flame at a temperature of from  $2500$  to  $3000^{\circ}C$ .

7. Method according to claim 3, wherein said synthesis gas produced is dewatered and stripped of  $CO_2$  and at least a portion of the latter is recycled through said burner or directly into said reactor.

8. Method according to claim 3, wherein said synthesis gas exits said primary reactor at a temperature above about  $650^{\circ}C$  and contains less than about two percent by volume of gases with molecular structure having more than two carbon atoms.

9. Method according to claim 8, further comprising maintaining the temperature of said synthesis gas exiting said primary reactor above  $650^{\circ}C$ ;

transferring said synthesis gas to a secondary reactor; increasing the temperature of said synthesis gas in the secondary reactor by contacting said synthesis gas with a finishing secondary gas stream injected therein;

said finishing gas stream being chosen from the group consisting of the product of a combustion of a fuel with a secondary oxygen-containing gas and a secondary oxygen-containing gas only, which latter is injected into the effluent synthesis gas from the primary reactor at a rate of up to about 5 percent on a volume basis relative to such effluent synthesis gas; and

the temperature of said synthesis gas is raised on the order of up to 50°C, and at least a portion of any carbon particles and complex hydrocarbon gases in said synthesis gas effluent from said primary reactor are  
5 reacted and/or dissociated preferentially into CO and H<sub>2</sub>.

10. Method according to claim 9, further comprising removing entrained particles remaining in said synthesis gas from said secondary reactor by subjecting said synthesis gas to cyclonic separation and wet scrubbing.

10 11. Method according to claim 9, wherein said finishing secondary gas stream is produced by combustion of a fuel with an oxygen-containing gas and is injected at a rate such that the temperature of said synthesis gas effluent from said primary reactor thereby is raised to  
15 above 700°C, and at least a portion of any remaining free carbon or complex hydrocarbon gases in said synthesis gas are reacted and/or dissociated preferentially into CO and H<sub>2</sub>.

12. Method according to claim 1, wherein the charge  
20 containing organic materials is selected from the group consisting of automotive shredder residue (ASR); garbage; municipal waste; plastic wastes; tire chips; motor oil; and residues derived from petrochemical, polymer and plastics industries other than those previously listed.

25 13. Method according to claim 1, wherein said heating is accomplished by a plurality of burners positioned and directed into said primary reactor such that said oxidizing combustion products contact said evolved gases such that said resulting synthesis gas  
30 contains less than two percent by volume of gases with a molecular structure having more than two carbon atoms.

14. Method according to claim 1, wherein said tumbling is accomplished by rotating said reactor about its horizontal axis; the charge containing organic  
35 materials is fed into said primary reactor at said charge end; and said residue is discharged from said primary

reactor by volumetric displacement through an opening at said discharge end by means of said tumbling.


15. Method according to claim 1, wherein said fuel for said primary reactor is partially or wholly comprised  
5 of said synthesis gas.

16. Method according to claim 1, wherein said fuel is selected from the group consisting of natural gas, synthesis gas, fuel oil, and coal.

17. Method according to claim 1, further comprising  
10 using the synthesis gas in the direct reduction of iron ore.


18. Method according to claim 12, wherein iron ore is reduced by a hydrogen and carbon monoxide containing reduction gas in a reducing zone and the resulting spent  
15 reducing gas is recirculated with dewatering and CO<sub>2</sub> removal prior to reintroduction into the reducing zone, said synthesis gas being itself dewatered and added to the recirculation loop at least prior to the CO<sub>2</sub> removal.

19. Method according to claim 1, wherein at least a  
20 portion of the CO<sub>2</sub> removed from the spent reducing gas is recycled through said burner or directly into said reactor.





**FIG.3**



## INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 96/09628

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 C10J3/06 C10J3/14 C10J3/66

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 C10J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 568 997 (PROLER ENVIRON. SERVICE) 10 November 1993 cited in the application see page 10-11; claims 1-21 ---	1-19
A	GB,A,227 880 (HARALD NIELSEN) 19 February 1925 see page 1, line 11 - page 2, line 47 see page 3, line 43 - page 5, line 55 ---	1-3
A	US,A,4 295 331 (REKANT) 20 October 1981 see column 6; claims 1-6 ---	1,19
A	GB,A,2 087 424 (FOSTER WHEELER POWER) 26 May 1982 see page 1, line 1-113 ---	1-3,12
	-/--	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

## \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

16 September 1996

Date of mailing of the international search report

25.09.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+ 31-70) 340-3016

Authorized officer

Wendling, J-P

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/US 96/09628

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB,A,1 437 845 (CHEVRON RES.) 3 June 1976 see page 2, line 49 - page 4, line 5 ---	1-3,9, 10,12
A	EP,A,0 153 235 (FRAMATOME) 28 August 1985 see page 8-9; claims 1-7 ---	1,9
A	GB,A,2 099 014 (ALLIS-CHALMER) 1 December 1982 -----	

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 96/09628

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-568997	10-11-93	CA-A- 2095665 JP-A- 6073384 US-A- 5425792	08-11-93 15-03-94 20-06-95
GB-A-227880		NONE	
US-A-4295331	20-10-81	NONE	
GB-A-2087424	26-05-82	NONE	
GB-A-1437845	03-06-76	NONE	
EP-A-153235	28-08-85	FR-A- 2559776 AU-B- 578660 AU-A- 3893285	23-08-85 03-11-88 22-08-85
GB-A-2099014	01-12-82	US-A- 4374650 AU-B- 545077 AU-A- 8342082 CA-A- 1169657 DE-A- 3216836 FR-A- 2505864 JP-A- 58001791 SE-B- 453099 SE-A- 8202808 SU-A- 1114342	22-02-83 27-06-85 25-11-82 26-06-84 02-12-82 19-11-82 07-01-83 11-01-88 19-11-82 15-09-84